



SPECIFICATION

• Supplier : Samsung electro-mechanics • Samsung P/N : CL31A335KPHNNNE

• Product : Multi-layer Ceramic Capacitor • Descriptiont : CAP, 3.3 µF, 10V, ±10%, X5R, 1206

A. Samsung Part Number

<u>CL</u> <u>31</u> <u>A</u> <u>335</u> <u>K</u> <u>P</u> <u>H</u> <u>N</u> <u>N</u> <u>N</u> <u>E</u> ① ② ③ ④ ⑤ ⑥ ⑦ ⑧ ⑨ ⑩ ⑪

1	Series	Samsung Multi-layer Ceramic Capacitor								
2	Size	1206 (inch d	code)	L: 3.2	± 0.2	mm	W:	1.6	± 0.2	mm
③	Dielectric	X5R		8	Inner e	lectrode		Ni		
4	Capacitance	3.3 µF			Termin	ation		Cu		
(5)	Capacitance	±10 %			Plating			Sn 10	00%	(Pb Free)
	tolerance			9	Produc	t		Norm	al	
6	Rated Voltage	10 V		10	Specia	l		Rese	rved for	future use
7	Thickness	1.6 ± 0.2	mm	11	Packag	jing		Embo	ssed T	ype, 7"reel(2,000ea)

B. Samsung Reliability Test and Judgement condition

	Performance	Test condition					
Capacitance	Within specified tolerance	1kl½±10% 1.0±0.2Vrms					
Tan δ (DF)	0.05 max.						
Insulation	More than 100Mohm⋅ <i>μ</i> F	Rated Voltage 60~120 sec.					
Resistance							
Appearance	No abnormal exterior appearance	Visual inspection					
Withstanding	No dielectric breakdown or	250% of the rated voltage					
Voltage	mechanical breakdown						
Temperature	X5R						
Characterisitcs	(From -55℃ to 85℃, Capacitance change should be within ±15%)						
Adhesive Strength	No peeling shall be occur on the	500g·F, for 10±1 sec.					
of Termination	terminal electrode						
Bending Strength	Capacitance change: within ±12.5%	Bending to the limit (1mm)					
		with 1.0mm/sec.					
Solderability	More than 75% of terminal surface	SnAg3.0Cu0.5 solder					
	is to be soldered newly	245±5℃, 3±0.3sec.					
		(preheating : 80~120 ℃ for 10~30sec.)					
Resistance to	Capacitance change: within ±7.5%	Solder pot : 270±5℃, 10±1sec.					
Soldering heat	Tan δ, IR : initial spec.						

	Performance	Test condition					
Vibration Test	Capacitance change : within ±5%	Amplitude : 1.5mm					
	Tan δ, IR : initial spec.	From 10Hz to 55Hz (return : 1min.)					
		2hours × 3 direction (x, y, z)					
Moisture	Capacitance change: within ±12.5%	With rated voltage					
Resistance	Tan δ : 0.075 max	40±2℃, 90~95%RH, 500+12/-0 hours					
	IR ∶ More than 25‰· <i>μ</i> F						
High Temperature	Capacitance change: within ±12.5%	With 200% of the rated voltage					
Resistance	Tan δ : 0.075 max	Max. operating temperature					
	IR ∶ More than 50MΩ· <i>μ</i> F						
		1000+48/-0 hours					
Temperature	Capacitance change: within ±7.5%	1 cycle condition					
Cycling	Tan δ, IR : initial spec.	Min. operating temperature → 25 °C					
		→ Max. operating temperature → 25°C					
		5 cycles test					

C. Recommended Soldering method:

Reflow (Reflow Peak Temperature : 260+0/-5 $^{\circ}$ C, 10sec. Max)

^{*} For the more detail Specification, Please refer to the Samsung MLCC catalogue.