


## VinylSTAT VMC / VMD

### Homogeneous Vinyl Mat

#### Homogenous ESD work surface matting

A homogeneous polymer mix construction with unsurpassed electrical properties, gives VinylSTAT C a consistent, controlled static drain and physical properties with highest level of protection. VinylSTAT D is made with the same homogeneous polymer mix as the VinylSTAT C but 0.0625" thick.

Resistant to degradation by inorganic acids, organic acids, reducing agents, detergent solutions, alcohols, aliphatic hydrocarbons, mineral oil, amines, and aldehydes.



#### Features

- Homogenous ESD Table Mat
- Surface resistivity is  $10^7 - 10^8$ .
- Blue or Gray
- Available in rolls or an assortment of lengths.

#### Applications:

**Creates an ESD safe work area by a providing a path-to-ground for electrical charges as well as protecting the work surface from damage.**

#### Specifications:

Color	(Blue, Gray)
Emboss Pattern	KidGrain
Gauge	VinylStat C: 0.093" VinylStat D: 0.0625"
Tensile	350 lb/in <sup>2</sup> minimum
Elongation	110% minimum
Tear	80 lb/in minimum
Durometer	85 + 5 (Shore A)
RTT	$1.0 \times 10^7 - 7^8 \Omega/\text{sq}$
Static Decay	<0.01 seconds
Suggested Service Temperature	-20o F to + 160o F (2)

#### Part Numbers:

VMC 2450B:	2' x 50', Blue, Solid vinyl roll
VMC 3050B:	30" x 50', Blue, Solid vinyl roll
VMC 3650B:	3' x 50', Blue, Solid vinyl roll
VMC 4850B:	4' x 50', Blue, Solid vinyl roll
VMD 2450B:	2' x 50', Blue, Solid vinyl roll
VMD 3050B:	30" x 50', Blue, Solid vinyl roll
VMD 3650B:	3' x 50', Blue, Solid vinyl roll
VMD 4850B:	4' x 50', Blue, Solid vinyl roll

\*Specify (GY) in place of (B) for GRAY

This document is prepared for our customers as a service, and is to the best of our knowledge true and accurate. However, it is understood and agreed by the users of this document that we will accept no liability for the conclusions reached. Users of this document may therefore wish to perform additional testing before determining that products mentioned are suitable.