

LOCTITE 3900

September 2014

PRODUCT DESCRIPTION

LOCTITE 3900 provides the following product characteristics:

Technology	Acrylic
Chemical Type	Acrylic resin
Appearance (uncured)	Transparent, colorless to slightly amber solution ^{LMS}
Components	One component - requires no mixing
Cure	Room temperature cure
Application	Conformal coating
Specific Benefit	<ul style="list-style-type: none">• High dielectric strength• Fast drying• Precision spray nozzle• Contains no CFC's

LOCTITE 3900 is a clear acrylic formulated without chlorinated solvents or CFC's. The coating is spray-applied and air dries tack-free in five minutes to provide a tough environmental and solvent-resistant coating. The material provides protection of printed circuit boards, electronic components, thick-film circuits and other substrates. This product is typically used in applications with an operating range of -40 °C to +125 °C.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C 1.14
Flash Point - See SDS

TYPICAL PROPERTIES OF CURED MATERIAL**Physical Properties**

Water Vapor Trans. Rate, ASTM E96, g/(h·m ²)	0.325
Shore Hardness, ISO 868, Durometer D	60
Elongation, ISO 527-3, %	1.5
Tensile Strength, ISO 527-3	N/mm ² 5.9 (psi) (850)
Tensile Modulus, ISO 527-3	N/mm ² 586 (psi) (85,000)

Electrical Properties

Volume Resistivity, IEC 60093, Ω·cm	7.21×10 ¹⁵
Surface Resistivity, IEC 60093, Ω	1.88×10 ¹⁷
Dielectric Breakdown Strength, IEC 60243-1, kV/mm	65
Dielectric Constant / Dissipation Factor, IEC 60250:	
100 Hz	3.37 / 0.062
1 kHz	3.07 / 0.052

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for use:

1. Surface should be free of flux, grease, ionic residue or any other contaminates. Mask board if required.
2. Shake can thoroughly before use.
3. Spray board 15 to 20 cm from surface with even motion.
4. Rotate board and repeat application 2-3 times for best coverage.
5. Application with PCB in horizontal position recommended for even coating.
6. A coating of 0.05 to 0.07 mm will air dry tack-free within 5 minutes @ 22 °C and 40 to 60 %RH. Full cure requires 24 hours @ 22 °C.
7. Cured coatings may be removed by soaking in acetone. Component replacement may be accomplished by localized desoldering/soldering through the coating and reapplication.

Loctite Material Specification^{LMS}

LMS dated April 26, 2001. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties. Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

(°C x 1.8) + 32 = °F
kV/mm x 25.4 = V/mil
mm / 25.4 = inches
µm / 25.4 = mil
N x 0.225 = lb
N/mm x 5.71 = lb/in
N/mm² x 145 = psi
MPa x 145 = psi
N·m x 8.851 = lb·in
N·m x 0.738 = lb·ft
N·mm x 0.142 = oz·in
mPa·s = cP

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.2