

Technical Data Sheet

Rev. D (3/21) Page 1 of 2

Fine-L-Kote HT High-Temp Silicone Conformal Coating

Product# 2106

Product Description

High Temperature Silicone Coating is designed to prevent thermal breakdown at high temperatures. Silicone Conformal Coating is the most universal coating, offering protection for a wide variety of environments.

Features / Benefits

- Designed for high temperature environments
- Fast-drying silicone 1-step process
- Thermal resistance to 662°F (350°C)
- Dielectric strength 560 volts/mil
- IPC-CC-830B Certified
- UL94 V-0 rated
- Moisture resistant
- Vibration resistant flexible
- UV indicator for black light inspection

Usage Instructions

For industrial use only. Read MSDS carefully prior to use. Before applying Fine-L-Kote $^{\text{TM}}$ conformal coatings, clean circuit boards to remove contamination and allow to dry. Cleaning may be performed with Techspray G3, E-LINETM and Precision-V defluxers.

Spray Application: Apply top to bottom, allowing coating to flow evenly around components. Rotate PCB 90° and repeat application. Rotate and apply coating two additional times, then allow board to cure. If additional thickness is desired, apply additional coatings. When using liquid spray with automatic dispensing equipment, adjustments may be required in application rate and viscosity.

Dip Application: Using automatic equipment or hand immersion technique, slowly immerse PCB into the coating and remove slowly. Use an average rate of approximately 1 foot per minute. After allowing the board to cure, process may be repeated to achieve desired thickness.

Brush Application: Evenly apply coating to areas desired at thickness required. Allow time for curing before reapplying to achieve a thick coating. Use WonderMASK to protect components during conformal coating process. After application, cured Fine-L-KoteTM may be removed using Techspray Conformal Coating Removal Pen (2510-N or 2510-P).



Typical Product Data and Physical Properties

**	•	
Physical State:	Liquid	
Odor:	Aromatic odor	
Color:	Colorless	
Percent volatile:	80	
Vapor Density:	>1 (Air=1)	
Boiling Point:	230ºF (110ºC)	
Flashpoint and method:	40ºF (TAG CC)	
Solubility in water	Insoluble	
Density:	0.92	
VOC:	724 g/L	
Shelf life:	1 year	



Technical Data Sheet

Rev. D (3/21) Page 2 of 2

Fine-L-Kote HT High-Temp Silicone Conformal Coating

Product# 2106

Performance & Application Data

Cure type	Thermal/air
Tack-free time (min)	45
Accelerated cure time/temp	1 Step: 15 Min. @ 49 °C
Ambient cure time	24 hr.
Viscosity (bulk)	10-30 cps
Operating temperature range	-40° to 350°C
Dielectric strength	560 V/Mil
Insulation resistance (ohms)	1.33 x 10 ¹⁶
Coverage (1 mil dry film)	1 aerosol can = 20ft² (1.9M²) 1 gal. liquid = 880ft² (81.8M²)

Packaging and Availability

2106-12S 12oz. Liquid **2106-G** 1 Gallon Liquid

Environmental Policy

Techspray® is committed to developing products to ensure a safer and cleaner environment. We will continue to meet and sustain the regulations of all federal, state and local government agencies.

Resources

Techspray® products are supported by global sales, technical and customer services resources.

For additional technical information on this product or other Techspray® products in the United States, call the technical sales department at 800-858-4043, email tsales@techspray.com or visit our web site at: www.techspray.com.

Important Notice to Purchaser/User: The information in this publication is based on tests that we believe are reliable. The results may vary due to differences in tests type and conditions. We recommend that each user evaluate the product to determine its suitability for the intended application. Conditions of use are outside our control and vary widely. Techspray's only obligation and your only solution is replacement of product that is shown to be defective when you receive it. In no case will Techspray® be liable for any special, incidental, or consequential damages based on breach of warranty, negligence or any other theory.



tsales@techspray.com

China