



# **SPECIFICATION**

(Reference sheet)

- Supplier : Samsung electro-mechanics - Samsung P/N: CL05A104KA5NNNC

Product : Multi-layer Ceramic Capacitor


Description : CAP, 100nF, 25V, ±10%, X5R, 0402

## A. Samsung Part Number

<u>CL</u> <u>05</u> <u>A</u> <u>104</u> <u>K</u> <u>A</u> <u>5</u> <u>N</u> <u>N</u> <u>N</u> <u>C</u> 1 2 3 4 5 6 7 8 9 10 11

1	Series	Samsung Multi-layer Ceramic Capacitor					
2	Size	0402 (inch code)	L: 1.00	± 0.05 mm	W:	$0.50 \pm 0.05$ mm	
3	Dielectric	X5R	8	Inner electrode		Ni	
4	Capacitance	100 nF		Termination		Cu	
(5)	Capacitance	±10 %		Plating		Sn 100% (Pb Free)	
	tolerance		9	Product		Normal	
6	Rated Voltage	25 V	10	Special		Reserved for future use	
7	Thickness	$0.50 \pm 0.05$ mm	11)	Packaging		Cardboard Type, 7" reel	

#### **B. Structure & Dimension**



Samsung P/N	Dimension(mm)					
Samsung F/N	L	W	Т	BW		
CL05A104KA5NNNC	1.00 ± 0.05	0.50 ± 0.05	0.50 ± 0.05	0.25 ± 0.10		

### C. Samsung Reliablility Test and Judgement Condition

	Judgement	Test condition
Capacitance	Within specified tolerance	1 kHz ±10% / 1.0±0.2Vrms
Tan δ (DF)	0.035 max.	*A capacitor prior to measuring the capacitance is heat treated at $150^{\circ}\text{C} + 0/-10^{\circ}\text{C}$ for 1 hour and maintained in ambient air for 24±2 hours.
Insulation	10,000Mohm or 100Mohm× <i>μ</i> F	Rated Voltage 60~120 sec.
Resistance	Whichever is smaller	
Appearance No abnormal exterior appearance		Microscope (x10)
Withstanding	No dielectric breakdown or	250% of the rated voltage
Voltage	mechanical breakdown	
Temperature	X5R	
Characteristics	(From-55℃ to 85℃, Capacitance change sl	hould be within ±15%)
Adhesive Strength	No peeling shall be occur on the	500g·f, for 10±1 sec.
of Termination	terminal electrode	
Bending Strength	Capacitance change: within ±12.5%	Bending to the limit (1mm)
		with 1.0mm/sec.
Solderability	More than 75% of terminal surface	SnAg3.0Cu0.5 solder
	is to be soldered newly	245±5°C, 3±0.3sec.
		(preheating: 80~120°C for 10~30sec.)
Resistance to	Capacitance change : within ±7.5%	Solder pot : 270±5°C, 10±1sec.
Soldering Heat	Tan δ, IR : initial spec.	
Vibration Test	Capacitance change : within $\pm$ 5% Tan $\delta$ , IR : initial spec.	Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z)
Moisture	Capacitance change: within ±12.5%	With rated voltage
Resistance	Tan δ: 0.05 max	40±2°C, 90~95%RH, 500+12/-0hrs
	IR: 500Mohm or 12.5Mohm × $\mu$ F	
	Whichever is smaller	
High Temperature	Capacitance change: within ±12.5%	With 150% of the rated voltage
Resistance	Tan δ: 0.05 max	Max. operating temperature
	IR: 1,000Mohm or 12.5Mohm × $\mu$ F	1000+48/-0hrs
	Whichever is smaller	
Temperature	Capacitance change: within ±7.5%	1 cycle condition
Cycling	Tan δ, IR : initial spec.	Min. operating temperature → 25°C
		→ Max. operating temperature → 25°C
		5 cycle test

X The reliability test condition can be replaced by the corresponding accelerated test condition.

## D. Recommended Soldering method:

Reflow ( Reflow Peak Temperature : 260+0/-5°C, 10sec. Max )



A Product specifications included in the specifications are effective as of March 1, 2013.

Please be advised that they are standard product specifications for reference only.

We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications,

please contact our sales personnel or application engineers.