

# G3380NA/NB/NC

## Non-Silicone Thermal Grease Series

Non-Silicone Thermal Compound G3380N is made of non-silicon resin material and pollution of optical surfaces. Low thermal resistance and great thermal conductivity. G3380N has been used extensively in Consumer electronics and Microprocessors for their thermal control techniques. The grease can cover several coats on the component interface. When the component's temperature rises, the grease stickiness will decrease, which can moisten the interface components.

### ■ FEATURES

- / Thermal conductivity: 1.3 / 3.2 / 4.5 W/m\*K
- / No outgassing
- / Low thermal impedance

### ■ TYPICAL APPLICATION

- / CPU and chip coolers
- / Switching power supplies
- / LED appliance
- / Between any heat-generating component and heat sink

### ■ CONFIGURATIONS

- / Cartridges: 50ml
- / Tinplate Can:1kg
- / Other special and custom sizes are available upon request

### ■ PRESERVATION

It can be preserved for 60 months under the condition of unopened and under room temperature 25°C.

### ■ TYPICAL PROPERTIES

PROPERTY	G3380NA	G3380NB	G3380NC	TEST METHOD	UNIT
Color	White	Gray	Gray	Visual	-
Resin base	Non-Silicone	Non-Silicone	Non-Silicone	-	-
Filler	Non-Metal	Metal	Metal	-	-
Viscosity	96	43	93	ISO 3219	Pa.s
Density	2.2	1.9	2.1	ASTM D792	g/cm <sup>3</sup>
Application temperature	-60~150	-60~150	-60~150	-	°C
Bond line thickness	55	33	30	-	µm
Shelf life	60 months	60 months	60 months	-	-
ROHS & REACH	Compliant	Compliant	Compliant	-	-
<b>ELECTRICAL</b>					
Dielectric breakdown	14	N/A	N/A	ASTM D149	KV/mm
Volume resistivity	>10 <sup>11</sup>	N/A	N/A	ASTM D257	Ohm-m
<b>THERMAL</b>					
Thermal conductivity	1.3	3.2	4.5	ASTM D5470	W/m*K
Thermal impedance@50psi	0.05	0.03	0.02	ASTM D5470	°C-in <sup>2</sup> / W
Thermal impedance@50psi	32.2	22.5	12.9	ASTM D5470	°C-mm <sup>2</sup> / W



Note: All specifications provided by LiPOLY are subject to change without notice. The test methods used by LiPOLY are based on the TIM Tester method and ASTM D5470 test method. These test methods are used as the definition standards for LiPOLY. Property values provided in this document are not for product specifications or guaranteed. This document does not guarantee the performance and quality required for the purchaser's specific purpose. The purchaser needs to evaluate and verify the safety before using the material. We strongly recommend the purchaser pre-test the product and verify the performance of the product under the purchaser's specific conditions. Liability and use of the product are the responsibility of the end user. LiPOLY makes no warranty as to the suitability, merchantability, or non-infringement of any LiPOLY material or product for any specific or general uses. LiPOLY shall not be liable for incidental or consequential damages of any kind. All LiPOLY products are sold in accordance with the LiPOLY Terms and Conditions in effect at the time of purchase and a copy of which will be furnished upon request. All rights reserved, including LiPOLY trademarks or registered trademarks of LiPOLY or its affiliates. Statements concerning possible or suggested uses made herein shall not be relied upon or be construed as a guaranty of patent infringement. Copyright 2022 LiPOLY.