

SILTEL SG-TC6.0

Thermally Conductive Gap Filler Pad

Thermal Conductivity: 6.0 W/m-K

SILTEL SG-TC6.0 is an electrically insulating thermally conductive silicone gap filler material ideal for use in applications where thermal transfer over large gaps (large tolerances) or different stack ups must be achieved. Due to the specific formulation and ceramic particle filler, SG-TC6.0 demonstrates VERY high thermal conductivity through it's compliable feature and overall elastomer design within a range of pressures.

Through SG-TC6.0's softness, the pad perfectly mates to irregular surfaces thus filling gaps and operates at low pressure offering low thermal resistance. SG-TC6.0 offers a few different tack configurations with either its standard natural tack both sides or single side tack option.

SILTEL SG-TC6.0 is available in sheets or TIMTEL cut parts to match a wide range of industry standard or customer defined outlines.

- Excellent Thermal Conductivity of 6.0 W/m-K
- Soft and Compliant Pad Design
- Excellent Chemical Resistance and Stability
- Operates at Low Pressure
- Shock Absorbing
- Standard Tack Both Sides or Single Side Tack

Standard SILTEL SG-TC6.0 Cross Section

Standard Tack Both Sides (Optional Single Side Tack)



SG-TC6.0: Standard Tack Both Sides

SG-TC6.0-A1: Optional Single Side Tack

Typical Applications

- SMD Packages
- Through-hole Vias
- RDRAMs Memory Modules
- Capacitors
- Interfaces with Large Gaps / Tolerances
- Electronics to Heat Pipe Assemblies



Standard Thickness Options

- SG.50-TC6.0.....0.020" (0.50mm)
- SG1.0-TC6.0.....0.039" (1.00mm)
- SG2.0-TC6.0.....0.078" (2.00mm)

SG-TC6.0 General Properties

Thermal Conductivity.....6.0 W/m-K
 Color..... Gray
 Hardness.....55 (Shore 00)
 Dielectric Strength.....10 kV/mm
 Volume Resistivity.....1 x 10¹³
 Operating Temperature.....-60°C to 180°C

Characteristic	SILTEL SG-TC6.0
Base Material	Ceramic Filled Silicone
Substrate	NONE
Color	Gray
Available Formats	Sheets or Cut Pads
Standard Sheet Sizes	18.11" x 3.940" (460mm x 100mm)
TIMTEL Cutting Capabilities	Razor Plotter Cut for Gap Filler Pads
TIMTEL Die Cut Delivery Formats	Individuals or Multiples per Master Sheet
TIMTEL Die Cut Dimensional Tolerances	0.010"(0.25mm) to 0.020"(0.51mm) (depending on thickness)
Storage	Cool, dry location at or below 80F/ 27C
Shelf Life	2 years from date of manufacture

0.020" / 0.50mm Thermal Resistance

Thermal Impedance @ 10 PSI.....0.190 °C in² / Watt
 Thermal Impedance @ 30 PSI.....0.180 °C in² / Watt
 Thermal Impedance @ 60 PSI.....0.160 °C in² / Watt

0.039" / 1.00mm Thermal Resistance

Thermal Impedance @ 10 PSI.....0.350 °C in² / Watt
 Thermal Impedance @ 30 PSI.....0.310 °C in² / Watt
 Thermal Impedance @ 60 PSI.....0.260 °C in² / Watt

0.078" / 2.00mm Thermal Resistance

Thermal Impedance @ 10 PSI.....0.560 °C in² / Watt
 Thermal Impedance @ 30 PSI.....0.490 °C in² / Watt
 Thermal Impedance @ 60 PSI.....0.410 °C in² / Watt

Thermal material evaluation is always critical when designing in a new material or developing a new product. These sheet samples of SILTEL are intended to determine the optimal SILTEL thickness as well as overall material construction and performance best suited within the scope of your application requirements.

Please contact us for more information on how to order specific sizes and shapes for your final design requirements.

TIMTEL
 Thermal Management Materials

Supplied By:

