

Technical Data Sheet

Product Description

CR Technology offers a wide variety of thermally conductive pads also known as gap fillers. These materials are available in both silicone and non-silicone formulations. EVERTHERM pads offer an endless range of thermal conductivity, softness and thickness options to easily solve any heat related issue. EVERTHERM pads are naturally tacky and can be cut to any size or shape for easy installation. EVERTHERM pads are designed and engineered to achieve the highest level of thermal management to protect today's most advanced electronics.





Material Properties

- High thermal conductivity
- Excellent flame retardant
- Good electrical insulation performance
- Good flexibility and high compression ratio

EVSF500			
Color			
Thickness	1.0mm		
Specific Gravity			
Thermal Conductivity			
Hardness (Shore OO)	30 - 90		
Elongation	40%		
Tensile Strength	30psi		
Electrical Strength	>8000V/mm		ASTM D149
UL Flammability Rating			
Volume resistivity	1*101 ³ Ω.cm		
Operating Temperature	−50 - 200°C		
Thermal Resistance(1mm,@40psi)	0.45℃*in2/W		
Compression Ratio(1mm,@40psi)	30%		
Dielectric Constant 1MHz	7.5		
RoHS (10)			
Halogen (4)			
REACH (191)			
Standard Sheet Size	200mm x 300mm		

(Note: Other sheet sizes may be available upon request.)

Test fixtures using ASTM D5470. Recorded values include interface thermal resistance. These values are for reference only. The actual application performance is directly related to the applied surface roughness, flatness and pressure.





EVSF500

Applications

- ✓ Semiconductor heat sink
- ✓ Electric Vehicle (EV) Batteries
- Ocommunication & power devises & modules
- ✓ LED lighting equipment
- Section Components like:

LEDs, CPUs, MOS • Mobiles, Laptops, Tablets

Thermal Resistance VS Pressure 3.50 Thermal Resistance-1mm 3.00 **Thermal Resistance-2mm** Thermal Resistance (C4in/V) 2.50 2.00 1.50 1.00 0.50 0.00 10 20 30 40 50 60 70 **Pressure (Psi) CR Technology, Inc** 55 Chase St. Methuen, Massachusetts 01844 Technology sales@crtechinc.com 978.681.5300

Note: The information provided herein is accurate at time of publication. It is the responsibility of the end-user to confirm compliance to their application. All test data is typical. Therefore, these recommendations and data are for reference only and not as a product warranty.