

Techclean Wiper

Product# 2350

Product Description

Hydro entangled cellulose/polyester wipe with high absorbency and extra low particulate count and no chemical extractable.

Features / Benefits

- Class 100 cleanroom qualified
- High absorbency
- Very low particulate count

Physical Properties

Fabric Weight (g/sq-m):	69
Extrinsic Sorbency (ml/sq-m):	282

Extractable Ions in Deionized Water (ppm)

Chloride:	29.60
Bromide	0.88
Fluoride	0.88
Sodium:	45.00
Potassium:	5.80
Magnesium:	0.98
Ammonium	0.88
Calcium:	2.50
Lithium	0.98
Sulfate	35.00
Nitrate	1.31
Nitrite	0.88
Phosphate	1.20

Non-Volatile Residue (g/sq-m)

Deionized Water:	0.053
Isopropyl Alcohol:	0.015

Particle Generation (ASTM E2090)

.5 - 5 $\mu\text{m} / \text{m}^2$	86,000,000
5-100 $\mu\text{m} / \text{m}^2$	6,019,365
>100 $\mu\text{m} / \text{m}^2$	187,499
Cumulative	92,206,864



Packaging and Availability

2350-100	100 – 8" x 10" (20cm x 25cm) c-fold wipes, double-bagged 12 bags/case
----------	---

Environmental Policy

Techspray® is committed to developing products to ensure a safer and cleaner environment. We will continue to meet and sustain the regulations of all federal, state and local government agencies.

Resources

Techspray® products are supported by global sales, technical and customer services resources.

For additional technical information on this product or other Techspray® products in the United States, call the technical sales department at 800-858-4043, email tsales@techspray.com or visit our web site at: www.techspray.com.

Important Notice to Purchaser/User: The information in this publication is based on tests that we believe are reliable. The results may vary due to differences in tests type and conditions. We recommend that each user evaluate the product to determine its suitability for the intended application. Conditions of use are outside our control and vary widely. Techspray's only obligation and your only solution is replacement of product that is shown to be defective when you receive it. In no case will Techspray® be liable for any special, incidental, or consequential damages based on breach of warranty, negligence or any other theory.