SPECIFICATION CONTROL DRAWING

CHEMINAX

.063

.079

50 OHM, AWG 26, 7 STRANDS OF AWG 34, COAXIAL CABLE, OUTER SPACE USE
 Date
 3-7-08

 Revision
 C

5026S1614

THIS SPECIFICATION SHEET FORMS A PART OF THE LATEST ISSUE OF RAYCHEM SPECIFICATION 1200


CONSTRUCTION DETAILS

ELECTRICAL CHARACTERISTICS

DIMENSIONS ARE NOMINAL VALUES IN INCHES UNLESS OTHERWISE DESIGNATED.

C.A.

CHARACTERISTIC IMPEDANCE 50 ± 2 ohms, Method A CAPACITANCE 26.7 pF/ft. (nominal) VELOCITY OF PROPAGATION 76% (nominal)



SHIELD

JACKET

Radiation-Crosslinked,

Modified ETFE

AWG 38,

Tin-Coated Copper

ADDITIONAL REQUIREMENTS

ELECTRICAL

CONDUCTOR RESISTANCE 43.9 ohms/1000 ft. (nominal)

INSULATION RESISTANCE 10,000 megohms (minimum) for 1000 ft.

JACKET FLAWS

SPARK TEST 1.0 kV (rms)
IMPULSE TEST 6.0 kV (peak)

VOLTAGE WITHSTAND (DIELECTRIC) 1000 volts (rms) (minimum)

ENVIRONMENTAL

FLAMMABILITY Method B HEAT SHOCK 225°C

LOW TEMPERATURE-COLD BEND -55°C/2.25 inch mandrel

VOLTAGE WITHSTAND

(Post Environmental) 1000 volts (rms), 1 minute

PHYSICAL

INSULATION (DIELECTRIC)

(Prior to Cabling)

ELONGATION 50% (minimum)
TENSILE STRENGTH 1000 lbf/in² (minimum)

JACKET

ELONGATION 50% (minimum)
TENSILE STRENGTH 5000 lbf/in² (minimum)

JACKET THICKNESS .008 inch (nominal)

SHIELD COVERAGE 90% (minimum)

WEIGHT 5.5 lbs/1000 ft. (nominal)

Outer jacket color will be white (designated by a "-9" appended to the part number, e.g. 5026S1614-9) unless otherwise

Designate outer jacket color with a dash number in accordance with MIL-STD-681. Other codes and suffixes may be added to the part number, as necessary, to capture any additional requirements imposed by the purchase order.

OUTER SPACE REQUIREMENTS

RADIATION RESISTANCE 500 megarads/2.25 inch mandrel

VACUUM STABILITY

TOTAL MASS LOSS (TML) 1.00% (maximum) VOLATILE CONDENSABLE 0.10% (maximum)

MATERIAL (VCM)

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

The TE logo, Tyco Electronics, Cheminax, Raychem and Rayfoam are trademarks.

