

**BRADY B-362 THERMAL TRANSFER PRINTABLE TAMPER-RESISTANT METALLIZED VINYL LABEL STOCK**

TDS No. B-362  
Effective Date: 01/11/2019

**Description:**

**GENERAL**

**Print Technology:** Thermal Transfer

**Material Type:** Tamper-Resistant Metallized Vinyl

**Finish:** Glossy Silver

**Adhesive:** Acrylic

**APPLICATIONS**

Rating and serial plates that require high performance and resistance to product tampering.

**RECOMMENDED RIBBONS**

Brady Series R6000 Halogen Free

Brady Series R4400 colored (red, blue, and green)

**REGULATORY APPROVALS**

For information on the Weee-RoHS compliance status for a Brady Product go to one of the following websites:

In Canada: [www.bradycanada.ca/weee-rohs](http://www.bradycanada.ca/weee-rohs)

In Europe: [www.bradyeurope.com/rohs](http://www.bradyeurope.com/rohs)

In Japan: [www.bradyc.co.jp/products/labelsuse/rohs](http://www.bradyc.co.jp/products/labelsuse/rohs)

All other regions: [www.bradycid.com/weee-rohs](http://www.bradycid.com/weee-rohs)

**SPECIAL FEATURES**

Brady B-362 is designed to fracture easily in order to show signs of product tampering and to prevent one-piece label removal. Use caution when removing from liner as material is fragile. For best tamper evidency, a 24 hour room temperature dwell is recommended.

**Details:**

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 Total (excludes liner)	0.0025 inch (0.064 mm)
Adhesion to: -Stainless Steel -Polypropylene -Smooth ABS -Aluminum -Glass -Painted Enamel	ASTM D 1000 24 hour dwell	Label destroys upon removal
Tensile Strength and Elongation	ASTM D 1000	9 lbs/in (158 N/100 mm), 2%

Performance properties tested on B-362 printed with the Brady Series R6000 Halogen Free ribbon. Printed samples were laminated to aluminum and allowed to dwell 24 hours before exposure to the indicated environments.

PERFORMANCE PROPERTIES	TEST METHODS	TYPICAL RESULTS
High Service Temperature	30 days at various temperatures	No visible effect to label at 176°F (80°C). Slight discoloration at 194°F (90°C); moderate discoloration at 212°F (100°C), but label is still functional.
Low Service Temperature	30 days at -94°F (-70°C)	No visible effect
Humidity Resistance	30 days at 100°F (37°C), 95% R.H.	No visible effect
UV Light Resistance	ASTM G155, Cycle 1, Dry 30 days in Q-Sun Xenon Test Chamber	No visible effect
Weatherability	ASTM G155, Cycle 1 30 days in Xenon Arc Weather-Ometer®	No visible effect

PERFORMANCE PROPERTY	CHEMICAL RESISTANCE
----------------------	---------------------

Samples were printed with the Brady Series R6000 Halogen Free ribbon. Samples were laminated to aluminum panels and allowed to dwell 24 hours prior to testing. Testing was conducted at room temperature and consisted of 5 cycles of 10 minute immersions in the specified chemical followed by 30 minute recovery periods. After final immersion, samples rubbed 10 times with cotton swabs saturated in test fluids.

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE		
	LABEL STOCK SUBSTRATE/ ADHESIVE	R6000 Halogen Free PRINTING EFFECTS OF IMMERSION	R6000 Halogen Free PRINTING COTTON SWAB RUBS
Methyl Ethyl Ketone	Label no longer adhered to surface	Label no longer adhered to surface	Label no longer adhered to surface
Toluene	Label no longer adhered to surface	Label no longer adhered to surface	Label no longer adhered to surface
Isopropyl Alcohol	No visible effect	No visible effect	No visible effect
Mineral Spirits	No visible effect	No visible effect	No visible effect
JP-8 Jet Fuel	No visible effect	No visible effect	No visible effect
SAE 20 WT Oil	No visible effect	No visible effect	No visible effect
Mil 5606 Oil	No visible effect	No visible effect	No visible effect
Gasoline	Slight adhesive ooze	No visible effect	Slight print fade
Rust Veto® 342	No visible effect	No visible effect	No visible effect
Skydrol® 500B-4	Some silver color removed	No visible effect	Complete print removal, Silver color removed
Super Agitene®	No visible effect	No visible effect	No visible effect
Deionized Water	No visible effect	No visible effect	No visible effect
3% Alconox® Detergent	No visible effect	No visible effect	No visible effect
10% Sodium Hydroxide Solution	No visible effect	No visible effect	No visible effect
10% Sulfuric Acid Solution	No visible effect	No visible effect	No visible effect

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

**Trademarks:**

ASTM: American Society for Testing and Materials (U.S.A.)

Alconox® is a registered trademark of Alconox Co.

All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units

Rust Veto® is a registered trademark of Houghton Technical Corp.

S. I.: International System of Units

SAE: Society of Automotive Engineers (U.S.A.)

Skydrol® is a registered trademark of Solutia Inc.

Super Agitene® is a registered trademark of Graymills Corporation

Weather-Ometer® is a registered trademark of Atlas Material Testing Technology LLC

**Note:** All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

**WARRANTY**

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers.

This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2019 Brady Worldwide, Inc. | All Rights Reserved  
Material may not be reproduced or distributed in any form without written permission.

---

Brady North America | 6555 W. Good Hope Rd | Milwaukee, WI 53223 | USA | Tel: 414-358-6600 | Fax: 800-292-2289