

3M™ Heat Shrink Tubing PSTH

Elastomeric Polyester, Flexible

Data Sheet

November 2018

| | |
|---------------------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Description | 3M™ Heat Shrink Tubing PSTH is a high performance, rugged heat shrinkable tubing designed for harsh operating conditions. The tubing is made from flexible elastomeric polyester and has a continuous operating temperature range of -55°C (-70°F) to 150°C (302°F). 3M PSTH tubing is resistant to a wide range of solvents and chemicals including aviation fuel, diesel fuel, lubricating oils and hydraulic fluid. 3M PSTH tubing is specifically designed to pass the SC-X1511C military specification but also meets the functional requirements of MIL-DTL-23053/16. |
| Agency Approvals & Self Certifications | Meets requirements of: <ul data-bbox="451 842 1260 953" style="list-style-type: none">• AS23053/16*• SC-X-1511• For RoHS and REACH information, please visit www.3M.com/regs <p data-bbox="451 989 1409 1016">*Formerly MIL-I-AS23053/16, MIL-DTL-23053/16 and SAE-AMS-DTL-23053/16</p> |
| Typical Applications | 3M PSTH tubing is primarily designed for wire harnessing applications on military ground vehicles. It was primarily developed for the M-1 tank program, but is well suited for any application where conditions call for a high performance heat shrink tubing, particularly where the tubing will be exposed to petroleum based fluids. 3M PSTH tubing is also an excellent choice for heavy duty equipment and off-road vehicles. |
| Shrink Ratio | 3M PSTH tubing has a 2:1 shrink ratio. When freely recovered, the tubing will shrink to 50% of its as-supplied internal diameter. The recovered wall thickness is proportional to the degree of recovery. |

3M™ Heat Shrink Tubing PSTH

Standard Sizes and Dimensions

| Ordering Size | Expanded I.D. (Minimum) | | Recovered I.D. (Maximum) | | Recovered Wall Thickness (Nominal) | |
|---------------|----------------------------|---------|-----------------------------|---------|---------------------------------------|--------|
| | In. | (mm) | In. | (mm) | In. | (mm) |
| 3/16 | .187 | (4,75) | .093 | (2,36) | .035 | (0,89) |
| 1/4 | .250 | (6,35) | .125 | (3,18) | .035 | (0,89) |
| 3/8 | .375 | (9,53) | .187 | (4,75) | .035 | (0,89) |
| 1/2 | .500 | (12,70) | .250 | (6,35) | .035 | (0,89) |
| 5/8 | .625 | (15,88) | .312 | (7,92) | .042 | (1,07) |
| 3/4 | .750 | (19,05) | .250 | (6,35) | .042 | (1,07) |
| 7/8 | .875 | (22,23) | .437 | (11,10) | .045 | (1,14) |
| 1 | 1.000 | (25,40) | .500 | (12,70) | .049 | (1,24) |
| 1-1/4 | 1.250 | (31,75) | .625 | (15,88) | .055 | (1,40) |
| 1-1/2 | 1.500 | (38,10) | .750 | (19,05) | .055 | (1,40) |
| 2 | 2.000 | (50,80) | 1.000 | (25,40) | .065 | (1,65) |
| 2 1/2 | 2.500 | (63,50) | 1.250 | (31,75) | .065 | (1,65) |

Typical Properties

Technical information provided consists of typical product data and should not be used for specification purposes. Unless otherwise noted, all tests are performed at room temperature.

| | |
|----------------------------------------------|-------------------------------------------|
| Physical Property | Typical Value US units (metric) |
| Tensile Strength | 2200 PSI |
| Ultimate Elongation | 350% |
| Longitudinal Change | +2, -8% |
| Specific Gravity | 1.6 |
| Operating Temperature Range | -55°C to +150°C |
| Shrink Temperature (Min.) | 170°C (338°F) |
| Low Temperature Flexibility 4 hrs @ -55°C | No cracking |
| Flammability | Self-extinguish |
| Electrical Property | Typical Value US units (metric) |
| Dielectric Strength | 500 V/mil |
| Volume Resistivity | 7x10 ¹⁴ ohm/cm |
| Chemical Property | Typical Value US units (metric) |
| Corrosion Resistance | Non-corrosive |
| Fuel & Oil Resistance | Excellent |
| Solvent Resistance | Excellent |
| Abrasion Resistance | Excellent |
| Acids & Alkalis Resistance | Excellent |

3M™ Heat Shrink Tubing PSTH

Standard Colors Black

Shelf Life & Storage 3M™ Heat Shrink Tubing PSTH has a 4-year shelf life from date of manufacture when stored in a humidity controlled storage (10°C/50°F to 27°C/80°F and <75% relative humidity).

Availability **Standard Packaging**

Spools

Order 3M PSTH tubing by product name, size equivalent to the expanded inside diameter, package type and color. Always order the largest size that will shrink snugly over the component to be covered.
Example: PSTH, 3/8", black, spools.

Please contact your local distributor; available from 3M.com/oem [Where to Buy] or call 1-800-676-8381.

3M is a trademark of 3M Company.

Important Notice All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product, which are not contained in 3M's current publications, or any contrary statements contained on your purchase order, shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

Warranty; Limited Remedy; Limited Liability This product will be free from defects in material and manufacture at the time of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any direct, indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.**



Electrical Markets Division

Austin, TX
800 676.8381
FAX: 800 828.9329
www.3M.com/oem

Please recycle
© 3M 2018 All rights reserved
78-9237-1399-0 Rev A