

STATFREE® ESD ULTRA CLEAR BAG



Meets the required limits of ANSI/ESD S20.20, Packaging standard ANSI/ESD S541, and Static Control Bag standard ANSI/ESD S11.4 Level 5.

Specifications:

Electrical Properties	Typical Value	Test Procedures/Method
Surface Resisitance:		
(Interior and Exterior)	1 x 10 ⁴ to < 1 x 10 ¹¹ ohms	per ANSI/ESD STM11.11
Charge Generation:		
Teflon	-0.10 (nC/in ²) +0.10 (nC/in ²)	Modified Incline Plane
Quartz	+0.10 (nC/in ²)	Modified Incline Plane
Physical Properties:		

Thickness Width (Inside Dimensions) Length (Inside Dimensions) Light Transmission Heat Seal Tensile Strength Puncture Resistance Silicone MVTR

Nominal 3.5mil (.09mm) ±10%	MIL-STD-3010, 1003
Nominal -0" / + 1/4"	
Nominal +/- 1/8", Offset 0" to 1/4"	
>90 (%)	STM D-1003
>8 (lbs/in)	375°F, .75 sec 60 ps
>5,300 (MD/TD, psi)	ASTM D-882
>14 lbs	MIL-STD-3010, 2065
Not detected	FTIR
0.35 (grams / 100 in² / 24 hrs)	ASTM F-1249

Chemical Properties

Polycarbonate compatible: Contains no Amines, Amides, or N-Octanoic Acid.

Bag is free of amines, N-octanoic acid, silicones and heavy metals.

ANSI/ESD S541 section 6.1 Inside an EPA

"Packaging used within an EPA (that satisfies the minimum requirements of ANSI/ESD S20.20) shall be:

- Low charge generation
- · Dissipative or conductive materials for intimate contact"

RoHS, REACH and Conflict Minerals, Statement

See the Desco Industries RoHS, REACH, and Conflict Minerals Statement: https://desco.descoindustries.com/pdf/Regulatory_Statements_Desco_Statshield_Bags.pdf

See the Desco Limited Warranty:

PHONE (781) 821-8370

Desco.DescoIndustries.com/Limited-Warranty.aspx

Statshield® and Statfree® are Registered Trademarks of Desco Industries Inc. See Bag Selection Chart Click <u>HERE</u>.



Specifications and procedures subject to change without notice.

STATFREE® ESD ULTRA CLEAR BAG WITH ZIPPER, 3.5MIL (.09mm)

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com PHONE (909) 627-8178 DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407

