

Technical Data Sheet

EVAF100 non-silicone thermal gap pads are manufactured from highly Engineered resins. EVAF100 non-silicone thermal gap pads will not create circuit failure as they contain no siloxane volatilization, therefore will not promote silicone oil EVAF100 seeping. Non-Silicone thermal gap pads have excellent tensile strength and wear resistance. EverTherm Non-Silicone pads exhibit low outgassing, excellent tensile and wear resistance.



Applications

- ✓ Power battery pack
- ✓ Vehicle navigator
- ✓ Optical precision equipment
- ✓ Camera equipment
- ✓ Notebook computer
- Mobile and communication equipment
- Automotive engine control equipment
- High end industrial control and medical electronics



EVAF100 SILICONE FREE

Color	White		Visual	
Thickness	0.5mm		ASTM D37	4
Specific Gravity	1.9g/cm3		ASTM D79	2
Thermal Conductivity	1.0 W/mK		ASTM D547	70
Hardness(shore oo)	40-80		ASTM D224	40
Elongation	100%		ASTM D41	2
Tensile Strength	75psi		ASTM D41	2
Dielectric Breakdown Voltage	>8KV/AC/mm		ASTM D14	9
Flammability Rating	94 V-0		UL 94	
Volume Resistivity	10 ¹³ Ω.cm		ASTM D25	57
Operating Temperature	-40 - 130°C			
Thermal Resistance(1mm,@40psi)	1.10°C*in2/W		ASTM D547	70
Compression Ratio(1mm,@40psi)	30%			
RoHS	PASS		IEC 6232	1
Halogen	PASS		EN14582	
REACH	PASS		EN14372	
Ctandard Chast Ci-s	000		200	

Standard Sheet Size 200 x 300mm (Note: Other sheet sizes may be available upon request.)

Test fixtures using ASTM D5470. Recorded values include interface thermal resistance. These values are for reference only. The actual application performance is directly related to the applied surface roughness, flatness and pressure.

CR Technology, Inc

- 55 Chase St. Methuen, Massachusetts 01844
- sales@crtechinc.com
- 978.681.5300

