

Product Description

PA 4535 CF is among the strongest PA6 co-polymer carbon fiber filaments available on the market, delivering increased strength and stiffness.

Typical applications for PA 4535 CF are aluminum replacement parts, housings that require tight printing dimensional tolerances, clips, brackets, retainers, covers, in addition to jigs, fixtures, and tooling.

Advantages

PA 4535 CF has the highest carbon fiber loading available in the industry, providing 40% improvement in tensile strength, impact strength, Z strength and elongation at break, with the added benefit of being ESD safe.

Additionally, the combination of carbon fiber in the already extremely low-warp nylon results in extraordinarily

Storage and Use

PA 4535 CF is highly hygroscopic, meaning it will quickly absorb and retain moisture from the atmosphere, affecting visual quality and mechanical properties. For best results, print and store filament in a dry environment. If necessary, dry filament in an oven at up to 75 °C (165 °F) for 6 - 12 hours.

Due to its high stiffness, material feeding may be challenging near the end of the spool or when the filament is very dry. Pre-heating the filament or allowing the filament to absorb a small amount of moisture from the atmosphere will make it more workable.

[Download Jabil's optimized print profile by clicking here.](#)

Properties

| Mechanical Properties - Dry as Printed¹ | | | |
|---|-----------------------|----------------------|-------------------|
| | Test Condition | Typical Value | Method |
| Tensile Modulus (MPa) | XY coupons, Ambient | 10600 | ASTM D638, Type I |
| Tensile Elongation at Break (%) | | 2.9 | |
| Ultimate Tensile Strength (MPa) | | 88.0 | |
| Flexural Modulus (MPa) | XY coupons, Ambient | 5420 | ASTM D790 |
| Flexural Strength (MPa) | | 118 | |
| Flexural Strain (%) | | 4.3 | |
| Izod Impact, notched (J/m) | XY coupons, Ambient | 125 | ASTM D256 |
| Izod impact, un-notched (J/m) | XY coupons, Ambient | 525 | |

1. Testing conducted on bars printed at 270 °C and tested at <0.20 wt% moisture. Typical values are for reference only.

| Mechanical Properties - Moisture Conditioned¹ | | | |
|---|-----------------------|----------------------|-------------------|
| | Test Condition | Typical Value | Method |
| Tensile Modulus (MPa) | XY coupons, Ambient | 4850 | ASTM D638, Type I |
| Tensile Elongation at Break (%) | | 7.7 | |
| Ultimate Tensile Strength (MPa) | | 55.6 | |
| Flexural Modulus (MPa) | XY coupons, Ambient | 2380 | ASTM D790 |
| Flexural Strength (MPa) | | 62 | |
| Flexural Strain (%) | | >5% | |
| Izod Impact, notched (J/m) | XY coupons, Ambient | 193 | ASTM D256 |
| Izod impact, un-notched (J/m) | XY coupons, Ambient | 653 | |

1. Testing conducted on bars printed at 270 °C and conditioned for 14 days at 23 °C and 50 % RH. Typical values are for reference only.

| Thermal Properties | | | |
|----------------------------------|-----------------------|----------------------|---------------|
| | Test Condition | Typical Value | Method |
| Heat Deflection Temperature (°C) | 0.455 Mpa | 162 | DMA |
| Heat Deflection Temperature (°C) | 1.82 Mpa | 91 | DMA |
| Melt Temperature, Peak (°C) | 20°C/min ramp | 190 | DSC |

| Other Physical Properties | | | |
|----------------------------------|-----------------------|----------------------|---------------|
| | Test Condition | Typical Value | Method |
| Density (g/cm ³) | Ambient | 1.26 | ASTM D792 |

| Dimensional Properties | | | |
|----------------------------------|--------------------------|------------------------|------------------|
| | Test Condition | Typical Value | Method |
| Diameter: Mean, Indiv. Axis (mm) | In-line, 100% inspection | 1.75±0.05 2.85±0.05 | Laser Micrometer |

Disclaimer: The information in this technical data sheet, including material properties, are obtained from testing representative samples under carefully controlled conditions and are provided for reference only. Material properties may be impacted by storage, handling, processing equipment/parameters, and product design, among other factors. The information is not a substitute for user testing to determine fitness for any specific use and the user is responsible for ensuring safe and lawful use of the product.

No express or implied warranties are provided and the implied warranties of merchantability or fitness for a particular purpose are expressly disclaimed. No representations are made, and no liability is assumed arising from or relating to the product.

Copyright/Trademark: © 2019 Jabil Inc. All rights reserved. JABIL® and the JABIL logo are registered trademarks of Jabil Inc.