

# APPROVAL SHEET

## MULTILAYER CERAMIC CAPACITORS

General Purpose Series (4V to 100V)

0201 to 1812 Sizes

NP0, X7R, Y5V, X6S, X7S & X5R Dielectrics

Halogen Free & RoHS Compliance



\*Contents in this sheet are subject to change without prior notice.

## Multilayer Ceramic Capacitors

### 1. DESCRIPTION

MLCC consists of a conducting material and electrodes. To manufacture a chip-type SMT and achieve miniaturization, high density and high efficiency, ceramic condensers are used.

WTC's MLCC is made by NP0, X7R, X6S, X5R and Y5V dielectric material and which provides product with high electrical precision, stability and reliability.

### 2. FEATURES

- a. A wide selection of sizes is available (0201 to 1812).
- b. High capacitance in given case size.
- c. Capacitor with lead-free termination (pure Tin).

### 3. APPLICATIONS


- a. For general digital circuit.
- b. For power supply bypass capacitors.
- c. For consumer electronics.
- d. For telecommunication.

### 4. HOW TO ORDER

<b>1206</b>	<b>B</b>	<b>104</b>	<b>K</b>	<b>500</b>	<b>C</b>	<b>I</b>
<b>Size</b> Inch (mm)	<b>Dielectric</b> N=NP0 (C0G)	<b>Capacitance</b> Two significant digits followed by no. of zeros. And R is in place of decimal point.  eg.: 0R5=0.5pF 1R0=1.0pF 104=10x10 <sup>-4</sup> =100nF	<b>Tolerance</b> A=±0.05pF B=±0.1pF C=±0.25pF D=±0.5pF F=±1% G=±2% J=±5% K=±10% M=±20% Z=20/+80%	<b>Rated voltage</b> Two significant digits followed by no. of zeros. And R is in place of decimal point.  4R0=4 VDC 6R3=6.3 VDC 100=10 VDC 160=16 VDC 250=25 VDC 500=50 VDC 101=100 VDC	<b>Termination</b> C=Cu/Ni/Sn	<b>Packaging style</b> T=7" reeled G=13" reeled
<b>0201</b> (0603)						
<b>0402</b> (1005)						
<b>0603</b> (1608)						
<b>0805</b> (2012)						
<b>1206</b> (3216)						
<b>1210</b> (3225)						
<b>1812</b> (4532)						

Multilayer Ceramic Capacitors

**5. EXTERNAL DIMENSIONS**

Outline	Size Inch (mm)	L (mm)	W (mm)	T (mm)/Symbol	Soldering Method *	M <sub>B</sub> (mm)
	01R5 (0402)	0.4±0.02	0.2±0.02	0.2±0.02	V R	0.10±0.03
	0201 (0603)	0.6±0.03	0.3±0.03	0.3±0.03	L R	0.15±0.05
		0.6±0.05 <sup>#2</sup>	0.3±0.05 <sup>#2</sup>	0.3±0.05 <sup>#2</sup>		
		0.6±0.09 <sup>#3</sup>	0.3±0.09 <sup>#3</sup>	0.3±0.09 <sup>#3</sup>		0.15+0.1/-0.05
	0402 (1005)	1.00±0.05	0.50±0.05	0.50±0.05	N R	0.25
				0.50+0.02/-0.05	Q R	
		1.00±0.20	0.50±0.20	0.5±0.20	E R	+0.05/-0.10
	0603 (1608)	1.60±0.10	0.80±0.10	0.80±0.07	S R / W	0.40±0.15
		1.60+0.15/-0.10	0.80+0.15/-0.10	0.50±0.10	H R / W	
		1.60±0.20 <sup>#1</sup>	0.80±0.20 <sup>#1</sup>	0.80+0.15/-0.10	X R / W	
				0.8±0.20 <sup>#1</sup>		
	0805 (2012)	2.00±0.15	1.25±0.10	0.50±0.10	H R / W	0.50±0.20
				0.60±0.10	A R / W	
				0.80±0.10	B R / W	
				1.25±0.10	D R	
		2.00±0.20	1.25±0.20	0.85±0.10	T R / W	
				1.25±0.20	I R	
	1206 (3216)	3.20±0.15	1.60±0.15	0.80±0.10	B R / W	0.60±0.20 (0.5±0.25)***
				0.95±0.10	C R	
				1.25±0.10	D R	
				1.15±0.15	J R	
		3.20±0.20	1.60±0.20	1.60±0.20	G R	
				0.85±0.10	T R / W	
				1.60+0.30/-0.10	P R	
				3.20+0.30/-0.1 <sup>#5</sup>		
	1210 (3225)	3.20±0.30	2.50±0.20	0.95±0.10	C R	0.75±0.25
				0.85±0.10	T R	
				1.25±0.10	D R	
		3.20±0.40	2.50±0.30	1.60±0.20	G R	
				2.00±0.20	K R	
				2.50±0.30	M R	
	1808 (4520)	4.50±0.40 (4.5±0.5/-0.3)**	2.03±0.25	2.50±0.50 <sup>#4</sup>	2.50±0.50 <sup>#4</sup>	0.75±0.25 (0.5±0.25)***
				1.25±0.10	D R	
				1.40±0.15	F R	
				1.60±0.20	G R	
		4.50±0.40 (4.5±0.5/-0.3)**	3.20±0.30	2.00±0.20	K R	
				2.50±0.30	M R	
	1812 (4532)	4.50±0.40 (4.5±0.5/-0.3)**	3.20±0.30	2.80±0.30	U R	0.75±0.25 (0.5±0.25)***
				1.25±0.10	D R	
				1.60±0.20	G R	
				2.00±0.20	K R	
		3.20±0.40	3.20±0.40	2.50±0.30	M R	
				2.80±0.30	U R	

\* R = Reflow soldering process ; W = Wave soldering process.

\*\* For 1808/1812/1825\_200V~4000V and safety certificated products.

\*\*\* For 1206<sub>≥</sub>1000V, 1808/1812\_200V~4000V and safety certificated products.

#1: For 0603/Cap $\geq$ 10μF or 0603( $\leq$ 6.3V)/Cap $\geq$ 4.7μF For 0603(>10V)/Cap>1μF products.

#2: For 0201/0.1uF < Cap < 0.68uF products, Excluding 0201X334~474( $\leq$ 6.3V) & 0201X224( $\leq$ 10V).

#3: For 0201/Cap $\geq$ 0.68μF products.

#4: For 1210(100V)/Cap>1μF or 1210(250V)/Cap>0.47μF or 1210(400V~630V)/Cap>0.22μF.

#5: For 1206(100V)/Cap $\geq$ 1.2μF products.

Multilayer Ceramic Capacitors

## 6. GENERAL ELECTRICAL DATA

Dielectric	NP0	X7R	Y5V	X5R	X6S	X7S
Size	0201, 0402, 0603, 0805, 1206, 1210, 1812					
Capacitance range*	0.1pF to 0.1μF	100pF to 47μF	0.01μF to 100μF	100pF to 220μF	0.1μF to 100μF	0.1μF to 100μF
Capacitance tolerance**	Cap≤5pF <sup>#1</sup> : A ( $\pm 0.05\mu F$ ), B ( $\pm 0.1\mu F$ ), C ( $\pm 0.25\mu F$ ) 5pF<Cap<10pF: C ( $\pm 0.25\mu F$ ), D ( $\pm 0.5\mu F$ ) Cap≥10pF: F ( $\pm 1\%$ ), G ( $\pm 2\%$ ), J ( $\pm 5\%$ ), K ( $\pm 10\%$ )	J ( $\pm 5\%$ ), K ( $\pm 10\%$ ), M ( $\pm 20\%$ )	M ( $\pm 20\%$ ), Z (-20/+80%)	K ( $\pm 10\%$ ), M ( $\pm 20\%$ )	K ( $\pm 10\%$ ), M ( $\pm 20\%$ )	K ( $\pm 10\%$ ), M ( $\pm 20\%$ )
Rated voltage (WVDC)	10V, 16V, 25V, 50V, 100V	6.3V, 10V, 16V, 25V, 50V, 100V				
Operating temperature	-55 to +125°C		-25 to +85°C	-55 to +85°C	-55 to +105°C	-55 to +125°C
Capacitance characteristic	±30ppm	±15%	+30/-80%	±15%	±22%	±22%
Termination	Ni/Sn (lead-free termination)					

#1: NP0, 0.1pF product only provide B tolerance; 0603N0R3/0R4 provide B&C tolerance.

\* Measured at the condition of 30~70% related humidity.

NP0: Apply  $1.0 \pm 0.2\text{VRms}$ ,  $1.0\text{MHz} \pm 10\%$  for  $\text{Cap} \leq 1000\text{pF}$  and  $1.0 \pm 0.2\text{VRms}$ ,  $1.0\text{kHz} \pm 10\%$  for  $\text{Cap} > 1000\text{pF}$ ,  $25^\circ\text{C}$  at ambient temperature

X7R/X6S/X5R/X7S: Please refer to page 13 "Reliability test conditions and requirements" for detail.

Y5V: Apply  $1.0 \pm 0.2\text{VRms}$ ,  $1.0\text{kHz} \pm 10\%$ , at  $20^\circ\text{C}$  ambient temperature.

\*\* Preconditioning for Class II MLCC: Perform a heat treatment at  $150 \pm 10^\circ\text{C}$  for 1 hour and then leave in ambient condition for  $24 \pm 2$  hours before measurement.



Multilayer Ceramic Capacitors

## 7. CAPACITANCE RANGE

### 7-1. NPO Dielectric 0201, 0402, 0603, 0805 Sizes

Capacitance	DIELECTRIC	NPO																			
	SIZE	0201					0402					0603					0805				
	RATED VOLTAGE (VDC)	10	16	25	50	100	10	16	25	50	100	10	16	25	50	100	10	16	25	50	100
0.1pF (0R1)	L	L	L	L	L	N	N	N	N												
0.2pF (0R2)	L	L	L	L	L	N	N	N	N												
0.3pF (0R3)	L	L	L	L	L	N	N	N	N		S	S	S	S	S						
0.4pF (0R4)	L	L	L	L	L	N	N	N	N		S	S	S	S	S						
0.5pF (0R5)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
0.6pF (0R6)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
0.7pF (0R7)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
0.8pF (0R8)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
0.9pF (0R9)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
1.0pF (1R0)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
1.2pF (1R2)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
1.5pF (1R5)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
1.8pF (1R8)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
2.0pF (2R0)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
2.2pF (2R2)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
2.7pF (2R7)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
3.0pF (3R0)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
3.3pF (3R3)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
3.9pF (3R9)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
4.0pF (4R0)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
4.7pF (4R7)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
5.0pF (5R0)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
5.6pF (5R6)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
6.0pF (6R0)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
6.8pF (6R8)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
7.0pF (7R0)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
8.0pF (8R0)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
8.2pF (8R2)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
9.0pF (9R0)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
10pF (100)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
12pF (120)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
15pF (150)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
18pF (180)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
22pF (220)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
27pF (270)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
33pF (330)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
39pF (390)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
47pF (470)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
56pF (560)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
68pF (680)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
82pF (820)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
100pF (101)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
120pF (121)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
150pF (151)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
180pF (181)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
220pF (221)	L	L	L	L	L	N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
270pF (271)	L					N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
330pF (331)	L					N	N	N	N		S	S	S	S	S	S	A	A	A	A	A
390pF (391)	L					N	N	N	N		S	S	S	S	S	S	B	B	B	B	B
470pF (471)	L					N	N	N	N		S	S	S	S	S	S	B	B	B	B	B
560pF (561)	L					N	N	N	N		S	S	S	S	S	S	B	B	B	B	B
680pF (681)						N	N	N	N		S	S	S	S	S	S	B	B	B	B	B
820pF (821)						N	N	N	N		S	S	S	S	S	S	B	B	B	B	B
1,000pF (102)						N	N	N	N		S	S	S	S	S	S	B	B	B	B	B
1,200pF (122)											X	X	X	X	X		B	B	B	B	B
1,500pF (152)											X	X	X	X	X		B	B	B	B	B
1,800pF (182)											X	X	X	X	X		B	B	B	B	B
2,200pF (222)											X	X	X	X	X		B	B	B	B	B
2,700pF (272)											X	X	X	X	X		D	D	D	D	D
3,300pF (332)											X	X	X	X	X		D	D	D	D	D
3,900pF (392)											X	X	X	X	X		D	D	D	D	D
4,700pF (472)											X	X	X	X	X		D	D	D	D	D
5,600pF (562)											X	X	X	X	X		D	D	D	D	D
6,800pF (682)											X	X	X	X	X		D	D	D	D	D
8,200pF (822)											X	X	X	X	X		D	D	D	D	D
0.010uF (103)											X	X	X	X	X		D	D	D	D	D
0.012uF (123)																	D	D	D	D	D
0.015uF (153)																	D	D	D	D	D
0.018uF (183)																	D	D	D	D	D
0.022uF (223)																	D	D	D	D	D

1. The letter in cell is expressed the symbol of product thickness.

2. The letter in cell with “\*” mark is expressed capacitance tolerance “J” ( $\pm 5\%$ ) only.

3. For more information about products with special capacitance or other data, please contact WTC local representative.

Multilayer Ceramic Capacitors

**7-1. NP0 Dielectric 1206, 1210, 1812 Sizes**

DIELECTRIC		NP0													
SIZE		1206					1210					1812			
RATED VOLTAGE (VDC)		10	16	25	50	100	10	16	25	50	100	16	25	50	100
Capacitance	1.0pF (1R0)														
	1.2pF (1R2)	B	B	B	B	B									
	1.5pF (1R5)	B	B	B	B	B									
	1.8pF (1R8)	B	B	B	B	B									
	2.2pF (2R2)	B	B	B	B	B									
	2.7pF (2R7)	B	B	B	B	B									
	3.3pF (3R3)	B	B	B	B	B									
	3.9pF (3R9)	B	B	B	B	B									
	4.7pF (4R7)	B	B	B	B	B									
	5.6pF (5R6)	B	B	B	B	B									
	6.8pF (6R8)	B	B	B	B	B									
	8.2pF (8R2)	B	B	B	B	B									
	10pF (100)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	12pF (120)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	15pF (150)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	18pF (180)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	22pF (220)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	27pF (270)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	33pF (330)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	39pF (390)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	47pF (470)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	56pF (560)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	68pF (680)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	82pF (820)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	100pF (101)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	120pF (121)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	150pF (151)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	180pF (181)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	220pF (221)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	270pF (271)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	330pF (331)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	390pF (391)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	470pF (471)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	560pF (561)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	680pF (681)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	820pF (821)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	1.000pF (102)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	1,200pF (122)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	1,500pF (152)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	1,800pF (182)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	2,200pF (222)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	2,700pF (272)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	3,300pF (332)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	3,900pF (392)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	4,700pF (472)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	5,600pF (562)	B	B	B	B	B	C	C	C	C	C	D	D	D	
	6,800pF (682)	C	C	C	C	C	C	C	C	C	C	D	D	D	
	8,200pF (822)	D	D	D	D	D	C	C	C	C	C	D	D	D	
	0.010μF (103)	D	D	D	D	D	C	C	C	C	C	D	D	D	
	0.012μF (123)	P	P	P	P	P	D	D	D	D	D	D	D	D	
	0.015μF (153)	P	P	P	P	P	D	D	D	D	D	D	D	D	
	0.018μF (183)	P	P	P	P	P	K	K	K	K	K	D	D	D	
	0.022μF (223)	P	P	P	P	P	K	K	K	K	K	D	D	D	
	0.027μF (273)	P	P	P	P		K	K	K	K	K	D	D	D	
	0.033μF (333)	P	P	P	P	T	K	K	K	K	K	D	D	D	
	0.039μF (393)	P	P	P	P		K	K	K	K	K	M	M	M	
	0.047μF (473)	P	P	P	P		K	K	K	K	K	M	M	M	
	0.056μF (563)	P	P	P	P							M	M	M	
	0.068μF (683)	P	P	P	P							M	M	M	
	0.082μF (823)	P	P	P	P							M	M	M	
	0.1μF (104)	P	P	P	P							M	M	M	

1. The letter in cell is expressed the symbol of product thickness.

2. The letter in cell with “\*” mark is expressed capacitance tolerance “J” ( $\pm 5\%$ ) only.

3. For more information about products with special capacitance or other data, please contact WTC local representative.

Multilayer Ceramic Capacitors

7-2. X7R Dielectric 0201, 0402, 0603, 0805 Sizes

DIELECTRIC		X7R																						
SIZE		0201					0402					0603					0805							
RATED VOLTAGE (VDC)		6.3	10	16	25	50	6.3	10	16	25	50	100	6.3	10	16	25	50	100	6.3	10	16	25	50	100
100pF (101)		L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
120pF (121)		L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
150pF (151)		L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
180pF (181)		L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
220pF (221)		L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
270pF (271)		L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
330pF (331)		L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
390pF (391)		L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
470pF (471)		L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
560pF (561)		L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
680pF (681)		L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
820pF (821)		L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
1,000pF (102)	L	L	L	L	L	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
1,200pF (122)	L	L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
1,500pF (152)	L	L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
1,800pF (182)	L	L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
2,200pF (222)	L	L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
2,700pF (272)	L	L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
3,300pF (332)	L	L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
3,900pF (392)	L	L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
4,700pF (472)	L	L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
5,600pF (562)	L	L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
6,800pF (682)	L	L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
8,200pF (822)	L	L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
0.010μF (103)	L	L	L	L	N	N	N	N	N	S	S	S	S	S	B	B	B	B	B					
0.012μF (123)					N	N	N	N	N	S	S	S	S	X	B	B	B	B	B					
0.015μF (153)					N	N	N	N	N	S	S	S	S	X	B	B	B	B	B					
0.018μF (183)					N	N	N	N	N	S	S	S	S	X	B	B	B	B	B					
0.022μF (223)	L	L	N	N	N	N	N	N	N	S	S	S	S	X	B	B	B	B	B					
0.027μF (273)			N	N	N	N	N	N	N	S	S	S	S	X	B	B	B	B	D					
0.033μF (333)			N	N	N	N	N	N	N	S	S	S	S	X	X	B	B	B	D					
0.039μF (393)			N	N	N	N	N	N	N	S	S	S	S	X	X	B	B	B	D					
0.047μF (473)			N	N	N	N	N	N	N	S	S	S	S	X	X	B	B	B	D					
0.056μF (563)			N	N	N	E	N	N	N	S	S	S	S	X	X	B	B	B	D					
0.068μF (683)			N	N	N	E	N	N	N	S	S	S	S	X	X	B	B	B	D					
0.082μF (823)			N	N	N	E	N	N	N	S	S	S	S	X	X	B	B	B	D					
0.10μF (104)			N	N	N	E	N	N	N	S	S	S	S	X	X	B	B	B	D					
0.12μF (124)										S	S	X				B	B	B	B	I				
0.15μF (154)										S	S	X	X			D	D	D	D	I				
0.18μF (184)										S	S	X				D	D	D	D	I				
0.22μF (224)										N	N	N	N	S	X	X	D	D	D	D	I			
0.27μF (274)										X	X	X	X			D	D	D	I	I				
0.33μF (334)										X	X	X	X	X		D	D	D	I	I				
0.39μF (394)										X	X	X	X	X		D	D	D	I	I				
0.47μF (474)										N	N	X	X	X	X	D	D	D	I	I				
0.56μF (564)										X	X	X				D	D	D	D					
0.68μF (684)										X	X	X				D	D	D	I					
0.82μF (824)										X	X	X				D	D	D	D					
1.0μF (105)										N		X	X	X	X	X	D	D	D	I				
1.5μF (155)																I	I	I						
2.2μF (225)																X	I	I	I	I	I			
3.3μF (335)																X	I	I	I	I	I			
4.7μF (475)																								
6.8μF (685)																								
10μF (106)																								
22μF (226)																								

1. The letter in cell is expressed the symbol of product thickness.

2. The letter in cell with “\*” mark is expressed product not in 10% (code “K”) tolerance.

Multilayer Ceramic Capacitors

7-2. X7R Dielectric 1206, 1210, 1812 Sizes

Capacitance	DIELECTRIC	X7R																		
	SIZE	1206					1210					1812								
	RATED VOLTAGE (VDC)	6.3	10	16	25	35	50	100	6.3	10	16	25	35	50	100	10	16	25	50	100
	100pF (101)																			
	120pF (121)																			
	150pF (151)	B	B	B		B	B													
	180pF (181)	B	B	B		B	B													
	220pF (221)	B	B	B		B	B													
	270pF (271)	B	B	B		B	B													
	330pF (331)	B	B	B		B	B													
	390pF (391)	B	B	B		B	B													
	470pF (471)	B	B	B		B	B													
	560pF (561)	B	B	B		B	B													
	680pF (681)	B	B	B		B	B													
	820pF (821)	B	B	B		B	B													
	1,000pF (102)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	1,200pF (122)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	1,500pF (152)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	1,800pF (182)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	2,200pF (222)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	2,700pF (272)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	3,300pF (332)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	3,900pF (392)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	4,700pF (472)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	5,600pF (562)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	6,800pF (682)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	8,200pF (822)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	0.010μF (103)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	0.012μF (123)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	0.015μF (153)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	0.018μF (183)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	0.022μF (223)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	0.027μF (273)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	0.033μF (333)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	0.039μF (393)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	0.047μF (473)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	0.056μF (563)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	0.068μF (683)	B	B	B		B	B		C	C	C		C	C	D	D	D	D	D	
	0.082μF (823)	B	B	B		B	D		C	C	C		C	C	D	D	D	D	D	
	0.10μF (104)	B	B	B		B	C		C	C	C		C	C	D	D	D	D	D	
	0.12μF (124)	B	B	B		B	D		C	C	C		C	C	D	D	D	D	D	
	0.15μF (154)	C	C	C		C	G		C	C	C		C	D	D	D	D	D	D	
	0.18μF (184)	C	C	C		C	G		C	C	C		C	D	D	D	D	D	D	
	0.22μF (224)	C	C	C		C	G		C	C	C		C	D	D	D	D	D	D	
	0.27μF (274)	C	C	C		D	G		C	C	C		C	G	D	D	D	D	D	
	0.33μF (334)	C	C	C		D	G		C	C	C		D	G	D	D	D	D	D	
	0.39μF (394)	C	C	J		P	G		C	C	C		D	M	D	D	D	D	D	
	0.47μF (474)	J	J	J		P	G		C	C	C		D	M	D	D	D	D	K	
	0.56μF (564)	J	J	J		P	P		D	D	D		D	M	D	D	D	D	K	
	0.68μF (684)	J	J	J		P	P		D	D	D		D	K	D	D	D	K	K	
	0.82μF (824)	J	J	J		P	P		D	D	D		D	K	D	D	D	K	K	
	1.0μF (105)	J	J	J		P	P		D	D	D		D	K	D	D	D	K	K	
	1.5μF (155)	J	J	J	P	P			G	G		M	M						K	
	2.2μF (225)	J	J	J	P	P	P		G	G		M	M				M	M		
	3.3μF (335)	P	P	P	P	P			G	G		M								
	4.7μF (475)	P	P	P	P	P			K	K	K	M	M							
	6.8μF (685)																			
	10μF (106)	P	P	P	P	P			K	K	K	M	M							
	22μF (226)	P	P	P*					M	M	M									
	47μF (476)								M	M										
	100μF (107)																			

1. The letter in cell is expressed the symbol of product thickness.

2. The letter in cell with “\*” mark is expressed product not in 10% (code “K”) tolerance.

Multilayer Ceramic Capacitors

**7-3. Y5V Dielectric 0402, 0603, 0805 Sizes**

DIELECTRIC		Y5V															
SIZE		0402					0603					0805					
RATED VOLTAGE (VDC)		6.3	10	16	25	50	6.3	10	16	25	50	6.3	10	16	25	50	100
Capacitance	0.010μF (103)	N	N	N	N		S	S	S	S		A	A	A	A	B	
	0.015μF (153)	N	N	N	N		S	S	S	S		A	A	A	A	B	
	0.022μF (223)	N	N	N	N		S	S	S	S		A	A	A	A	B	
	0.033μF (333)	N	N	N	N		S	S	S	S		A	A	A	A	B	
	0.047μF (473)	N	N	N			S	S	S	S		A	A	A	A	B	
	0.068μF (683)	N	N	N			S	S	S	S		A	A	A	A	B	
	0.10μF (104)	N	N	N			S	S	S	S		A	A	A	A	B	
	0.15μF (154)	N					S	S	S	S		A	A	A	A	A	
	0.22μF (224)	N	N				S	S	S	S		A	A	A	A	A	
	0.33μF (334)	N	N				S	S	S			B	B	B	B		
	0.47μF (474)	N	N				S	S				B	B	B	B		
	0.68μF (684)						S	X				B	B	D	D		
	1.0μF (105)						S	X				B	B	D	D		
	1.5μF (155)						S					D	D				
	2.2μF (225)						S	S				D	D				
	3.3μF (335)											D	D				
	4.7μF (475)											D	D				
	6.8μF (685)											I					
	10μF (106)										I	I					
	22μF (226)																

1. The letter in cell is expressed the symbol of product thickness.

2. For more information about products with special capacitance or other data, please contact WTC local representative.

**7-3. Y5V Dielectric 1206, 1210, 1812 Sizes**

DIELECTRIC		Y5V																	
SIZE		1206						1210						1812					
RATED VOLTAGE (VDC)		6.3	10	16	25	50	100	6.3	10	16	25	35	50	100	10	16	25	50	100
Capacitance	0.010μF (103)	B	B	B	B	B						C					D		
	0.015μF (153)	B	B	B	B	B						C					D		
	0.022μF (223)	B	B	B	B	B						C					D		
	0.033μF (333)	B	B	B	B	B						C					D		
	0.047μF (473)	B	B	B	B	B						C					D		
	0.068μF (683)	B	B	B	B	B						C					D		
	0.10μF (104)	B	B	B	B	B		C	C	C	C	C	C	D	D	D	D		
	0.15μF (154)	B	B	B	B	C	C	C	C	C	C	C	C	D	D	D	D		
	0.22μF (224)	B	B	B	B	C	C	C	C	C	C	C	C	D	D	D	D		
	0.33μF (334)	B	B	B	B		C	C	C	C	C	C	C	D	D	D	D		
	0.47μF (474)	B	B	B	B		C	C	C	C	C	C	C	D	D	D	D		
	0.68μF (684)	B	B	B	B		C	C	C	C	C	C	C	D	D	D	D		
	1.0μF (105)	C	C	C	C		C	C	C	C	C	C	C	D	D	D	D		
	1.5μF (155)	C	C	C			C	C	C					D	D	D	D		
	2.2μF (225)	C	C	C			C	C	C			G		D	D	D	D		
	3.3μF (335)	J	J	J			C	C	C					D	D	D	D		
	4.7μF (475)	J	J	J			C	C	D			G		D	D	D	D		
	6.8μF (685)	J	J				C	C	D					D	D	D	D		
	10μF (106)	J	J				D	D	G	K				D	D	D			
	22μF (226)	P					K	K						M					
	47μF (476)						K	K											
	100μF (107)						M												

1. The letter in cell is expressed the symbol of product thickness.

2. For more information about products with special capacitance or other data, please contact WTC local representative.

Multilayer Ceramic Capacitors

7-4. X5R Dielectric 0201, 0402, 0603, 0805, 1206, 1210 Sizes

Dielectric		X5R															
Size		0201					0402					0603					
Rated Voltage (VDC)	6.3	10	16	25	50	4	6.3	10	16	25	50	4	6.3	10	16	25	50
Capacitance	100pF (101)		L	L	L												
	150pF (151)		L	L	L												
	220pF (221)		L	L	L												
	330pF (331)		L	L	L												
	470pF (471)		L	L	L												
	680pF (681)		L	L	L												
	820pF (821)		L	L	L												
	1,000pF (102)	L	L	L	L												
	1,500pF (152)	L	L	L													
	2,200pF (222)	L	L	L													
	2,700pF (272)	L	L	L													
	3,300pF (332)	L	L	L													
	4,700pF (472)	L	L	L													
	6,800pF (682)	L	L	L													
	0.010μF (103)	L	L	L	L	L											
	0.015μF (153)	L	L									N					
	0.022μF (223)	L	L	L	L							N					
	0.033μF (333)	L	L									N	N				
	0.047μF (473)	L	L	L	L		N	N	N	N	N						
	0.068μF (683)	L	L				N	N	N	N	E						
	0.082μF (823)	L	L				N	N	N	N	E						
	0.10μF (104)	L	L	L	L		N	N	N	N	N	E					
	0.15μF (154)						N	N	N	N	N						
	0.22μF (224)	L	L	L*			N	N	N	N	N	X	X	X	X	X	
	0.33μF (334)	L					N	N	N	N		X	X	X	X	X	
	0.47μF (474)	L					N	N	N	N	E	X	X	X	X	X	X
	0.68μF (684)						N	N				X	X	X	X	X	
	0.82μF (824)											X	X	X	X	X	
	1.0μF (105)	L	L*	L*			N	N	N	N	E	X	X	X	X	X	X
	1.5μF (155)											X	X				
	2.2μF (225)	L*	L*				N	E	E			X	X	X	X	X	X
	3.3μF (335)											X	X				
	4.7μF (475)						E	E	E*			X	X	X	X	X	
	6.8μF (685)																
	10μF (106)						E*	E*	E*			X	X	X	X	X*	
	22μF (226)							E*				X*	X*	X*			
	47μF (476)											X*	X*				

Dielectric		X5R																		
Size		0805					1206					1210								
Rated Voltage (VDC)	4	6.3	10	16	25	50	4	6.3	10	16	25	50	4	6.3	10	16	25	35	50	
Capacitance	1.0μF (105)		D	D	D	I						P								
	1.5μF (155)	I	I	I	I	I		J	J				K	K						
	2.2μF (225)	I	I	I	I	I		J	J	P	P		K	K						
	3.3μF (335)	I	I	I	I	I		P	P	P	P		K	K						
	4.7μF (475)	I	I	I	I	I	P	P	P	P	P		K	K	K					
	6.8μF (685)						P	P												
	10μF (106)	I	I	I	I	I	P	P	P	P	P		K	K	K	K	M	M		
	22μF (226)	I	I*	I*	I*		P	P	P	P		M	M	M	M	M	M			
	47μF (476)	I*	I*				P	P	P*			M	M	M	M	M*				
	100μF (107)	I*	I*				P*					M*	M*	M*						
	220μF (227)											M*	M*							

1. The letter in cell is expressed the symbol of product thickness.

2. The letter in cell with “\*” mark is expressed product not in 10% (code “K”) tolerance.

Multilayer Ceramic Capacitors

**7-5. X6S Dielectric 0201, 0402, 0603, 0805, 1206, 1210 Sizes**

Dielectric		X6S																													
Size		0201					0402					0603					0805					1206					1210				
Rated Voltage (VDC)		4	6.3	10	16	25	6.3	10	16	25	4	6.3	10	16	25	4	6.3	10	16	25	50	6.3	10	16	25	50	6.3	10	16	25	50
Capacitance	0.10μF (104)	L	L	L	L	L	N																								
	0.15μF (154)																														
	0.22μF (224)	L	L*				N																								
	0.33μF (334)																														
	0.47μF (474)	L					N																								
	0.68μF (684)																														
	1.0μF (105)	L*	L*				N	N	N	E																					
	1.5μF (155)																														
	2.2μF (225)		E	E	E			X	X	X	X						I														
	3.3μF (335)																														
	4.7μF (475)		E	E			X	X	X	X	X						I	I	I	I	I										
	6.8μF (685)																														
	10μF (106)			E*			X*	X*	X*	X*		I	I	I	I	I	P														
	22μF (226)						X*	X*				I*	I*	I*	I*		P	P*	P							M	M	M			
	47μF (476)											I*	I*				P														
	100μF (107)																M*	M*													

1. The letter in cell is expressed the symbol of product thickness.

2. The letter in cell with “\*” mark is expressed product not in 10% (code “K”) tolerance.

**7-6. X7S Dielectric 0402, 0603, 0805, 1206, 1210 Sizes**

Dielectric		X7S																													
Size		0201					0402					0603					0805					1206					1210				
Rated Voltage (VDC)		10V	6.3	10	16	25	6.3	10	16	25	10	16	25	50	100	6.3	10	16	25	50	6.3	10	16	25	50	6.3	10	16	25	50	
Capacitance	0.1μF (104)	L														I															
	1.0μF (105)		E																												
	1.5μF (155)																														
	2.2μF (225)	E	E					X																							
	3.3μF (335)							X	X							I															
	4.7μF (475)							X	X																						
	6.8μF (685)																														
	10μF (106)																														
	22μF (226)																														
	47μF (476)																														
	100μF (107)																														

1. The letter in cell is expressed the symbol of product thickness.

2. The letter in cell with “\*” mark is expressed product not in 10% (code “K”) tolerance.

Multilayer Ceramic Capacitors

## 8. PACKAGING STYLE AND QUANTITY

Size	Thickness (mm)/Symbol	Paper tape		Plastic tape	
		7" reel	13" reel	7" reel	13" reel
0201 (0603)	0.30±0.03 L	15,000	70,000	-	-
	0.30±0.05 L	15,000	-	-	-
	0.30±0.09 L	15,000	-	-	-
0402 (1005)	0.50±0.05 N	10,000	50,000	-	-
	0.50+0.02/-0.05 Q	10,000	50,000	-	-
	0.50±0.20 E	10,000	-	-	-
0603 (1608)	0.50±0.10 H	4,000	-	-	-
	0.80±0.07 S	4,000	15,000	-	-
	0.80+0.15/-0.10 X	4,000	15,000	-	-
0805 (2012)	0.50±0.10 H	4,000	15,000	-	-
	0.60±0.10 A	4,000	15,000	-	-
	0.80±0.10 B	4,000	15,000	-	-
	0.85±0.10 T	4,000	15,000	-	-
	1.25±0.10 D	-	-	3,000	10,000
	1.25±0.20 I	-	-	3,000	10,000
1206 (3216)	0.80±0.10 B	4,000	15,000	-	-
	0.85±0.10 T	4,000	15,000	-	-
	0.95±0.10 C	-	-	3,000	10,000
	1.15±0.15 J	-	-	3,000	10,000
	1.25±0.10 D	-	-	3,000	10,000
	1.60±0.20 G	-	-	2,000	10,000
1210 (3225)	1.60+0.30/-0.10 P	-	-	2,000	9,000
	0.85±0.10 T	-	-	3,000	10,000
	0.95±0.10 C	-	-	3,000	10,000
	1.25±0.10 D	-	-	3,000	10,000
	1.60±0.20 G	-	-	2,000	-
	2.00±0.20 K	-	-	1,000	6,000
1808 (4520)	2.50±0.30 M	-	-	1,000	6,000
	1.25±0.10 D	-	-	2,000	10,000
	1.40±0.15 F	-	-	2,000	10,000
	1.60±0.20 G	-	-	2,000	8,000
1812 (4532)	2.00±0.20 K	-	-	1,000	6,000
	1.25±0.10 D	-	-	1,000	5,000
	1.60±0.20 G	-	-	1,000	-
	2.00±0.20 K	-	-	1,000	-
	2.50±0.30 M	-	-	500	3,000
	2.80±0.30 U	-	-	500	-

Unit: pieces

Multilayer Ceramic Capacitors

## 9. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements																																																																																																																																					
1.	Visual and Mechanical	---	* No remarkable defect. * Dimensions to conform to individual specification sheet.																																																																																																																																					
2.	Capacitance	*Test temp.: Room Temperature. *Class I: (NP0)	* Shall not exceed the limits given in the detailed spec.																																																																																																																																					
3.	Q/D.F. (Dissipation Factor)	<p><math>\leq 1000\text{pF}, 1.0 \pm 0.2\text{Vrms} \cdot 1\text{MHz} \pm 10\%</math>  <math>&gt; 1000\text{pF}, 1.0 \pm 0.2\text{Vrms} \cdot 1\text{KHz} \pm 10\%</math></p> <p>Class II: (X7R, X7E, X6S, X5R, X7S, Y5V)  <math>C \leq 10\mu\text{F}, 1.0 \pm 0.2\text{Vrms} \cdot 1\text{KHz} \pm 10\% **</math>  <math>C &gt; 10\mu\text{F}, 0.5 \pm 0.2\text{Vrms} \cdot 120\text{Hz} \pm 20\%</math></p> <p>** Test condition: <math>0.5 \pm 0.2\text{Vrms} \cdot 1\text{KHz} \pm 10\%</math></p> <p>X7R:  0603/475(6.3V)</p> <p>X5R:  0201 <math>\geq 224</math> (6.3V, 10V, 16V)<sup>#1</sup>,  0402 <math>\geq 475</math> (6.3V, 16V), 0402 <math>\geq 225</math> (10V),  0603=106 (6.3V)  TT18X <math>\geq 475</math> (10V), TT15X series</p> <p>X6S:  0201/474(4V), 0201&gt;104 (6.3V, 10V),  0402 <math>\geq 225</math> (6.3V),  0402/475 (10V), 0603/106 (6.3V),</p> <p>X7S:  0402/225(6.3V)</p> <p>#1 Excluding  X5R/0201/105(6.3V); 225(10V),  0402X475M6R3  (1.0 <math>\pm 0.2\text{Vrms} \cdot 1\text{KHz} \pm 10\%</math>)</p>	<p>NP0: Cap <math>\geq 30\text{pF}</math>, Q <math>\geq 1000</math>; Cap <math>&lt; 30\text{pF}</math>, Q <math>\geq 400 + 20\text{C}</math></p> <p>X7R:</p> <table border="1"> <thead> <tr> <th>Rated vol.</th> <th>D.F. <math>\leq</math></th> <th colspan="2">Exception of D.F. <math>\leq</math></th> </tr> </thead> <tbody> <tr> <td rowspan="3"><math>\geq 100\text{V}</math></td> <td><math>\leq 2.5\%</math></td> <td><math>\leq 3\%</math></td> <td><math>1206 \geq 0.47\mu\text{F}</math></td> </tr> <tr> <td></td> <td><math>\leq 5\%</math></td> <td>0603 <math>\geq 0.068\mu\text{F}</math>; 0805 <math>&gt; 0.1\mu\text{F}</math>; 1206 <math>\geq 1\mu\text{F}</math>; 1210 <math>\geq 2.2\mu\text{F}</math>;</td> </tr> <tr> <td></td> <td><math>\leq 10\%</math></td> <td>0805 <math>&gt; 0.22\mu\text{F}</math>; 1210 <math>\geq 3.3\mu\text{F}</math></td> </tr> <tr> <td rowspan="3">50V</td> <td><math>\leq 2.5\%</math></td> <td><math>\leq 3\%</math></td> <td>0201(50V); 0603 <math>\geq 0.047\mu\text{F}</math>; 0805 <math>\geq 0.18\mu\text{F}</math>; 1206 <math>\geq 0.47\mu\text{F}</math></td> </tr> <tr> <td></td> <td><math>\leq 5\%</math></td> <td>0201 <math>\geq 0.01\mu\text{F}</math>; 1210 <math>\geq 3.3\mu\text{F}</math></td> </tr> <tr> <td></td> <td><math>\leq 10\%</math></td> <td>0402 <math>\geq 0.012\mu\text{F}</math>; 0603 <math>&gt; 0.1\mu\text{F}</math>; 0805/X7R <math>&gt; 0.47\mu\text{F}</math>;  1206 <math>\geq 2.2\mu\text{F}</math>; 1210 <math>\geq 10\mu\text{F}</math></td> </tr> <tr> <td rowspan="3">35V</td> <td><math>\leq 3.5\%</math></td> <td><math>\leq 10\%</math></td> <td>0603 <math>\geq 1\mu\text{F}</math>; 0805 <math>\geq 2.2\mu\text{F}</math>; 1206 <math>\geq 2.2\mu\text{F}</math>; 1210 <math>\geq 10\mu\text{F}</math></td> </tr> <tr> <td></td> <td><math>\leq 5\%</math></td> <td>0201 <math>\geq 0.01\mu\text{F}</math>; 0805 <math>\geq 1\mu\text{F}</math>; 1210 <math>\geq 10\mu\text{F}</math></td> </tr> <tr> <td></td> <td><math>\leq 7\%</math></td> <td>0603 <math>\geq 0.33\mu\text{F}</math></td> </tr> <tr> <td rowspan="3">25V</td> <td><math>\leq 3.5\%</math></td> <td><math>\leq 10\%</math></td> <td>0201 <math>\geq 0.1\mu\text{F}</math>; 0402 <math>\geq 0.056\mu\text{F}</math>; 0603 <math>\geq 0.47\mu\text{F}</math>;  0805 <math>\geq 2.2\mu\text{F}</math>; 1206 <math>\geq 4.7\mu\text{F}</math>; 1210 <math>\geq 22\mu\text{F}</math></td> </tr> <tr> <td></td> <td><math>\leq 12.5\%</math></td> <td>0402 <math>\geq 0.47\mu\text{F}</math></td> </tr> <tr> <td rowspan="3">16V</td> <td><math>\leq 3.5\%</math></td> <td><math>\leq 5\%</math></td> <td>0201 <math>\geq 0.01\mu\text{F}</math>; 0402 <math>\geq 0.033\mu\text{F}</math>; 0603 <math>\geq 0.15\mu\text{F}</math>;  0805 <math>\geq 0.68\mu\text{F}</math>; 1206 <math>\geq 2.2\mu\text{F}</math>; 1210 <math>\geq 4.7\mu\text{F}</math></td> </tr> <tr> <td></td> <td><math>\leq 10\%</math></td> <td>0201/X7R <math>\geq 0.022\mu\text{F}</math>; 0402 <math>\geq 0.22\mu\text{F}</math>;  0603 <math>\geq 0.47\mu\text{F}</math>; 0805 <math>\geq 2.2\mu\text{F}</math>; 1206 <math>\geq 4.7\mu\text{F}</math>; 1210 <math>\geq 22\mu\text{F}</math></td> </tr> <tr> <td rowspan="3">10V</td> <td><math>\leq 5\%</math></td> <td><math>\leq 10\%</math></td> <td>0603 <math>\geq 0.33\mu\text{F}</math>; 0805 <math>\geq 2.2\mu\text{F}</math>; 1206 <math>\geq 2.2\mu\text{F}</math>; 1210 <math>\geq 22\mu\text{F}</math></td> </tr> <tr> <td></td> <td><math>\leq 15\%</math></td> <td>0201 <math>\geq 0.1\mu\text{F}</math>; 0402 <math>\geq 1\mu\text{F}</math></td> </tr> <tr> <td rowspan="3">6.3V</td> <td><math>\leq 10\%</math></td> <td><math>\leq 15\%</math></td> <td>0201 <math>\geq 0.1\mu\text{F}</math>; 0402 <math>\geq 1\mu\text{F}</math>; 0603 <math>\geq 10\mu\text{F}</math>;  0805 <math>\geq 4.7\mu\text{F}</math>; 1206 <math>\geq 47\mu\text{F}</math>; 1210 <math>\geq 100\mu\text{F}</math></td> </tr> <tr> <td></td> <td><math>\leq 20\%</math></td> <td>0402 <math>\geq 2.2\mu\text{F}</math></td> </tr> <tr> <td>4V</td> <td><math>\leq 15\%</math></td> <td>---</td> <td>---</td> </tr> <tr> <td colspan="7" style="text-align: center;">X5R:</td></tr> <tr> <td colspan="7" style="text-align: center;">*Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.</td></tr> <tr> <td colspan="7" style="text-align: center;">Copyright © WALGIN Technology Corporation 2021</td></tr> <tr> <td colspan="7" style="text-align: center;">Y5V:</td></tr> <tr> <td colspan="7" style="text-align: center;">Rated vol. D.F. <math>\leq</math> Exception of D.F. <math>\leq</math></td></tr> <tr> <td rowspan="2"><math>\geq 50\text{V}</math></td> <td rowspan="2"><math>\leq 5\%</math></td> <td><math>\leq 7\%</math></td> <td>0603 <math>\geq 0.1\mu\text{F}</math>; 0805 <math>\geq 0.47\mu\text{F}</math>; 1206 <math>\geq 4.7\mu\text{F}</math></td> </tr> <tr> <td><math>\leq 12.5\%</math></td> <td>1210 <math>\geq 6.8\mu\text{F}</math></td> </tr> <tr> <td>35V</td> <td><math>\leq 7\%</math></td> <td>---</td> <td>---</td> </tr> <tr> <td rowspan="2">25V</td> <td rowspan="2"><math>\leq 5\%</math></td> <td><math>\leq 7\%</math></td> <td>0402 <math>\geq 0.047\mu\text{F}</math>; 0603 <math>\geq 0.1\mu\text{F}</math>; 0805 <math>\geq 0.33\mu\text{F}</math>;  1206 <math>\geq 1\mu\text{F}</math>; 1210 <math>\geq 4.7\mu\text{F}</math></td> </tr> <tr> <td><math>\leq 9\%</math></td> <td>0402 <math>\geq 0.068\mu\text{F}</math>; 0603 <math>\geq 0.47\mu\text{F}</math>; 1206 <math>\geq 4.7\mu\text{F}</math>;  1210 <math>\geq 22\mu\text{F}</math></td> </tr> <tr> <td>16V (C&lt;1.0μF)</td> <td><math>\leq 7\%</math></td> <td><math>\leq 9\%</math></td> <td>0402 <math>\geq 0.068\mu\text{F}</math>; 0603 <math>\geq 0.68\mu\text{F}</math></td> </tr> <tr> <td>16V (C≥1.0μF)</td> <td><math>\leq 9\%</math></td> <td><math>\leq 12.5\%</math></td> <td>0603 <math>\geq 2.2\mu\text{F}</math>; 0805 <math>\geq 3.3\mu\text{F}</math>; 1206 <math>\geq 10\mu\text{F}</math>;  1210 <math>\geq 22\mu\text{F}</math>; 1812 <math>\geq 47\mu\text{F}</math></td> </tr> <tr> <td>10V</td> <td><math>\leq 12.5\%</math></td> <td><math>\leq 20\%</math></td> <td>0402 <math>\geq 0.47\mu\text{F}</math></td> </tr> <tr> <td>6.3V</td> <td><math>\leq 20\%</math></td> <td>---</td> <td>---</td> </tr> </tbody> </table>	Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$		$\geq 100\text{V}$	$\leq 2.5\%$	$\leq 3\%$	$1206 \geq 0.47\mu\text{F}$		$\leq 5\%$	0603 $\geq 0.068\mu\text{F}$ ; 0805 $> 0.1\mu\text{F}$ ; 1206 $\geq 1\mu\text{F}$ ; 1210 $\geq 2.2\mu\text{F}$ ;		$\leq 10\%$	0805 $> 0.22\mu\text{F}$ ; 1210 $\geq 3.3\mu\text{F}$	50V	$\leq 2.5\%$	$\leq 3\%$	0201(50V); 0603 $\geq 0.047\mu\text{F}$ ; 0805 $\geq 0.18\mu\text{F}$ ; 1206 $\geq 0.47\mu\text{F}$		$\leq 5\%$	0201 $\geq 0.01\mu\text{F}$ ; 1210 $\geq 3.3\mu\text{F}$		$\leq 10\%$	0402 $\geq 0.012\mu\text{F}$ ; 0603 $> 0.1\mu\text{F}$ ; 0805/X7R $> 0.47\mu\text{F}$ ; 1206 $\geq 2.2\mu\text{F}$ ; 1210 $\geq 10\mu\text{F}$	35V	$\leq 3.5\%$	$\leq 10\%$	0603 $\geq 1\mu\text{F}$ ; 0805 $\geq 2.2\mu\text{F}$ ; 1206 $\geq 2.2\mu\text{F}$ ; 1210 $\geq 10\mu\text{F}$		$\leq 5\%$	0201 $\geq 0.01\mu\text{F}$ ; 0805 $\geq 1\mu\text{F}$ ; 1210 $\geq 10\mu\text{F}$		$\leq 7\%$	0603 $\geq 0.33\mu\text{F}$	25V	$\leq 3.5\%$	$\leq 10\%$	0201 $\geq 0.1\mu\text{F}$ ; 0402 $\geq 0.056\mu\text{F}$ ; 0603 $\geq 0.47\mu\text{F}$ ; 0805 $\geq 2.2\mu\text{F}$ ; 1206 $\geq 4.7\mu\text{F}$ ; 1210 $\geq 22\mu\text{F}$		$\leq 12.5\%$	0402 $\geq 0.47\mu\text{F}$	16V	$\leq 3.5\%$	$\leq 5\%$	0201 $\geq 0.01\mu\text{F}$ ; 0402 $\geq 0.033\mu\text{F}$ ; 0603 $\geq 0.15\mu\text{F}$ ; 0805 $\geq 0.68\mu\text{F}$ ; 1206 $\geq 2.2\mu\text{F}$ ; 1210 $\geq 4.7\mu\text{F}$		$\leq 10\%$	0201/X7R $\geq 0.022\mu\text{F}$ ; 0402 $\geq 0.22\mu\text{F}$ ; 0603 $\geq 0.47\mu\text{F}$ ; 0805 $\geq 2.2\mu\text{F}$ ; 1206 $\geq 4.7\mu\text{F}$ ; 1210 $\geq 22\mu\text{F}$	10V	$\leq 5\%$	$\leq 10\%$	0603 $\geq 0.33\mu\text{F}$ ; 0805 $\geq 2.2\mu\text{F}$ ; 1206 $\geq 2.2\mu\text{F}$ ; 1210 $\geq 22\mu\text{F}$		$\leq 15\%$	0201 $\geq 0.1\mu\text{F}$ ; 0402 $\geq 1\mu\text{F}$	6.3V	$\leq 10\%$	$\leq 15\%$	0201 $\geq 0.1\mu\text{F}$ ; 0402 $\geq 1\mu\text{F}$ ; 0603 $\geq 10\mu\text{F}$ ; 0805 $\geq 4.7\mu\text{F}$ ; 1206 $\geq 47\mu\text{F}$ ; 1210 $\geq 100\mu\text{F}$		$\leq 20\%$	0402 $\geq 2.2\mu\text{F}$	4V	$\leq 15\%$	---	---	X5R:							*Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.							Copyright © WALGIN Technology Corporation 2021							Y5V:							Rated vol. D.F. $\leq$ Exception of D.F. $\leq$							$\geq 50\text{V}$	$\leq 5\%$	$\leq 7\%$	0603 $\geq 0.1\mu\text{F}$ ; 0805 $\geq 0.47\mu\text{F}$ ; 1206 $\geq 4.7\mu\text{F}$	$\leq 12.5\%$	1210 $\geq 6.8\mu\text{F}$	35V	$\leq 7\%$	---	---	25V	$\leq 5\%$	$\leq 7\%$	0402 $\geq 0.047\mu\text{F}$ ; 0603 $\geq 0.1\mu\text{F}$ ; 0805 $\geq 0.33\mu\text{F}$ ; 1206 $\geq 1\mu\text{F}$ ; 1210 $\geq 4.7\mu\text{F}$	$\leq 9\%$	0402 $\geq 0.068\mu\text{F}$ ; 0603 $\geq 0.47\mu\text{F}$ ; 1206 $\geq 4.7\mu\text{F}$ ; 1210 $\geq 22\mu\text{F}$	16V (C<1.0μF)	$\leq 7\%$	$\leq 9\%$	0402 $\geq 0.068\mu\text{F}$ ; 0603 $\geq 0.68\mu\text{F}$	16V (C≥1.0μF)	$\leq 9\%$	$\leq 12.5\%$	0603 $\geq 2.2\mu\text{F}$ ; 0805 $\geq 3.3\mu\text{F}$ ; 1206 $\geq 10\mu\text{F}$ ; 1210 $\geq 22\mu\text{F}$ ; 1812 $\geq 47\mu\text{F}$	10V	$\leq 12.5\%$	$\leq 20\%$	0402 $\geq 0.47\mu\text{F}$	6.3V	$\leq 20\%$	---	---
Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$																																																																																																																																						
$\geq 100\text{V}$	$\leq 2.5\%$	$\leq 3\%$	$1206 \geq 0.47\mu\text{F}$																																																																																																																																					
		$\leq 5\%$	0603 $\geq 0.068\mu\text{F}$ ; 0805 $> 0.1\mu\text{F}$ ; 1206 $\geq 1\mu\text{F}$ ; 1210 $\geq 2.2\mu\text{F}$ ;																																																																																																																																					
		$\leq 10\%$	0805 $> 0.22\mu\text{F}$ ; 1210 $\geq 3.3\mu\text{F}$																																																																																																																																					
50V	$\leq 2.5\%$	$\leq 3\%$	0201(50V); 0603 $\geq 0.047\mu\text{F}$ ; 0805 $\geq 0.18\mu\text{F}$ ; 1206 $\geq 0.47\mu\text{F}$																																																																																																																																					
		$\leq 5\%$	0201 $\geq 0.01\mu\text{F}$ ; 1210 $\geq 3.3\mu\text{F}$																																																																																																																																					
		$\leq 10\%$	0402 $\geq 0.012\mu\text{F}$ ; 0603 $> 0.1\mu\text{F}$ ; 0805/X7R $> 0.47\mu\text{F}$ ; 1206 $\geq 2.2\mu\text{F}$ ; 1210 $\geq 10\mu\text{F}$																																																																																																																																					
35V	$\leq 3.5\%$	$\leq 10\%$	0603 $\geq 1\mu\text{F}$ ; 0805 $\geq 2.2\mu\text{F}$ ; 1206 $\geq 2.2\mu\text{F}$ ; 1210 $\geq 10\mu\text{F}$																																																																																																																																					
		$\leq 5\%$	0201 $\geq 0.01\mu\text{F}$ ; 0805 $\geq 1\mu\text{F}$ ; 1210 $\geq 10\mu\text{F}$																																																																																																																																					
		$\leq 7\%$	0603 $\geq 0.33\mu\text{F}$																																																																																																																																					
25V	$\leq 3.5\%$	$\leq 10\%$	0201 $\geq 0.1\mu\text{F}$ ; 0402 $\geq 0.056\mu\text{F}$ ; 0603 $\geq 0.47\mu\text{F}$ ; 0805 $\geq 2.2\mu\text{F}$ ; 1206 $\geq 4.7\mu\text{F}$ ; 1210 $\geq 22\mu\text{F}$																																																																																																																																					
		$\leq 12.5\%$	0402 $\geq 0.47\mu\text{F}$																																																																																																																																					
	16V	$\leq 3.5\%$	$\leq 5\%$	0201 $\geq 0.01\mu\text{F}$ ; 0402 $\geq 0.033\mu\text{F}$ ; 0603 $\geq 0.15\mu\text{F}$ ; 0805 $\geq 0.68\mu\text{F}$ ; 1206 $\geq 2.2\mu\text{F}$ ; 1210 $\geq 4.7\mu\text{F}$																																																																																																																																				
		$\leq 10\%$	0201/X7R $\geq 0.022\mu\text{F}$ ; 0402 $\geq 0.22\mu\text{F}$ ; 0603 $\geq 0.47\mu\text{F}$ ; 0805 $\geq 2.2\mu\text{F}$ ; 1206 $\geq 4.7\mu\text{F}$ ; 1210 $\geq 22\mu\text{F}$																																																																																																																																					
10V		$\leq 5\%$	$\leq 10\%$	0603 $\geq 0.33\mu\text{F}$ ; 0805 $\geq 2.2\mu\text{F}$ ; 1206 $\geq 2.2\mu\text{F}$ ; 1210 $\geq 22\mu\text{F}$																																																																																																																																				
		$\leq 15\%$	0201 $\geq 0.1\mu\text{F}$ ; 0402 $\geq 1\mu\text{F}$																																																																																																																																					
	6.3V	$\leq 10\%$	$\leq 15\%$	0201 $\geq 0.1\mu\text{F}$ ; 0402 $\geq 1\mu\text{F}$ ; 0603 $\geq 10\mu\text{F}$ ; 0805 $\geq 4.7\mu\text{F}$ ; 1206 $\geq 47\mu\text{F}$ ; 1210 $\geq 100\mu\text{F}$																																																																																																																																				
		$\leq 20\%$	0402 $\geq 2.2\mu\text{F}$																																																																																																																																					
4V		$\leq 15\%$	---	---																																																																																																																																				
X5R:																																																																																																																																								
*Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.																																																																																																																																								
Copyright © WALGIN Technology Corporation 2021																																																																																																																																								
Y5V:																																																																																																																																								
Rated vol. D.F. $\leq$ Exception of D.F. $\leq$																																																																																																																																								
$\geq 50\text{V}$	$\leq 5\%$	$\leq 7\%$	0603 $\geq 0.1\mu\text{F}$ ; 0805 $\geq 0.47\mu\text{F}$ ; 1206 $\geq 4.7\mu\text{F}$																																																																																																																																					
		$\leq 12.5\%$	1210 $\geq 6.8\mu\text{F}$																																																																																																																																					
35V	$\leq 7\%$	---	---																																																																																																																																					
25V	$\leq 5\%$	$\leq 7\%$	0402 $\geq 0.047\mu\text{F}$ ; 0603 $\geq 0.1\mu\text{F}$ ; 0805 $\geq 0.33\mu\text{F}$ ; 1206 $\geq 1\mu\text{F}$ ; 1210 $\geq 4.7\mu\text{F}$																																																																																																																																					
		$\leq 9\%$	0402 $\geq 0.068\mu\text{F}$ ; 0603 $\geq 0.47\mu\text{F}$ ; 1206 $\geq 4.7\mu\text{F}$ ; 1210 $\geq 22\mu\text{F}$																																																																																																																																					
16V (C<1.0μF)	$\leq 7\%$	$\leq 9\%$	0402 $\geq 0.068\mu\text{F}$ ; 0603 $\geq 0.68\mu\text{F}$																																																																																																																																					
16V (C≥1.0μF)	$\leq 9\%$	$\leq 12.5\%$	0603 $\geq 2.2\mu\text{F}$ ; 0805 $\geq 3.3\mu\text{F}$ ; 1206 $\geq 10\mu\text{F}$ ; 1210 $\geq 22\mu\text{F}$ ; 1812 $\geq 47\mu\text{F}$																																																																																																																																					
10V	$\leq 12.5\%$	$\leq 20\%$	0402 $\geq 0.47\mu\text{F}$																																																																																																																																					
6.3V	$\leq 20\%$	---	---																																																																																																																																					

\* "Room condition" Temperature: 15 to 35°C, Relative humidity: 25 to 75%, Atmospheric pressure: 86 to 106kPa.

Multilayer Ceramic Capacitors

No.	Item	Test Condition		Requirements		
	<b>Q/D.F. (Dissipation Factor)</b>			X6S:		
		Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$		
		$\geq 100V$	$\leq 2.5\%$	$\leq 3\%$ 1206 $\geq 0.47\mu F$ $\leq 5\%$ 0603 $\geq 0.068\mu F$ ; 0805 $> 0.1\mu F$ ; 1206 $\geq 1\mu F$ ; 1210 $\geq 2.2\mu F$ $\leq 10\%$ 0805 $> 0.22\mu F$ ; 1210 $\geq 3.3\mu F$		
		$50V$	$\leq 2.5\%$	$\leq 3\%$ 0201(50V); 0603 $\geq 0.047\mu F$ ; 0805 $\geq 0.18\mu F$ ; 1206 $\geq 0.47\mu F$ $\leq 5\%$ 0201 $\geq 0.01\mu F$ ; 1210 $\geq 3.3\mu F$ $\leq 10\%$ 0402 $\geq 0.012\mu F$ ; 0603 $> 0.1\mu F$ ; 0805 $\geq 1\mu F$ ; 1206 $\geq 2.2\mu F$ ; 1210 $\geq 10\mu F$		
		$35V$	$\leq 3.5\%$	$\leq 10\%$ 0603 $\geq 1\mu F$ ; 0805 $\geq 2.2\mu F$ ; 1206 $\geq 2.2\mu F$ ; 1210 $\geq 10\mu F$ $\leq 5\%$ 0201 $\geq 0.01\mu F$ ; 0805 $\geq 1\mu F$ ; 1210 $\geq 10\mu F$ $\leq 7\%$ 0603 $\geq 0.33\mu F$ $\leq 10\%$ 0201 $\geq 0.1\mu F$ ; 0402 $\geq 0.10\mu F$ ; 0603 $\geq 0.47\mu F$ ; 0805 $\geq 2.2\mu F$ ; 1206 $\geq 4.7\mu F$ ; 1210 $\geq 22\mu F$		
		$25V$	$\leq 3.5\%$	$\leq 12.5\%$ 0402 $\geq 0.47\mu F$ ; 0805 $= 10\mu F$		
		$16V$	$\leq 3.5\%$	$\leq 5\%$ 0201 $\geq 0.01\mu F$ ; 0402 $\geq 0.033\mu F$ ; 0603 $\geq 0.15\mu F$ ; 0805 $\geq 0.68\mu F$ ; 1206 $\geq 2.2\mu F$ ; 1210 $\geq 4.7\mu F$ $\leq 10\%$ 0201 $\geq 0.1\mu F$ ; 0402 $\geq 0.22\mu F$ ; 0603 $> 0.47\mu F$ ; 0805 $\geq 2.2\mu F$ ; 1206 $\geq 4.7\mu F$ ; 1210 $\geq 22\mu F$ $\leq 12.5\%$ 0402 $\geq 1\mu F$ ; 0805 $\geq 10\mu F$		
		$10V$	$\leq 5\%$	$\leq 10\%$ 0201 $\geq 0.012\mu F$ ; 0402 $\geq 0.22\mu F$ ; 0603 $\geq 0.33\mu F$ ; 0805 $\geq 2.2\mu F$ ; 1206 $\geq 2.2\mu F$ ; 1210 $\geq 22\mu F$ $\leq 12.5\%$ 0805 $\geq 10\mu F$ $\leq 15\%$ 0201 $\geq 0.1\mu F$ ; 0402 $\geq 1\mu F$		
		$6.3V$	$\leq 10\%$	$\leq 15\%$ 0201 $\geq 0.1\mu F$ ; 0402 $\geq 0.47\mu F$ ; 0603 $\geq 10\mu F$ ; 0805 $\geq 4.7\mu F$ ; 1206 $\geq 47\mu F$ ; 1210 $\geq 100\mu F$ $\leq 20\%$ 0402 $\geq 2.2\mu F$		
		$4V$	$\leq 15\%$	---		
				X7S:		
		Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$		
		$\geq 100V$	$\leq 2.5\%$	$\leq 3\%$ 1206 $\geq 0.47\mu F$ $\leq 5\%$ 0603 $\geq 0.068\mu F$ ; 0805 $> 0.1\mu F$ ; 1206 $\geq 1\mu F$ ; 1210 $\geq 2.2\mu F$ $\leq 10\%$ 0805 $> 0.22\mu F$ ; 1210 $\geq 3.3\mu F$		
		$50V$	$\leq 2.5\%$	$\leq 3\%$ 0201(50V); 0603 $\geq 0.047\mu F$ ; 0805 $\geq 0.18\mu F$ ; 1206 $\geq 0.47\mu F$ $\leq 5\%$ 0201 $\geq 0.01\mu F$ ; 1210 $\geq 3.3\mu F$ $\leq 10\%$ 0402 $\geq 0.012\mu F$ ; 0603 $> 0.1\mu F$ ; 0805 $\geq 1\mu F$ ; 1206 $\geq 2.2\mu F$ ; 1210 $\geq 10\mu F$		
		$35V$	$\leq 3.5\%$	$\leq 10\%$ 0603 $\geq 1\mu F$ ; 0805 $\geq 2.2\mu F$ ; 1206 $\geq 2.2\mu F$ ; 1210 $\geq 10\mu F$ $\leq 5\%$ 0201 $\geq 0.01\mu F$ ; 0805 $\geq 1\mu F$ ; 1210 $\geq 10\mu F$ $\leq 7\%$ 0603 $\geq 0.33\mu F$ $\leq 10\%$ 0201 $\geq 0.1\mu F$ ; 0402 $\geq 0.10\mu F$ ; 0603 $\geq 0.47\mu F$ ; 0805 $\geq 2.2\mu F$ ; 1206 $\geq 4.7\mu F$ ; 1210 $\geq 22\mu F$ $\leq 12.5\%$ 0402 $\geq 0.47\mu F$		
		$25V$	$\leq 3.5\%$	$\leq 5\%$ 0201 $\geq 0.01\mu F$ ; 0402 $\geq 0.033\mu F$ ; 0603 $\geq 0.15\mu F$ ; 0805 $\geq 0.68\mu F$ ; 1206 $\geq 2.2\mu F$ ; 1210 $\geq 4.7\mu F$ $\leq 10\%$ 0201 $\geq 0.1\mu F$ ; 0402 $\geq 0.22\mu F$ ; 0603 $> 0.47\mu F$ ; 0805 $\geq 2.2\mu F$ ; 1206 $\geq 4.7\mu F$ ; 1210 $\geq 22\mu F$		
		$16V$	$\leq 3.5\%$	$\leq 10\%$ 0201 $\geq 0.012\mu F$ ; 0402 $\geq 0.22\mu F$ ; 0603 $\geq 0.33\mu F$ ; 0805 $\geq 4.7\mu F$ ; 1206 $\geq 47\mu F$ ; 1210 $\geq 100\mu F$ $\leq 15\%$ 0402 $\geq 2.2\mu F$		
		$10V$	$\leq 5\%$	$\leq 10\%$ 0201 $\geq 0.012\mu F$ ; 0402 $\geq 0.22\mu F$ ; 0603 $\geq 0.33\mu F$ ; 0805 $\geq 2.2\mu F$ ; 1206 $\geq 2.2\mu F$ ; 1210 $\geq 22\mu F$ $\leq 15\%$ 0201 $\geq 0.1\mu F$ ; 0402 $\geq 1\mu F$		
		$6.3V$	$\leq 10\%$	$\leq 15\%$ 0201 $\geq 0.1\mu F$ ; 0402 $\geq 1\mu F$ ; 0603 $\geq 10\mu F$ ; 0805 $\geq 4.7\mu F$ ; 1206 $\geq 47\mu F$ ; 1210 $\geq 100\mu F$ $\leq 20\%$ 0402 $\geq 2.2\mu F$		
		$4V$	$\leq 15\%$	---		
<b>4.</b>	<b>Dielectric Strength</b>	* To apply voltage ( $\leq 100V$ ) 250%. * Duration: 1 to 5 sec. * Charge and discharge current less than 50mA.	* No evidence of damage or flash over during test.			

\* "Room condition" Temperature: 15 to 35°C, Relative humidity: 25 to 75%, Atmospheric pressure: 86 to 106kPa.

Multilayer Ceramic Capacitors

No.	Item	Test Condition	Requirements																																										
5.	Insulation Resistance	<p>*Test temp.: Room Temperature.</p> <p>*To apply rated voltage for MAX. 120sec.</p>	<p>10GΩ or <math>R_x C \geq 500\Omega \cdot F</math> whichever is smaller.</p> <p>Class II (X7R, X7E, X5R, X6S, X7S, Y5V):</p> <table border="1"> <tr> <td>Rated voltage</td> <td>Insulation Resistance</td> </tr> <tr> <td>100V: All X7R</td> <td rowspan="5">10GΩ or <math>R_x C \geq 100 \Omega \cdot F</math> whichever is smaller.</td> </tr> <tr> <td>50V: 0402≥0.01μF; 0603≥1μF; 0805≥1μF; 1206≥4.7μF; 1210≥4.7μF</td> </tr> <tr> <td>35V: 0805≥2.2μF; 1206≥2.2μF; 1210≥10μF</td> </tr> <tr> <td>25V: 0402≥1μF; 0603≥2.2μF; 0805≥2.2μF; 1206≥10μF; 1210≥10μF</td> </tr> <tr> <td>16V: 0201≥0.1μF; 0402≥0.22μF; 0603≥1μF; 0805≥2.2μF; 1206≥10μF; 1210≥47μF</td> </tr> <tr> <td>10V: 0201≥47nF; 0402≥0.47μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥47μF</td> </tr> <tr> <td>6.3V ; 4V ; Size≥1812</td> </tr> <tr> <td>Rated voltage</td> <td>Insulation Resistance</td> </tr> <tr> <td>All X6S items, All X7S items</td> <td rowspan="5"><math>R_x C \geq 50 \Omega \cdot F</math>.</td> </tr> <tr> <td>100V: 1210≥3.3μF</td> </tr> <tr> <td>50V: 0402≥0.1μF; 0603≥2.2μF; 0805≥10μF; 1206≥10μF</td> </tr> <tr> <td>35V: 0603≥1μF;</td> </tr> <tr> <td>25V: 0201≥0.1μF; 0402≥2.2μF; 0603≥10μF; 0805≥10μF; 1206≥22μF</td> </tr> <tr> <td>16V: 0603≥10μF; 0402≥1μF; 0201≥0.22μF</td> </tr> <tr> <td>10V: 0201≥0.1μF; 0402≥1μF; 0603≥10μF; 0805≥47μF</td> </tr> <tr> <td>6.3V: 0201≥0.1μF; 0402≥1μF; 0603&gt;4.7μF; 0805≥47μF; 1206≥10μF</td> </tr> <tr> <td>4V: 0603≥22μF; 0805≥47μF; 1206≥100μF</td> </tr> </table>	Rated voltage	Insulation Resistance	100V: All X7R	10GΩ or $R_x C \geq 100 \Omega \cdot F$ whichever is smaller.	50V: 0402≥0.01μF; 0603≥1μF; 0805≥1μF; 1206≥4.7μF; 1210≥4.7μF	35V: 0805≥2.2μF; 1206≥2.2μF; 1210≥10μF	25V: 0402≥1μF; 0603≥2.2μF; 0805≥2.2μF; 1206≥10μF; 1210≥10μF	16V: 0201≥0.1μF; 0402≥0.22μF; 0603≥1μF; 0805≥2.2μF; 1206≥10μF; 1210≥47μF	10V: 0201≥47nF; 0402≥0.47μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥47μF	6.3V ; 4V ; Size≥1812	Rated voltage	Insulation Resistance	All X6S items, All X7S items	$R_x C \geq 50 \Omega \cdot F$ .	100V: 1210≥3.3μF	50V: 0402≥0.1μF; 0603≥2.2μF; 0805≥10μF; 1206≥10μF	35V: 0603≥1μF;	25V: 0201≥0.1μF; 0402≥2.2μF; 0603≥10μF; 0805≥10μF; 1206≥22μF	16V: 0603≥10μF; 0402≥1μF; 0201≥0.22μF	10V: 0201≥0.1μF; 0402≥1μF; 0603≥10μF; 0805≥47μF	6.3V: 0201≥0.1μF; 0402≥1μF; 0603>4.7μF; 0805≥47μF; 1206≥10μF	4V: 0603≥22μF; 0805≥47μF; 1206≥100μF																				
Rated voltage	Insulation Resistance																																												
100V: All X7R	10GΩ or $R_x C \geq 100 \Omega \cdot F$ whichever is smaller.																																												
50V: 0402≥0.01μF; 0603≥1μF; 0805≥1μF; 1206≥4.7μF; 1210≥4.7μF																																													
35V: 0805≥2.2μF; 1206≥2.2μF; 1210≥10μF																																													
25V: 0402≥1μF; 0603≥2.2μF; 0805≥2.2μF; 1206≥10μF; 1210≥10μF																																													
16V: 0201≥0.1μF; 0402≥0.22μF; 0603≥1μF; 0805≥2.2μF; 1206≥10μF; 1210≥47μF																																													
10V: 0201≥47nF; 0402≥0.47μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥47μF																																													
6.3V ; 4V ; Size≥1812																																													
Rated voltage	Insulation Resistance																																												
All X6S items, All X7S items	$R_x C \geq 50 \Omega \cdot F$ .																																												
100V: 1210≥3.3μF																																													
50V: 0402≥0.1μF; 0603≥2.2μF; 0805≥10μF; 1206≥10μF																																													
35V: 0603≥1μF;																																													
25V: 0201≥0.1μF; 0402≥2.2μF; 0603≥10μF; 0805≥10μF; 1206≥22μF																																													
16V: 0603≥10μF; 0402≥1μF; 0201≥0.22μF																																													
10V: 0201≥0.1μF; 0402≥1μF; 0603≥10μF; 0805≥47μF																																													
6.3V: 0201≥0.1μF; 0402≥1μF; 0603>4.7μF; 0805≥47μF; 1206≥10μF																																													
4V: 0603≥22μF; 0805≥47μF; 1206≥100μF																																													
6.	Temperature Coefficient	<p>With no electrical load.</p> <table border="1"> <tr> <td>T.C.</td> <td>Operating Temp</td> </tr> <tr> <td>NPO</td> <td>-55~125°C at 25°C</td> </tr> <tr> <td>X7R</td> <td>-55~125°C at 25°C</td> </tr> <tr> <td>X7S</td> <td>-55 ~ 125°C at 25°C</td> </tr> <tr> <td>X5R</td> <td>-55~ 85°C at 25°C</td> </tr> <tr> <td>X6S</td> <td>-55~105°C at 25°C</td> </tr> <tr> <td>Y5V</td> <td>-25~ 85°C at 20°C</td> </tr> </table> <p>*Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. * Measurement voltage for Class II:</p> <table border="1"> <tr> <td>01005</td> <td>0201</td> </tr> <tr> <td>Cap≤0.01μF: 0.5V</td> <td>Cap&lt;0.1μF: 1V</td> </tr> <tr> <td>Cap&gt;0.01μF: 0.2V</td> <td>0.1μF≤Cap&lt;1μF: 0.2V*</td> </tr> <tr> <td></td> <td>Cap≥1μF: 0.1V*</td> </tr> <tr> <td>*0201X104/6.3V~25V: 0.5V 0201X224/10V: 0.5V</td> <td>*0201S104/6.3V~16V: 0.3V 0201S224/6.3V: 0.3V 0201X105/6.3V&amp;10V: 0.3V</td> </tr> <tr> <td>0402</td> <td>0603</td> </tr> <tr> <td>Cap&lt;1μF: 1V</td> <td>Cap&lt;1μF: 1V</td> </tr> <tr> <td>Cap=1μF: 0.5V** 0402B224-16V: 0.5V 0402B474-10V: 0.5V 0402X475M6R3: 0.5V</td> <td>1μF≤Cap≤4.7μF: 0.5V</td> </tr> <tr> <td>1μF&lt;Cap&lt;10μF: 0.2V **0402B105M6R3V: 0.2V</td> <td>Cap&gt;4.7μF: 0.2V</td> </tr> <tr> <td>Cap≥10μF: 0.1V</td> <td></td> </tr> <tr> <td>0805</td> <td>1206/1210</td> </tr> <tr> <td>Cap&lt;10μF: 1V</td> <td>Cap≤10μF: 1V</td> </tr> <tr> <td>Cap=10μF: 0.5V 0805B475/6.3V~25V: 0.5V</td> <td>10μF&lt;Cap≤100μF: 0.5V</td> </tr> <tr> <td>Cap&gt;10μF: 0.2V</td> <td>Cap&gt;100μF: 0.2V</td> </tr> </table>	T.C.	Operating Temp	NPO	-55~125°C at 25°C	X7R	-55~125°C at 25°C	X7S	-55 ~ 125°C at 25°C	X5R	-55~ 85°C at 25°C	X6S	-55~105°C at 25°C	Y5V	-25~ 85°C at 20°C	01005	0201	Cap≤0.01μF: 0.5V	Cap<0.1μF: 1V	Cap>0.01μF: 0.2V	0.1μF≤Cap<1μF: 0.2V*		Cap≥1μF: 0.1V*	*0201X104/6.3V~25V: 0.5V 0201X224/10V: 0.5V	*0201S104/6.3V~16V: 0.3V 0201S224/6.3V: 0.3V 0201X105/6.3V&10V: 0.3V	0402	0603	Cap<1μF: 1V	Cap<1μF: 1V	Cap=1μF: 0.5V** 0402B224-16V: 0.5V 0402B474-10V: 0.5V 0402X475M6R3: 0.5V	1μF≤Cap≤4.7μF: 0.5V	1μF<Cap<10μF: 0.2V **0402B105M6R3V: 0.2V	Cap>4.7μF: 0.2V	Cap≥10μF: 0.1V		0805	1206/1210	Cap<10μF: 1V	Cap≤10μF: 1V	Cap=10μF: 0.5V 0805B475/6.3V~25V: 0.5V	10μF<Cap≤100μF: 0.5V	Cap>10μF: 0.2V	Cap>100μF: 0.2V	
T.C.	Operating Temp																																												
NPO	-55~125°C at 25°C																																												
X7R	-55~125°C at 25°C																																												
X7S	-55 ~ 125°C at 25°C																																												
X5R	-55~ 85°C at 25°C																																												
X6S	-55~105°C at 25°C																																												
Y5V	-25~ 85°C at 20°C																																												
01005	0201																																												
Cap≤0.01μF: 0.5V	Cap<0.1μF: 1V																																												
Cap>0.01μF: 0.2V	0.1μF≤Cap<1μF: 0.2V*																																												
	Cap≥1μF: 0.1V*																																												
*0201X104/6.3V~25V: 0.5V 0201X224/10V: 0.5V	*0201S104/6.3V~16V: 0.3V 0201S224/6.3V: 0.3V 0201X105/6.3V&10V: 0.3V																																												
0402	0603																																												
Cap<1μF: 1V	Cap<1μF: 1V																																												
Cap=1μF: 0.5V** 0402B224-16V: 0.5V 0402B474-10V: 0.5V 0402X475M6R3: 0.5V	1μF≤Cap≤4.7μF: 0.5V																																												
1μF<Cap<10μF: 0.2V **0402B105M6R3V: 0.2V	Cap>4.7μF: 0.2V																																												
Cap≥10μF: 0.1V																																													
0805	1206/1210																																												
Cap<10μF: 1V	Cap≤10μF: 1V																																												
Cap=10μF: 0.5V 0805B475/6.3V~25V: 0.5V	10μF<Cap≤100μF: 0.5V																																												
Cap>10μF: 0.2V	Cap>100μF: 0.2V																																												

\* "Room condition" Temperature: 15 to 35°C, Relative humidity: 25 to 75%, Atmospheric pressure: 86 to 106kPa.

Multilayer Ceramic Capacitors

No.	Item	Test Condition	Requirements															
7.	Adhesive Strength of Termination	* Pressurizing force : 2N (0201) and 5N ( $\leq$ 0603) and 10N ( $>$ 0603) * Test time: 10±1 sec.	* No remarkable damage or removal of the terminations.															
8.	Vibration Resistance	* Vibration frequency: 10-55 Hz/min. * Total amplitude: 1.5mm * Test time: 6 hrs. (Two hrs each in three mutually perpendicular directions.) * Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. * Cap./DF(Q) Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.	* No remarkable damage. * Cap change and Q/D.F.: To meet initial spec.															
9.	Solderability	* Solder temperature: 235±5°C * Dipping time: 2±0.5 sec.	95% min. coverage of all metallized area.															
10.	Bending Test	* The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1 mm per second until the deflection becomes 1 mm and then the pressure shall be maintained for 5±1 sec. * Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs.	* No remarkable damage. * Cap change : NP0: within ±5% or 0.5pF whichever is larger X7R, X5R, X6S, X7S: within ±12.5% Y5V: within ±30% (This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test.)															
11.	Resistance to Soldering Heat	* Solder temperature: 260±5°C * Dipping time: 10±1 sec * Preheating: 120 to 150°C for 1 minute before immerse the capacitor in a eutectic solder. * Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. * Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.	* No remarkable damage. * Cap change: NP0: within ±2.5% or 0.25pF whichever is larger X7R, X5R, X6S, X7S: within ±7.5% Y5V: within ±20% * Q/D.F., I.R. and dielectric strength: To meet initial requirements. * 25% max. leaching on each edge.															
12.	Temperature Cycle	* Conduct the five cycles according to the temperatures and time. <table border="1" style="margin-left: auto; margin-right: auto;"> <tr> <th>Step</th> <th>Temp. (°C)</th> <th>Time (min.)</th> </tr> <tr> <td>1</td> <td>Min. operating temp. +0/-3</td> <td>30±3</td> </tr> <tr> <td>2</td> <td>Room temp.</td> <td>2-3</td> </tr> <tr> <td>3</td> <td>Max. operating temp. +3/-0</td> <td>30±3</td> </tr> <tr> <td>4</td> <td>Room temp.</td> <td>2-3</td> </tr> </table> * Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. * Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.	Step	Temp. (°C)	Time (min.)	1	Min. operating temp. +0/-3	30±3	2	Room temp.	2-3	3	Max. operating temp. +3/-0	30±3	4	Room temp.	2-3	* No remarkable damage. * Cap change : NP0: within ±2.5% or 0.25pF whichever is larger X7R, X5R, X6S, X7S: within ±7.5% Y5V: within ±20% * Q/D.F., I.R. and dielectric strength: To meet initial requirements.
Step	Temp. (°C)	Time (min.)																
1	Min. operating temp. +0/-3	30±3																
2	Room temp.	2-3																
3	Max. operating temp. +3/-0	30±3																
4	Room temp.	2-3																

\* "Room condition" Temperature: 15 to 35°C, Relative humidity: 25 to 75%, Atmospheric pressure: 86 to 106kPa.

Multilayer Ceramic Capacitors

No.	Item	Test Condition	Requirements																																																			
13.	Humidity (Damp Heat) Steady State	<p>* Test temp.: <math>40 \pm 2^\circ\text{C}</math>            * Humidity: 90~95%RH            * Test time: 500+24+0hrs.            * Before initial measurement (Class II only): To apply de-aging at <math>150^\circ\text{C}</math> for 1hr then set for <math>24 \pm 2</math> hrs at room temp.            * Cap. / DF(Q) / I.R. Measurement to be made after de-aging at <math>150^\circ\text{C}</math> for 1hr then set for <math>24 \pm 2</math> hrs at room temp.</p>	<p>* No remarkable damage.            * Cap change:            NPO: within <math>\pm 5\%</math> or <math>0.5\mu\text{F}</math> whichever is larger            X7R, X5R, X6S, X7S: <math>\geq 10\text{V}^{**}</math>, within <math>\pm 12.5\%</math>; <math>\leq 6.3\text{V}</math> within <math>\pm 25\%</math>;            **10V: 0603 <math>\geq 4.7\mu\text{F}</math>; 0402 <math>\geq 1\mu\text{F}</math>; 0201 <math>\geq 0.1\mu\text{F}</math>, within <math>\pm 25\%</math>;            Y5V: <math>\geq 10\text{V}</math>, within <math>\pm 30\%</math>; <math>\leq 6.3\text{V}</math>, within <math>+30/-40\%</math>            * Q/D.F. value:            NPO: More than <math>30\text{pF}</math> <math>Q \geq 350</math>, <math>10\text{pF} \leq C &lt; 30\text{pF}</math>, <math>Q \geq 275 + 2.5\text{C}</math>            Less than <math>10\text{pF}</math> <math>Q \geq 200 + 10\text{C}</math>            X7R, X5R, X6S, X7S:</p> <table border="1"> <thead> <tr> <th>Rated vol.</th> <th>D.F. <math>\leq</math></th> <th>Exception of D.F. <math>\leq</math></th> </tr> </thead> <tbody> <tr> <td><math>\geq 100\text{V}</math></td> <td><math>\leq 3\%</math></td> <td><math>\leq 6\% 1206 \geq 0.47\mu\text{F}</math>  <math>\leq 7.5\% 0603 \geq 0.068\mu\text{F}; 0805 \geq 0.1\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 2.2\mu\text{F}</math>  <math>\leq 20\% 0805 \geq 0.22\mu\text{F}; 1210 \geq 3.3\mu\text{F}</math></td> </tr> <tr> <td>50V</td> <td><math>\leq 3\%</math></td> <td><math>\leq 6\% 0201(50\text{V}); 0603 \geq 0.047\mu\text{F}; 0805 \geq 0.18\mu\text{F}; 1206 \geq 0.47\mu\text{F}</math>  <math>\leq 10\% 0201 \geq 0.01\mu\text{F}; 1210 \geq 3.3\mu\text{F}</math>  <math>\leq 20\% 0402 \geq 0.012\mu\text{F}; 0603 &gt; 0.1\mu\text{F}; 0805 \geq 1\mu\text{F}(0805/X7R &gt; 0.47\mu\text{F}); 1206 \geq 2.2\mu\text{F}; 1210 \geq 10\mu\text{F}</math></td> </tr> <tr> <td>35V</td> <td><math>\leq 5\%</math></td> <td><math>\leq 20\% 0603 \geq 1\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 10\mu\text{F}</math>  <math>\leq 10\% 0201 = 0.01\mu\text{F}; 0805 \geq 1\mu\text{F}; 1210 \geq 10\mu\text{F}^*</math>  <math>\leq 14\% 0603 \geq 0.33\mu\text{F}</math>  <math>\leq 15\% 0201 &gt; 0.01\mu\text{F}; 0402 \geq 0.10\mu\text{F}(0402/X7R \geq 0.056\mu\text{F}); 0603 \geq 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}(1210/X5R \geq 10\mu\text{F})^*</math>  <math>\leq 20\% 0402 \geq 0.47\mu\text{F}</math></td> </tr> <tr> <td>25V</td> <td><math>\leq 5\%</math></td> <td><math>\leq 10\% 0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}</math>  <math>\leq 15\% 0201 \geq 0.01\mu\text{F}(0201/X7R \geq 0.022\mu\text{F}); 0402 \geq 0.033\mu\text{F}; 0603 &gt; 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}</math></td> </tr> <tr> <td>16V</td> <td><math>\leq 5\%</math></td> <td><math>\leq 15\% 0201 \geq 0.012\mu\text{F}; 0402 \geq 0.22\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}</math>  <math>\leq 20\% 0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}; 0603 \geq 10\mu\text{F}; 01R5/X5R</math></td> </tr> <tr> <td>10V</td> <td><math>\leq 7.5\%</math></td> <td><math>\leq 15\% 0201 \geq 0.012\mu\text{F}; 0402 \geq 0.22\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}</math>  <math>\leq 20\% 0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}; 0603 \geq 10\mu\text{F}; 01R5/X5R</math></td> </tr> <tr> <td>6.3V</td> <td><math>\leq 15\%</math></td> <td><math>\leq 30\% 0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}(0402/X6S \geq 0.47\mu\text{F}); 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}</math></td> </tr> <tr> <td>4V</td> <td><math>\leq 20\%</math></td> <td>---</td> </tr> </tbody> </table> <p>Y5V:</p> <table border="1"> <thead> <tr> <th>Rated vol.</th> <th>D.F. <math>\leq</math></th> <th>Exception of D.F. <math>\leq</math></th> </tr> </thead> <tbody> <tr> <td><math>\geq 50\text{V}</math></td> <td><math>\leq 7.5\%</math></td> <td><math>\leq 10\% 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}</math>  <math>\leq 20\% 1210 \geq 6.8\mu\text{F}</math></td> </tr> <tr> <td>35V</td> <td><math>\leq 10\%</math></td> <td>---</td> </tr> <tr> <td>25V</td> <td><math>\leq 7.5\%</math></td> <td><math>\leq 10\% 0402 \geq 0.047\mu\text{F}; 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.33\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 4.7\mu\text{F}</math>  <math>\leq 15\% 0402 \geq 0.068\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}</math></td> </tr> <tr> <td>16V (C<math>\geq 1.0\mu\text{F}</math>)</td> <td><math>\leq 10\%</math></td> <td><math>\leq 12.5\% 0402 \geq 0.068\mu\text{F}; 0603 \geq 0.68\mu\text{F}</math>  <math>\leq 20\% 0402 \geq 0.22\mu\text{F}</math></td> </tr> <tr> <td>16V (C <math>\geq 1.0\mu\text{F}</math>)</td> <td><math>\leq 12.5\%</math></td> <td><math>\leq 20\% 0603 \geq 2.2\mu\text{F}; 0805 \geq 3.3\mu\text{F}; 1206 \geq 10\mu\text{F}; 1210 \geq 22\mu\text{F}; 1812 \geq 47\mu\text{F}</math></td> </tr> <tr> <td>10V</td> <td><math>\leq 20\%</math></td> <td><math>\leq 30\% 0402 \geq 0.47\mu\text{F}</math></td> </tr> <tr> <td>6.3V</td> <td><math>\leq 30\%</math></td> <td>---</td> </tr> </tbody> </table>	Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$	$\geq 100\text{V}$	$\leq 3\%$	$\leq 6\% 1206 \geq 0.47\mu\text{F}$ $\leq 7.5\% 0603 \geq 0.068\mu\text{F}; 0805 \geq 0.1\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 2.2\mu\text{F}$ $\leq 20\% 0805 \geq 0.22\mu\text{F}; 1210 \geq 3.3\mu\text{F}$	50V	$\leq 3\%$	$\leq 6\% 0201(50\text{V}); 0603 \geq 0.047\mu\text{F}; 0805 \geq 0.18\mu\text{F}; 1206 \geq 0.47\mu\text{F}$ $\leq 10\% 0201 \geq 0.01\mu\text{F}; 1210 \geq 3.3\mu\text{F}$ $\leq 20\% 0402 \geq 0.012\mu\text{F}; 0603 > 0.1\mu\text{F}; 0805 \geq 1\mu\text{F}(0805/X7R > 0.47\mu\text{F}); 1206 \geq 2.2\mu\text{F}; 1210 \geq 10\mu\text{F}$	35V	$\leq 5\%$	$\leq 20\% 0603 \geq 1\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 10\mu\text{F}$ $\leq 10\% 0201 = 0.01\mu\text{F}; 0805 \geq 1\mu\text{F}; 1210 \geq 10\mu\text{F}^*$ $\leq 14\% 0603 \geq 0.33\mu\text{F}$ $\leq 15\% 0201 > 0.01\mu\text{F}; 0402 \geq 0.10\mu\text{F}(0402/X7R \geq 0.056\mu\text{F}); 0603 \geq 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}(1210/X5R \geq 10\mu\text{F})^*$ $\leq 20\% 0402 \geq 0.47\mu\text{F}$	25V	$\leq 5\%$	$\leq 10\% 0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}$ $\leq 15\% 0201 \geq 0.01\mu\text{F}(0201/X7R \geq 0.022\mu\text{F}); 0402 \geq 0.033\mu\text{F}; 0603 > 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$	16V	$\leq 5\%$	$\leq 15\% 0201 \geq 0.012\mu\text{F}; 0402 \geq 0.22\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$ $\leq 20\% 0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}; 0603 \geq 10\mu\text{F}; 01R5/X5R$	10V	$\leq 7.5\%$	$\leq 15\% 0201 \geq 0.012\mu\text{F}; 0402 \geq 0.22\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$ $\leq 20\% 0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}; 0603 \geq 10\mu\text{F}; 01R5/X5R$	6.3V	$\leq 15\%$	$\leq 30\% 0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}(0402/X6S \geq 0.47\mu\text{F}); 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}$	4V	$\leq 20\%$	---	Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$	$\geq 50\text{V}$	$\leq 7.5\%$	$\leq 10\% 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}$ $\leq 20\% 1210 \geq 6.8\mu\text{F}$	35V	$\leq 10\%$	---	25V	$\leq 7.5\%$	$\leq 10\% 0402 \geq 0.047\mu\text{F}; 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.33\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 4.7\mu\text{F}$ $\leq 15\% 0402 \geq 0.068\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$	16V (C $\geq 1.0\mu\text{F}$ )	$\leq 10\%$	$\leq 12.5\% 0402 \geq 0.068\mu\text{F}; 0603 \geq 0.68\mu\text{F}$ $\leq 20\% 0402 \geq 0.22\mu\text{F}$	16V (C $\geq 1.0\mu\text{F}$ )	$\leq 12.5\%$	$\leq 20\% 0603 \geq 2.2\mu\text{F}; 0805 \geq 3.3\mu\text{F}; 1206 \geq 10\mu\text{F}; 1210 \geq 22\mu\text{F}; 1812 \geq 47\mu\text{F}$	10V	$\leq 20\%$	$\leq 30\% 0402 \geq 0.47\mu\text{F}$	6.3V	$\leq 30\%$	---
Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$																																																				
$\geq 100\text{V}$	$\leq 3\%$	$\leq 6\% 1206 \geq 0.47\mu\text{F}$ $\leq 7.5\% 0603 \geq 0.068\mu\text{F}; 0805 \geq 0.1\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 2.2\mu\text{F}$ $\leq 20\% 0805 \geq 0.22\mu\text{F}; 1210 \geq 3.3\mu\text{F}$																																																				
50V	$\leq 3\%$	$\leq 6\% 0201(50\text{V}); 0603 \geq 0.047\mu\text{F}; 0805 \geq 0.18\mu\text{F}; 1206 \geq 0.47\mu\text{F}$ $\leq 10\% 0201 \geq 0.01\mu\text{F}; 1210 \geq 3.3\mu\text{F}$ $\leq 20\% 0402 \geq 0.012\mu\text{F}; 0603 > 0.1\mu\text{F}; 0805 \geq 1\mu\text{F}(0805/X7R > 0.47\mu\text{F}); 1206 \geq 2.2\mu\text{F}; 1210 \geq 10\mu\text{F}$																																																				
35V	$\leq 5\%$	$\leq 20\% 0603 \geq 1\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 10\mu\text{F}$ $\leq 10\% 0201 = 0.01\mu\text{F}; 0805 \geq 1\mu\text{F}; 1210 \geq 10\mu\text{F}^*$ $\leq 14\% 0603 \geq 0.33\mu\text{F}$ $\leq 15\% 0201 > 0.01\mu\text{F}; 0402 \geq 0.10\mu\text{F}(0402/X7R \geq 0.056\mu\text{F}); 0603 \geq 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}(1210/X5R \geq 10\mu\text{F})^*$ $\leq 20\% 0402 \geq 0.47\mu\text{F}$																																																				
25V	$\leq 5\%$	$\leq 10\% 0603 \geq 0.15\mu\text{F}; 0805 \geq 0.68\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 4.7\mu\text{F}$ $\leq 15\% 0201 \geq 0.01\mu\text{F}(0201/X7R \geq 0.022\mu\text{F}); 0402 \geq 0.033\mu\text{F}; 0603 > 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$																																																				
16V	$\leq 5\%$	$\leq 15\% 0201 \geq 0.012\mu\text{F}; 0402 \geq 0.22\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$ $\leq 20\% 0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}; 0603 \geq 10\mu\text{F}; 01R5/X5R$																																																				
10V	$\leq 7.5\%$	$\leq 15\% 0201 \geq 0.012\mu\text{F}; 0402 \geq 0.22\mu\text{F}; 0603 \geq 0.33\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 22\mu\text{F}$ $\leq 20\% 0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}; 0603 \geq 10\mu\text{F}; 01R5/X5R$																																																				
6.3V	$\leq 15\%$	$\leq 30\% 0201 \geq 0.1\mu\text{F}; 0402 \geq 1\mu\text{F}(0402/X6S \geq 0.47\mu\text{F}); 0603 \geq 10\mu\text{F}; 0805 \geq 4.7\mu\text{F}; 1206 \geq 47\mu\text{F}; 1210 \geq 100\mu\text{F}$																																																				
4V	$\leq 20\%$	---																																																				
Rated vol.	D.F. $\leq$	Exception of D.F. $\leq$																																																				
$\geq 50\text{V}$	$\leq 7.5\%$	$\leq 10\% 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}$ $\leq 20\% 1210 \geq 6.8\mu\text{F}$																																																				
35V	$\leq 10\%$	---																																																				
25V	$\leq 7.5\%$	$\leq 10\% 0402 \geq 0.047\mu\text{F}; 0603 \geq 0.1\mu\text{F}; 0805 \geq 0.33\mu\text{F}; 1206 \geq 1\mu\text{F}; 1210 \geq 4.7\mu\text{F}$ $\leq 15\% 0402 \geq 0.068\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 22\mu\text{F}$																																																				
16V (C $\geq 1.0\mu\text{F}$ )	$\leq 10\%$	$\leq 12.5\% 0402 \geq 0.068\mu\text{F}; 0603 \geq 0.68\mu\text{F}$ $\leq 20\% 0402 \geq 0.22\mu\text{F}$																																																				
16V (C $\geq 1.0\mu\text{F}$ )	$\leq 12.5\%$	$\leq 20\% 0603 \geq 2.2\mu\text{F}; 0805 \geq 3.3\mu\text{F}; 1206 \geq 10\mu\text{F}; 1210 \geq 22\mu\text{F}; 1812 \geq 47\mu\text{F}$																																																				
10V	$\leq 20\%$	$\leq 30\% 0402 \geq 0.47\mu\text{F}$																																																				
6.3V	$\leq 30\%$	---																																																				

\*I.R.:  $\geq 10\text{V}$ ,  $1\text{G}\Omega$  or  $50\text{ Q}\cdot\text{F}$  whichever is smaller.

Class II (X7R, X5R, X6S, X7S, Y5V)

Rated voltage	Insulation Resistance
100V: All X7R; 1210 $\geq 3.3\mu\text{F}$	
50V: 0402 $\geq 0.01\mu\text{F}$ ; 0603 $\geq 1\mu\text{F}$ ; 0805 $\geq 1\mu\text{F}$ ; 1206 $\geq 4.7\mu\text{F}$ ; 1210 $\geq 4.7\mu\text{F}$	
35V: 0603 $\geq 1\mu\text{F}$ ; 0805 $\geq 2.2\mu\text{F}$ ; 1206 $\geq 2.2\mu\text{F}$ ; 1210 $\geq 10\mu\text{F}$	
25V: 0201 $\geq 0.1\mu\text{F}$ ; 0402 $\geq 0.22\mu\text{F}$ ; 0603 $\geq 2.2\mu\text{F}$ ; 0805 $\geq 2.2\mu\text{F}$ ; 1206 $\geq 10\mu\text{F}$ ; 1210 $\geq 10\mu\text{F}$	1G $\Omega$ or $R_{\text{XC}} \geq 10\text{ Q}\cdot\text{F}$ whichever is smaller.
16V: 0201 $\geq 0.1\mu\text{F}$ ; 0402 $\geq 0.22\mu\text{F}$ ; 0603 $\geq 1\mu\text{F}$ ; 0805 $\geq 2.2\mu\text{F}$ ; 1206 $\geq 10\mu\text{F}$ ; 1210 $\geq 47\mu\text{F}$	
10V: 0201 $\geq 47\text{nF}$ ; 0402 $\geq 0.47\mu\text{F}$ ; 0603 $\geq 0.47\mu\text{F}$ ; 0805 $\geq 2.2\mu\text{F}$ ; 1206 $\geq 4.7\mu\text{F}$ ; 1210 $\geq 47\mu\text{F}$	
6.3V ; 4V ; All X6S/X7S items; Size $\geq 1812$	

\* "Room condition" Temperature: 15 to  $35^\circ\text{C}$ , Relative humidity: 25 to 75%, Atmospheric pressure: 86 to 106kPa.

Multilayer Ceramic Capacitors

No	Item	Test Condition	Requirements																																																																																	
14	Humidity (Damp Heat) Load	<p>*Test temp. : 40±2°C            *Humidity : 90~95%RH            *Test time : 500+24/-0 hrs.            *To apply voltage :               Rated voltage (MAX. 500V)            *Before initial measurement (Class II only): To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.            * Cap. / DF(Q) / I.R. Measurement to be made after de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.</p>	<p>* No remarkable damage.            Cap change:            NPO: ±7.5% or 0.75pF whichever is larger.            X7R, X5R, X6S, X7S: ≥10V**, within ±12.5%; ≤6.3V within ±25%;            **10V: 0603≥4.7μF; 0402≥1μF; 0201≥0.1μF, within ±25%;            Y5V: ≥10V, within ±30%; ≤6.3V, within +30/-40%            Q/D.F. value:            NP0: C≥30pF, Q≥200; C&lt;30pF, Q≥100+10/3C            X7R, X5R, X6S, X7S:</p> <table border="1"> <thead> <tr> <th>Rated vol.</th> <th>D.F. ≤</th> <th>Exception of D.F. ≤</th> </tr> </thead> <tbody> <tr> <td rowspan="3">≥ 100V</td> <td rowspan="3">≤ 3%</td> <td>≤ 6% 1206≥0.47μF</td> </tr> <tr> <td>≤ 7.5% 0603≥0.068μF; 0805≥0.1μF; 1206≥1μF; 1210≥2.2μF</td> </tr> <tr> <td>≤ 20% 0805≥0.22μF; 1210≥3.3μF</td> </tr> <tr> <td rowspan="3">50V</td> <td rowspan="3">≤ 3%</td> <td>≤ 6% 0201(50V); 0603≥0.047μF; 0805≥0.18μF; 1206≥0.47μF</td> </tr> <tr> <td>≤ 10% 0201≥0.01μF; 1210≥3.3μF</td> </tr> <tr> <td>≤ 20% 0402≥0.012μF; 0603&gt;0.1μF; 0805≥1μF(0805/X7R&gt;0.47μF); 1206≥2.2μF; 1210≥10μF;</td> </tr> <tr> <td rowspan="3">35V</td> <td rowspan="3">≤ 5%</td> <td>≤ 20% 0603≥1μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥10μF</td> </tr> <tr> <td>≤ 10% 0201≥0.01μF(0201/X5R=0.01μF); 0805≥1μF; 1210≥10μF*</td> </tr> <tr> <td>≤ 14% 0603≥0.33μF</td> </tr> <tr> <td rowspan="3">25V</td> <td rowspan="3">≤ 5%</td> <td>≤ 10% 0201≥0.1μF(0201/X5R&gt;0.01μF); 0603≥0.47μF; TTseries</td> </tr> <tr> <td>≤ 15% 0402≥0.10μF(0402/X7R≥0.056μF); 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF(1210/X5R≥10μF)*;</td> </tr> <tr> <td>≤ 20% 0402≥0.47μF</td> </tr> <tr> <td rowspan="3">16V</td> <td rowspan="3">≤ 5%</td> <td>≤ 10% 0603≥0.15μF; 0805≥0.68μF; 1206≥2.2μF; 1210≥4.7μF</td> </tr> <tr> <td>≤ 15% 0201≥0.01μF(0201/X7R≥0.022μF); 0402≥0.033μF; 0603&gt;0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF</td> </tr> <tr> <td>≤ 20% 0201≥0.1μF; 0402≥1μF; 0603/X5R≥10μF; 01R5/X5R</td> </tr> <tr> <td rowspan="2">10V</td> <td rowspan="2">≤ 7.5%</td> <td>≤ 15% 0201≥0.012μF; 0402≥0.22μF; 0603≥0.33μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥22μF</td> </tr> <tr> <td>≤ 20% 0201≥0.1μF; 0402≥1μF(0402/X6S≥0.47μF); 0603≥10μF; 0805≥4.7μF; 1206≥47μF; 1210≥100μF</td> </tr> <tr> <td>6.3V</td> <td>≤ 15%</td> <td>≤ 30% 0201≥0.1μF; 0402≥1μF(0402/X6S≥0.47μF); 0603≥10μF; 0805≥4.7μF; 1206≥47μF; 1210≥100μF</td> </tr> <tr> <td>4V</td> <td>≤ 20%</td> <td>---</td> </tr> <tr> <td colspan="4">Y5V:</td> </tr> <tr> <td rowspan="10">Rated vol.</td> <td rowspan="10">D.F. ≤</td> <td>Exception of D.F. ≤</td> </tr> <tr> <td>≤ 10% 0603≥0.1μF; 0805≥0.47μF; 1206≥4.7μF</td> </tr> <tr> <td>≤ 20% 1210≥6.8μF</td> </tr> <tr> <td rowspan="3">35V</td> <td rowspan="3">≤ 10%</td> <td>---</td> </tr> <tr> <td>≤ 10% 0402≥0.047μF; 0603≥0.1μF;</td> </tr> <tr> <td>0805≥0.33μF; 1206≥1μF; 1210≥4.7μF</td> </tr> <tr> <td rowspan="3">25V</td> <td rowspan="3">≤ 7.5%</td> <td>≤ 10% 0402≥0.068μF; 0603≥0.47μF;</td> </tr> <tr> <td>1206≥4.7μF; 1210≥22μF</td> </tr> <tr> <td>≤ 15% 0402≥0.068μF; 0603≥0.68μF</td> </tr> <tr> <td rowspan="2">16V (C&lt;1.0μF)</td> <td rowspan="2">≤ 10%</td> <td>≤ 12.5% 0402≥0.068μF; 0603≥0.68μF</td> </tr> <tr> <td>≤ 20% 0402≥0.22μF</td> </tr> <tr> <td rowspan="2">16V (C≥1.0μF)</td> <td rowspan="2">≤ 12.5%</td> <td>≤ 20% 0603≥2.2μF; 0805≥3.3μF; 1206≥10μF; 1210≥22μF; 1812≥47μF</td> </tr> <tr> <td>≤ 30% 0402≥0.47μF</td> </tr> <tr> <td>10V</td> <td>≤ 20%</td> <td>≤ 30% 0402≥0.47μF</td> </tr> <tr> <td>6.3V</td> <td>≤ 30%</td> <td>---</td> </tr> </tbody> </table> <p>*I.R.: ≥10V, 500MΩ or 25 Ω·F whichever is smaller.            Class II (X7R, X5R, X6S, X7S, Y5V)</p> <table border="1"> <thead> <tr> <th>Rated voltage</th> <th>Insulation Resistance</th> </tr> </thead> <tbody> <tr> <td>100V: All X7R; 1210≥3.3μF</td> <td rowspan="7">500MΩ or RxC≥5 Ω·F whichever is smaller.</td> </tr> <tr> <td>50V: 0402≥0.01μF; 0603≥1μF; 0805≥1μF; 1206≥4.7μF; 1210≥4.7μF</td> </tr> <tr> <td>35V: 0603≥1μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥10μF</td> </tr> <tr> <td>25V: 0201≥0.1μF; 0402≥0.22μF; 0603≥2.2μF; 0805≥2.2μF; 1206≥10μF; 1210≥10μF</td> </tr> <tr> <td>16V: 0201≥0.1μF; 0402≥0.22μF; 0603≥1μF; 0805≥2.2μF; 1206≥10μF; 1210≥47μF</td> </tr> <tr> <td>10V: 0201≥47nF; 0402≥0.47μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥47μF</td> </tr> <tr> <td>6.3V ; 4V ; All X6S/X7S items; Size≥1812</td> </tr> </tbody> </table>	Rated vol.	D.F. ≤	Exception of D.F. ≤	≥ 100V	≤ 3%	≤ 6% 1206≥0.47μF	≤ 7.5% 0603≥0.068μF; 0805≥0.1μF; 1206≥1μF; 1210≥2.2μF	≤ 20% 0805≥0.22μF; 1210≥3.3μF	50V	≤ 3%	≤ 6% 0201(50V); 0603≥0.047μF; 0805≥0.18μF; 1206≥0.47μF	≤ 10% 0201≥0.01μF; 1210≥3.3μF	≤ 20% 0402≥0.012μF; 0603>0.1μF; 0805≥1μF(0805/X7R>0.47μF); 1206≥2.2μF; 1210≥10μF;	35V	≤ 5%	≤ 20% 0603≥1μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥10μF	≤ 10% 0201≥0.01μF(0201/X5R=0.01μF); 0805≥1μF; 1210≥10μF*	≤ 14% 0603≥0.33μF	25V	≤ 5%	≤ 10% 0201≥0.1μF(0201/X5R>0.01μF); 0603≥0.47μF; TTseries	≤ 15% 0402≥0.10μF(0402/X7R≥0.056μF); 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF(1210/X5R≥10μF)*;	≤ 20% 0402≥0.47μF	16V	≤ 5%	≤ 10% 0603≥0.15μF; 0805≥0.68μF; 1206≥2.2μF; 1210≥4.7μF	≤ 15% 0201≥0.01μF(0201/X7R≥0.022μF); 0402≥0.033μF; 0603>0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF	≤ 20% 0201≥0.1μF; 0402≥1μF; 0603/X5R≥10μF; 01R5/X5R	10V	≤ 7.5%	≤ 15% 0201≥0.012μF; 0402≥0.22μF; 0603≥0.33μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥22μF	≤ 20% 0201≥0.1μF; 0402≥1μF(0402/X6S≥0.47μF); 0603≥10μF; 0805≥4.7μF; 1206≥47μF; 1210≥100μF	6.3V	≤ 15%	≤ 30% 0201≥0.1μF; 0402≥1μF(0402/X6S≥0.47μF); 0603≥10μF; 0805≥4.7μF; 1206≥47μF; 1210≥100μF	4V	≤ 20%	---	Y5V:				Rated vol.	D.F. ≤	Exception of D.F. ≤	≤ 10% 0603≥0.1μF; 0805≥0.47μF; 1206≥4.7μF	≤ 20% 1210≥6.8μF	35V	≤ 10%	---	≤ 10% 0402≥0.047μF; 0603≥0.1μF;	0805≥0.33μF; 1206≥1μF; 1210≥4.7μF	25V	≤ 7.5%	≤ 10% 0402≥0.068μF; 0603≥0.47μF;	1206≥4.7μF; 1210≥22μF	≤ 15% 0402≥0.068μF; 0603≥0.68μF	16V (C<1.0μF)	≤ 10%	≤ 12.5% 0402≥0.068μF; 0603≥0.68μF	≤ 20% 0402≥0.22μF	16V (C≥1.0μF)	≤ 12.5%	≤ 20% 0603≥2.2μF; 0805≥3.3μF; 1206≥10μF; 1210≥22μF; 1812≥47μF	≤ 30% 0402≥0.47μF	10V	≤ 20%	≤ 30% 0402≥0.47μF	6.3V	≤ 30%	---	Rated voltage	Insulation Resistance	100V: All X7R; 1210≥3.3μF	500MΩ or RxC≥5 Ω·F whichever is smaller.	50V: 0402≥0.01μF; 0603≥1μF; 0805≥1μF; 1206≥4.7μF; 1210≥4.7μF	35V: 0603≥1μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥10μF	25V: 0201≥0.1μF; 0402≥0.22μF; 0603≥2.2μF; 0805≥2.2μF; 1206≥10μF; 1210≥10μF	16V: 0201≥0.1μF; 0402≥0.22μF; 0603≥1μF; 0805≥2.2μF; 1206≥10μF; 1210≥47μF	10V: 0201≥47nF; 0402≥0.47μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥47μF	6.3V ; 4V ; All X6S/X7S items; Size≥1812
Rated vol.	D.F. ≤	Exception of D.F. ≤																																																																																		
≥ 100V	≤ 3%	≤ 6% 1206≥0.47μF																																																																																		
		≤ 7.5% 0603≥0.068μF; 0805≥0.1μF; 1206≥1μF; 1210≥2.2μF																																																																																		
		≤ 20% 0805≥0.22μF; 1210≥3.3μF																																																																																		
50V	≤ 3%	≤ 6% 0201(50V); 0603≥0.047μF; 0805≥0.18μF; 1206≥0.47μF																																																																																		
		≤ 10% 0201≥0.01μF; 1210≥3.3μF																																																																																		
		≤ 20% 0402≥0.012μF; 0603>0.1μF; 0805≥1μF(0805/X7R>0.47μF); 1206≥2.2μF; 1210≥10μF;																																																																																		
35V	≤ 5%	≤ 20% 0603≥1μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥10μF																																																																																		
		≤ 10% 0201≥0.01μF(0201/X5R=0.01μF); 0805≥1μF; 1210≥10μF*																																																																																		
		≤ 14% 0603≥0.33μF																																																																																		
25V	≤ 5%	≤ 10% 0201≥0.1μF(0201/X5R>0.01μF); 0603≥0.47μF; TTseries																																																																																		
		≤ 15% 0402≥0.10μF(0402/X7R≥0.056μF); 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF(1210/X5R≥10μF)*;																																																																																		
		≤ 20% 0402≥0.47μF																																																																																		
16V	≤ 5%	≤ 10% 0603≥0.15μF; 0805≥0.68μF; 1206≥2.2μF; 1210≥4.7μF																																																																																		
		≤ 15% 0201≥0.01μF(0201/X7R≥0.022μF); 0402≥0.033μF; 0603>0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥22μF																																																																																		
		≤ 20% 0201≥0.1μF; 0402≥1μF; 0603/X5R≥10μF; 01R5/X5R																																																																																		
10V	≤ 7.5%	≤ 15% 0201≥0.012μF; 0402≥0.22μF; 0603≥0.33μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥22μF																																																																																		
		≤ 20% 0201≥0.1μF; 0402≥1μF(0402/X6S≥0.47μF); 0603≥10μF; 0805≥4.7μF; 1206≥47μF; 1210≥100μF																																																																																		
6.3V	≤ 15%	≤ 30% 0201≥0.1μF; 0402≥1μF(0402/X6S≥0.47μF); 0603≥10μF; 0805≥4.7μF; 1206≥47μF; 1210≥100μF																																																																																		
4V	≤ 20%	---																																																																																		
Y5V:																																																																																				
Rated vol.	D.F. ≤	Exception of D.F. ≤																																																																																		
		≤ 10% 0603≥0.1μF; 0805≥0.47μF; 1206≥4.7μF																																																																																		
		≤ 20% 1210≥6.8μF																																																																																		
		35V	≤ 10%	---																																																																																
				≤ 10% 0402≥0.047μF; 0603≥0.1μF;																																																																																
				0805≥0.33μF; 1206≥1μF; 1210≥4.7μF																																																																																
		25V	≤ 7.5%	≤ 10% 0402≥0.068μF; 0603≥0.47μF;																																																																																
				1206≥4.7μF; 1210≥22μF																																																																																
				≤ 15% 0402≥0.068μF; 0603≥0.68μF																																																																																
		16V (C<1.0μF)	≤ 10%	≤ 12.5% 0402≥0.068μF; 0603≥0.68μF																																																																																
≤ 20% 0402≥0.22μF																																																																																				
16V (C≥1.0μF)	≤ 12.5%	≤ 20% 0603≥2.2μF; 0805≥3.3μF; 1206≥10μF; 1210≥22μF; 1812≥47μF																																																																																		
		≤ 30% 0402≥0.47μF																																																																																		
10V	≤ 20%	≤ 30% 0402≥0.47μF																																																																																		
6.3V	≤ 30%	---																																																																																		
Rated voltage	Insulation Resistance																																																																																			
100V: All X7R; 1210≥3.3μF	500MΩ or RxC≥5 Ω·F whichever is smaller.																																																																																			
50V: 0402≥0.01μF; 0603≥1μF; 0805≥1μF; 1206≥4.7μF; 1210≥4.7μF																																																																																				
35V: 0603≥1μF; 0805≥2.2μF; 1206≥2.2μF; 1210≥10μF																																																																																				
25V: 0201≥0.1μF; 0402≥0.22μF; 0603≥2.2μF; 0805≥2.2μF; 1206≥10μF; 1210≥10μF																																																																																				
16V: 0201≥0.1μF; 0402≥0.22μF; 0603≥1μF; 0805≥2.2μF; 1206≥10μF; 1210≥47μF																																																																																				
10V: 0201≥47nF; 0402≥0.47μF; 0603≥0.47μF; 0805≥2.2μF; 1206≥4.7μF; 1210≥47μF																																																																																				
6.3V ; 4V ; All X6S/X7S items; Size≥1812																																																																																				

\* "Room condition" Temperature: 15 to 35°C, Relative humidity: 25 to 75%, Atmospheric pressure: 86 to 106kPa.

## Multilayer Ceramic Capacitors



No	Item	Test Condition				Requirements																																																																																		
15.	High Temperature Load (Endurance)	* Test temp. : NPO, X7R/X7E/X7S: $125 \pm 3^\circ\text{C}$ X6S: $105 \pm 3^\circ\text{C}$ X5R, Y5V: $85 \pm 3^\circ\text{C}$ * Test time: $1000 + 24/-0$ hrs. To apply voltage: (1) 100% of rated voltage for below range.				* No remarkable damage. Cap change: NPO: $\pm 3.0\%$ or $\pm 0.3\mu\text{F}$ whichever is larger X7R, X5R, X6S, X7S: $\geq 10V^{**}$ , within $\pm 12.5\%$ ; $\leq 6.3V$ within $\pm 25\%$ ; ** $10V: 0603 \geq 4.7\mu\text{F}; 0402 \geq 1\mu\text{F}; 0201 \geq 0.1\mu\text{F}$ , within $\pm 25\%$ Y5V: $\geq 10V$ , within $\pm 30\%$ ; $\leq 6.3V$ , within $+30/-40\%$ Q/D.F. value: NPO: More than $30\text{pF}$ , $Q \geq 350$ $10\text{pF} \leq C < 30\text{pF}$ , $Q \geq 275 + 2.5C$ Less than $10\text{pF}$ , $Q \geq 200 + 10C$																																																																																		
		<table border="1"> <thead> <tr> <th>Size</th> <th>Dielectric</th> <th>Rated voltage</th> <th>Capacitance</th> </tr> </thead> <tbody> <tr> <td rowspan="2">0201</td> <td>X5R/X7R/ X6S/X7S</td> <td><math>\leq 10V</math></td> <td><math>C \geq 0.1\mu\text{F}</math></td> </tr> <tr> <td></td> <td><math>\geq 16V</math></td> <td><math>C &gt; 0.1\mu\text{F}</math></td> </tr> <tr> <td rowspan="4">0402</td> <td rowspan="2">X5R</td> <td><math>\leq 16V</math></td> <td><math>C &gt; 1.0\mu\text{F}</math></td> </tr> <tr> <td><math>25V, 50V</math></td> <td><math>C \geq 1.0\mu\text{F}</math></td> </tr> <tr> <td rowspan="2">X6S</td> <td><math>6.3V, 10V</math></td> <td><math>C &gt; 1.0\mu\text{F}</math></td> </tr> <tr> <td><math>16V, 25V</math></td> <td><math>C \geq 1.0\mu\text{F}</math></td> </tr> <tr> <td>X7R/X7S/Y5V</td> <td><math>6.3V, 10V</math></td> <td><math>C \geq 1.0\mu\text{F}</math></td> </tr> <tr> <td rowspan="5">0603</td> <td>X5R/X7R/ X6S/X7S</td> <td><math>4V</math></td> <td><math>C \geq 22\mu\text{F}</math></td> </tr> <tr> <td></td> <td><math>6.3V, 10V</math></td> <td><math>C \geq 4.7\mu\text{F}</math></td> </tr> <tr> <td>X5R/X6S/X7S</td> <td><math>25V</math></td> <td><math>C \geq 1.0\mu\text{F}</math></td> </tr> <tr> <td>X7R</td> <td><math>35V</math></td> <td><math>C \geq 1.0\mu\text{F}</math></td> </tr> <tr> <td>X5R/X7R/ X6S/X7S</td> <td><math>4V</math></td> <td><math>C \geq 47\mu\text{F}</math></td> </tr> <tr> <td rowspan="5">0805</td> <td rowspan="2">X6S</td> <td><math>6.3V</math></td> <td><math>C \geq 22\mu\text{F}</math></td> </tr> <tr> <td><math>10V, 50V</math></td> <td><math>C \geq 10\mu\text{F}</math></td> </tr> <tr> <td rowspan="2">X7R/X7S</td> <td><math>16V</math></td> <td><math>C &gt; 10\mu\text{F}</math></td> </tr> <tr> <td><math>16V, 25V</math></td> <td><math>C \geq 10\mu\text{F}</math></td> </tr> <tr> <td>X5R</td> <td><math>25V</math></td> <td><math>C \geq 22\mu\text{F}</math></td> </tr> <tr> <td>1206</td> <td>X5R/X7R/X6S</td> <td><math>\leq 6.3V</math></td> <td><math>C \geq 47\mu\text{F}</math></td> </tr> <tr> <td>1210</td> <td>X5R/X7R/X6S</td> <td><math>16V</math></td> <td><math>C \geq 47\mu\text{F}</math></td> </tr> <tr> <td></td> <td>X7R</td> <td><math>100V</math></td> <td><math>C \geq 3.3\mu\text{F}</math></td> </tr> <tr> <td>TT15</td> <td>X5R</td> <td><math>6.3V</math></td> <td><math>C &gt; 1.0\mu\text{F}</math></td> </tr> <tr> <td>TT21</td> <td>X5R/X7R/X6S</td> <td><math>\leq 10V</math></td> <td><math>C \geq 10\mu\text{F}</math></td> </tr> </tbody> </table>				Size	Dielectric	Rated voltage	Capacitance	0201	X5R/X7R/ X6S/X7S	$\leq 10V$	$C \geq 0.1\mu\text{F}$		$\geq 16V$	$C > 0.1\mu\text{F}$	0402	X5R	$\leq 16V$	$C > 1.0\mu\text{F}$	$25V, 50V$	$C \geq 1.0\mu\text{F}$	X6S	$6.3V, 10V$	$C > 1.0\mu\text{F}$	$16V, 25V$	$C \geq 1.0\mu\text{F}$	X7R/X7S/Y5V	$6.3V, 10V$	$C \geq 1.0\mu\text{F}$	0603	X5R/X7R/ X6S/X7S	$4V$	$C \geq 22\mu\text{F}$		$6.3V, 10V$	$C \geq 4.7\mu\text{F}$	X5R/X6S/X7S	$25V$	$C \geq 1.0\mu\text{F}$	X7R	$35V$	$C \geq 1.0\mu\text{F}$	X5R/X7R/ X6S/X7S	$4V$	$C \geq 47\mu\text{F}$	0805	X6S	$6.3V$	$C \geq 22\mu\text{F}$	$10V, 50V$	$C \geq 10\mu\text{F}$	X7R/X7S	$16V$	$C > 10\mu\text{F}$	$16V, 25V$	$C \geq 10\mu\text{F}$	X5R	$25V$	$C \geq 22\mu\text{F}$	1206	X5R/X7R/X6S	$\leq 6.3V$	$C \geq 47\mu\text{F}$	1210	X5R/X7R/X6S	$16V$	$C \geq 47\mu\text{F}$		X7R	$100V$	$C \geq 3.3\mu\text{F}$	TT15	X5R	$6.3V$	$C > 1.0\mu\text{F}$	TT21	X5R/X7R/X6S	$\leq 10V$	$C \geq 10\mu\text{F}$								
Size	Dielectric	Rated voltage	Capacitance																																																																																					
0201	X5R/X7R/ X6S/X7S	$\leq 10V$	$C \geq 0.1\mu\text{F}$																																																																																					
		$\geq 16V$	$C > 0.1\mu\text{F}$																																																																																					
0402	X5R	$\leq 16V$	$C > 1.0\mu\text{F}$																																																																																					
		$25V, 50V$	$C \geq 1.0\mu\text{F}$																																																																																					
	X6S	$6.3V, 10V$	$C > 1.0\mu\text{F}$																																																																																					
		$16V, 25V$	$C \geq 1.0\mu\text{F}$																																																																																					
X7R/X7S/Y5V	$6.3V, 10V$	$C \geq 1.0\mu\text{F}$																																																																																						
0603	X5R/X7R/ X6S/X7S	$4V$	$C \geq 22\mu\text{F}$																																																																																					
		$6.3V, 10V$	$C \geq 4.7\mu\text{F}$																																																																																					
	X5R/X6S/X7S	$25V$	$C \geq 1.0\mu\text{F}$																																																																																					
	X7R	$35V$	$C \geq 1.0\mu\text{F}$																																																																																					
	X5R/X7R/ X6S/X7S	$4V$	$C \geq 47\mu\text{F}$																																																																																					
0805	X6S	$6.3V$	$C \geq 22\mu\text{F}$																																																																																					
		$10V, 50V$	$C \geq 10\mu\text{F}$																																																																																					
	X7R/X7S	$16V$	$C > 10\mu\text{F}$																																																																																					
		$16V, 25V$	$C \geq 10\mu\text{F}$																																																																																					
	X5R	$25V$	$C \geq 22\mu\text{F}$																																																																																					
1206	X5R/X7R/X6S	$\leq 6.3V$	$C \geq 47\mu\text{F}$																																																																																					
1210	X5R/X7R/X6S	$16V$	$C \geq 47\mu\text{F}$																																																																																					
	X7R	$100V$	$C \geq 3.3\mu\text{F}$																																																																																					
TT15	X5R	$6.3V$	$C > 1.0\mu\text{F}$																																																																																					
TT21	X5R/X7R/X6S	$\leq 10V$	$C \geq 10\mu\text{F}$																																																																																					
		** 1WV items must follow de-rating conditions. (2) 150% of rated voltage for below range.				<table border="1"> <thead> <tr> <th>Size</th> <th>Dielectric</th> <th>Rated voltage</th> <th>Capacitance</th> </tr> </thead> <tbody> <tr> <td rowspan="2">0201</td> <td>X5R/X6S</td> <td><math>16V, 25V</math></td> <td><math>C = 0.1\mu\text{F}</math></td> </tr> <tr> <td>X7R</td> <td><math>16V</math></td> <td><math>C \geq 0.22\mu\text{F}</math></td> </tr> <tr> <td rowspan="3">0402</td> <td>X7R/X5R/ X6S</td> <td><math>50V</math></td> <td><math>C &gt; 0.01\mu\text{F}</math></td> </tr> <tr> <td>X6S</td> <td><math>10-25V</math></td> <td><math>C \geq 0.22\mu\text{F}</math></td> </tr> <tr> <td>Y5V</td> <td><math>16V</math></td> <td><math>C \geq 0.47\mu\text{F}</math></td> </tr> <tr> <td>X7S</td> <td><math>50V \sim 100V</math></td> <td><math>C &gt; 0.22\mu\text{F}</math></td> </tr> <tr> <td rowspan="5">0603</td> <td>X7R</td> <td><math>50V</math></td> <td><math>C &gt; 0.1\mu\text{F}</math></td> </tr> <tr> <td></td> <td><math>25V</math></td> <td><math>C = 1.0\mu\text{F}</math></td> </tr> <tr> <td>X5R</td> <td><math>50V</math></td> <td><math>C \geq 1.0\mu\text{F}</math></td> </tr> <tr> <td>X5R/X7R/ X6S/X7S</td> <td><math>10V, 16V</math></td> <td><math>C \geq 1.0\mu\text{F}</math></td> </tr> <tr> <td>Y5V</td> <td><math>16V</math></td> <td><math>C \geq 2.2\mu\text{F}</math></td> </tr> <tr> <td rowspan="5">0805</td> <td rowspan="5">X5R/X7R/ X6S/X7S</td> <td><math>100V</math></td> <td><math>C \geq 0.47\mu\text{F}</math></td> </tr> <tr> <td><math>50V</math></td> <td><math>C \geq 0.68\mu\text{F}</math></td> </tr> <tr> <td><math>35V</math></td> <td><math>C \geq 2.2\mu\text{F}</math></td> </tr> <tr> <td><math>10-25V</math></td> <td><math>C \geq 4.7\mu\text{F}</math></td> </tr> <tr> <td>Y5V</td> <td><math>16V</math></td> <td><math>C \geq 4.7\mu\text{F}</math></td> </tr> <tr> <td rowspan="3">1206</td> <td>X7R</td> <td><math>100V</math></td> <td><math>C \geq 1.0\mu\text{F}</math></td> </tr> <tr> <td></td> <td><math>50V</math></td> <td><math>C \geq 2.2\mu\text{F}</math></td> </tr> <tr> <td>X5R/X6S/ X7S</td> <td><math>100V</math></td> <td><math>C &gt; 1.0\mu\text{F}</math></td> </tr> <tr> <td rowspan="2">1210</td> <td>X5R/X7R/ X6S/X7S</td> <td><math>50V \sim 100V</math></td> <td><math>C \geq 2.2\mu\text{F}</math></td> </tr> <tr> <td>1825</td> <td>X7R</td> <td><math>100V \sim 250V</math></td> <td><math>C \geq 1.0\mu\text{F}</math></td> </tr> <tr> <td>2220</td> <td></td> <td></td> <td></td> </tr> <tr> <td>2225</td> <td></td> <td></td> <td></td> </tr> </tbody> </table>				Size	Dielectric	Rated voltage	Capacitance	0201	X5R/X6S	$16V, 25V$	$C = 0.1\mu\text{F}$	X7R	$16V$	$C \geq 0.22\mu\text{F}$	0402	X7R/X5R/ X6S	$50V$	$C > 0.01\mu\text{F}$	X6S	$10-25V$	$C \geq 0.22\mu\text{F}$	Y5V	$16V$	$C \geq 0.47\mu\text{F}$	X7S	$50V \sim 100V$	$C > 0.22\mu\text{F}$	0603	X7R	$50V$	$C > 0.1\mu\text{F}$		$25V$	$C = 1.0\mu\text{F}$	X5R	$50V$	$C \geq 1.0\mu\text{F}$	X5R/X7R/ X6S/X7S	$10V, 16V$	$C \geq 1.0\mu\text{F}$	Y5V	$16V$	$C \geq 2.2\mu\text{F}$	0805	X5R/X7R/ X6S/X7S	$100V$	$C \geq 0.47\mu\text{F}$	$50V$	$C \geq 0.68\mu\text{F}$	$35V$	$C \geq 2.2\mu\text{F}$	$10-25V$	$C \geq 4.7\mu\text{F}$	Y5V	$16V$	$C \geq 4.7\mu\text{F}$	1206	X7R	$100V$	$C \geq 1.0\mu\text{F}$		$50V$	$C \geq 2.2\mu\text{F}$	X5R/X6S/ X7S	$100V$	$C > 1.0\mu\text{F}$	1210	X5R/X7R/ X6S/X7S	$50V \sim 100V$	$C \geq 2.2\mu\text{F}$	1825	X7R	$100V \sim 250V$	$C \geq 1.0\mu\text{F}$	2220				2225			
Size	Dielectric	Rated voltage	Capacitance																																																																																					
0201	X5R/X6S	$16V, 25V$	$C = 0.1\mu\text{F}$																																																																																					
	X7R	$16V$	$C \geq 0.22\mu\text{F}$																																																																																					
0402	X7R/X5R/ X6S	$50V$	$C > 0.01\mu\text{F}$																																																																																					
	X6S	$10-25V$	$C \geq 0.22\mu\text{F}$																																																																																					
	Y5V	$16V$	$C \geq 0.47\mu\text{F}$																																																																																					
X7S	$50V \sim 100V$	$C > 0.22\mu\text{F}$																																																																																						
0603	X7R	$50V$	$C > 0.1\mu\text{F}$																																																																																					
		$25V$	$C = 1.0\mu\text{F}$																																																																																					
	X5R	$50V$	$C \geq 1.0\mu\text{F}$																																																																																					
	X5R/X7R/ X6S/X7S	$10V, 16V$	$C \geq 1.0\mu\text{F}$																																																																																					
	Y5V	$16V$	$C \geq 2.2\mu\text{F}$																																																																																					
0805	X5R/X7R/ X6S/X7S	$100V$	$C \geq 0.47\mu\text{F}$																																																																																					
		$50V$	$C \geq 0.68\mu\text{F}$																																																																																					
		$35V$	$C \geq 2.2\mu\text{F}$																																																																																					
		$10-25V$	$C \geq 4.7\mu\text{F}$																																																																																					
		Y5V	$16V$	$C \geq 4.7\mu\text{F}$																																																																																				
1206	X7R	$100V$	$C \geq 1.0\mu\text{F}$																																																																																					
		$50V$	$C \geq 2.2\mu\text{F}$																																																																																					
	X5R/X6S/ X7S	$100V$	$C > 1.0\mu\text{F}$																																																																																					
1210	X5R/X7R/ X6S/X7S	$50V \sim 100V$	$C \geq 2.2\mu\text{F}$																																																																																					
	1825	X7R	$100V \sim 250V$	$C \geq 1.0\mu\text{F}$																																																																																				
2220																																																																																								
2225																																																																																								
		(3) $\leq 6.3V$ or $C \geq 10\mu\text{F}$ : 150% of rated voltage. (4) $10V \leq U_r < 250V$ : 200% of rated voltage. (5) $500V$ : 150% of rated voltage. (6) $U_r \geq 630V$ : 120% of rated voltage * Before initial measurement (Class II only): To apply de-aging at $150^\circ\text{C}$ for 1 hr then set for $24 \pm 2$ hrs at room temp. * Cap. / DF(Q) / I.R. Measurement to be made after de-aging at $150^\circ\text{C}$ for 1 hr then set for $24 \pm 2$ hrs at room temp. ** De-rating conditions:				* I.R.: $\geq 10V$ , $1\text{G}\Omega$ or $50\text{ }\Omega\text{-F}$ whichever is smaller. Class II (X7R, X5R, X6S, X7S, Y5V)																																																																																		
						Rated voltage 100V: All X7R; $1210 \geq 3.3\mu\text{F}$ 50V: $0402 \geq 0.01\mu\text{F}; 0603 \geq 1\mu\text{F}; 0805 \geq 1\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 4.7\mu\text{F}$ 35V: $0603 \geq 1\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 2.2\mu\text{F}; 1210 \geq 10\mu\text{F}$ 25V: $0201 \geq 0.1\mu\text{F}; 0402 \geq 0.22\mu\text{F}; 0603 \geq 2.2\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 10\mu\text{F}; 1210 \geq 47\mu\text{F}$ 16V: $0201 \geq 0.1\mu\text{F}; 0402 \geq 0.22\mu\text{F}; 0603 \geq 1\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 10\mu\text{F}; 1210 \geq 47\mu\text{F}$ 10V: $0201 \geq 47n\text{F}; 0402 \geq 0.47\mu\text{F}; 0603 \geq 0.47\mu\text{F}; 0805 \geq 2.2\mu\text{F}; 1206 \geq 4.7\mu\text{F}; 1210 \geq 47\mu\text{F}$ 6.3V: $4V$ ; All X6S/X7S items; Size $\geq 1812$				Insulation Resistance 1GΩ or $R_{xC} \geq 10\text{ }\Omega\text{-F}$ whichever is smaller.																																																																														

\* "Room condition" Temperature: 15 to 35°C, Relative humidity: 25 to 75%, Atmospheric pressure: 86 to 106kPa.


## Multilayer Ceramic Capacitors

### APPENDIXES

#### □ Tape & reel dimensions




Size	0201	0402	0603	0805				1206				1210				1808			1812		
Thickness	L	N,E	S,H,X	A,H	B,T	D,I	B,T	C,J,D	G,P	T	C,D	G,K	M	D,F	G,K	D,F	G,K	M,U			
<b>A<sub>0</sub></b>	0.40 +/-0.10	0.70 +/-0.20	1.05 +/-0.30	1.50 +/-0.20	1.50 +/-0.20	<1.80	1.90 +/-0.50	<2.00	<2.30	<3.05	<3.05	<3.05	<3.20	<2.50	<2.50	<3.90	<3.90	<3.90			
<b>B<sub>0</sub></b>	0.70 +/-0.10	1.20 +/-0.20	1.80 +/-0.30	2.30 +/-0.20	2.30 +/-0.20	<2.70	3.50 +/-0.50	<3.70	<4.00	<3.80	<3.80	<3.80	<4.00	<5.30	<5.30	<5.30	<5.30				
<b>T</b>	≤0.55	≤0.80	≤1.20	≤1.15	≤1.20	0.23 +/-0.1	≤1.20	0.23 +/-0.1	0.23 +/-0.1	0.23 +/-0.1	0.23 +/-0.1	0.23 +/-0.1	0.25 +/-0.1	0.25 +/-0.1	0.25 +/-0.1	0.25 +/-0.1	0.25 +/-0.1				
<b>K<sub>0</sub></b>	-	-	-	-	-	<2.00	-	<2.00	<2.50	<1.50	<2.00	<2.50	<3.20	<2.00	<2.50	<2.00	<2.50	<3.50			
<b>W</b>	8.00 +/-0.30	12.00 +/-0.30	12.00 +/-0.30	12.00 +/-0.30	12.00 +/-0.30	12.00 +/-0.30															
<b>P<sub>0</sub></b>	4.00 +/-0.10																				
<b>10xP<sub>0</sub></b>	40.00 +/-0.10	40.00 +/-0.10	40.00 +/-0.20																		
<b>P<sub>1</sub></b>	2.00 +/-0.05	2.00 +/-0.05	4.00 +/-0.10																		
<b>P<sub>2</sub></b>	2.00 +/-0.05	2.00 +/-0.10	2.00 +/-0.10	2.00 +/-0.10	2.00 +/-0.10	2.00 +/-0.10															
<b>D<sub>0</sub></b>	1.50 +0.1/-0																				
<b>D<sub>1</sub></b>	-	-	-	-	-	1.00 +/-0.10	-	1.00 +/-0.10	1.00 +/-0.10	1.00 +/-0.10	1.00 +/-0.10	1.00 +/-0.10	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0	1.50 +0.1/-0				
<b>E</b>	1.75 +/-0.10																				
<b>F</b>	3.50 +/-0.05	5.50 +/-0.10	5.50 +/-0.10	5.50 +/-0.10	5.50 +/-0.10	5.50 +/-0.10															



Size	0201, 0402, 0603, 0805, 1206, 1210			1812
Reel size	7"	10"	13"	7"
<b>C</b>	13.0±0.5	13.0±0.5	13.0±0.5	13.0±0.5
<b>W<sub>1</sub></b>	10.0±1.5	10.0±1.5	10.0±1.5	12.4±2.0/-0
<b>A</b>	178.0±2.0	250.0±2.0	330.0±2.0	178.0±2.0
<b>N</b>	60.0±1.0/-0	50 min	50 min	60.0±1.0/-0

## Multilayer Ceramic Capacitors

### Example of customer label



- a. Customer name
- b. WTC order series and item number
- c. Customer P/O
- d. Customer P/N
- e. Description of product
- f. Quantity
- g. Bar code including quantity & WTC P/N or customer
- h. WTC P/N
- i. Shipping date
- j. Order bar code including series and item numbers
- k. Serial number of label

\*Customized label is available upon request

### Constructions

No.	Name	NPO	X7R, X5R, X6S, X7S, Y5V
①	Ceramic material	CaZrO <sub>3</sub> based	BaTiO <sub>3</sub> based
②	Inner electrode		Ni
③	Termination	Inner layer	Cu
④		Middle layer	Ni
⑤		Outer layer	Sn




Fig. 5 The construction of MLCC

### Storage and handling conditions

- (1) To store products at 5 to 40°C ambient temperature and 20 to 70% related humidity conditions; MSL Level 1.
- (2) The product is recommended to be used within one year after shipment. Check solderability in case of shelf life extension is needed.

#### Cautions:

- a. The corrosive gas reacts on the terminal electrodes of capacitors, and results in the poor solderability. Do not store the capacitors in the ambience of corrosive gas (e.g., hydrogen sulfide, sulfur dioxide, chlorine, ammonia gas etc.)
- b. In corrosive atmosphere, solderability might be degraded, and silver migration might occur to cause low reliability.
- c. Due to the dewing by rapid humidity change, or the photochemical change of the terminal electrode by direct sunlight, the solderability and electrical performance may deteriorate. Do not store capacitors under direct sunlight or dewing condition. To store products on the shelf and avoid exposure to moisture.

## Multilayer Ceramic Capacitors

### ■ Recommended soldering conditions

The lead-free termination MLCCs are not only to be used on SMT against lead-free solder paste, but also suitable against lead-containing solder paste. If the optimized solder joint is requested, increasing soldering time, temperature and concentration of N<sub>2</sub> within oven are recommended.




Fig. 6 Recommended reflow soldering profile for SMT process with SnAgCu series solder paste.




Fig. 7 Recommended wave soldering profile for SMT process with SnAgCu series solder.

