



Features

- Under Stencil Rolls for FUJI Printers
- Prevents smearing, bridging, solder balls, and other problems associated with the stencil printing of solder paste
- Manufactured from a blend of polyester and cellulose fibers
- More paper per roll resulting in less down time, less changeover time, and less inventory required
- Exceptionally low lint levels
- Solvent resistant material results in increased absorption per square inch

FUJI Paper Specifications

| Test | Orientation | Units | Value | Method |
|-----------------------|-------------------|--|--------------------------------------|------------|
| Composition | | | 54% Wood Pulp 46% Polyester White | |
| Basis Weight | | oz/yd ₂ g/m ₂ | 1.5 50.8 | ASTM D3776 |
| Thickness | | mils mm | 12 .30 | ASTM D1777 |
| Grab Tensile Strength | Machine Direction | lb N | 28 125 | ASTM D5034 |
| | Cross Direction | lb N | 16 71 | |

Dimensional Tolerances:

- Core Length: ± 1/16"
- Paper Width: ± 1/8"
- Core ID: + 1/8"
- Paper Length: ± 5%

FUJI Stencil Roll Part Number

| Part Number | Core Type | Core Length | Paper Width | Core ID | Paper Length |
|-------------|-----------|-------------|-------------|---------|--------------|
| EB41F1919 | Paper | 19.50" | 19.50" | 1.0" | 33' |

EasyBraid expressly warrants that for a period of one (1) year from the date of purchase, EasyBraid products will be free of defects in material (parts) and workmanship (labor). Within the warranty period, a unit/product will be tested, repaired or replaced at EasyBraid's option, free of charge.

Specifications and procedures subject to change without notice.

FUJI STENCIL ROLLS

11520 K-TEL DRIVE, MINNETONKA, MN 55343
 PHONE: (909) 627-2453
 WEBSITE: EASYBRAIDCO.COM

DRAWING NUMBER
FUJI

DATE:
March 2019

