



CORE DIMENSIONS					
UNCOATED CORE					36T0153-000
	MM	INCHES		MM	INCHES
OD	3.94	(.155)	±	.13	(.005)
ID	1.78	(.070)	±	.13	(.005)
TH	1.27	(.050)	±	.13	(.005)
SINGLE PARYLENE COATING					36T0153-00P
OD	3.96	(.156)	±	.13	(.005)
ID	1.75	(.069)	±	.13	(.005)
TH	1.30	(.051)	±	.13	(.005)

WEIGHT / K 0.1322 LBS
 INITIAL PERMEABILITY 4500

ELECTRICAL SPECIFICATION								
	MIN (μ H)	MIN TOL.	NOM (μ H)	MAX (μ H)	MAX TOL.	FREQ. (kHz)	VOLT. (V)	URNS
L	.681	(-25.0 %)	.909			100	$\leq .00029$	1
Q	30	-	-	-	-	100	$\leq .00029$	1

COATING SPECIFICATIONS			
TYPE	Max. Coating (mm/mils.)	Min. DLB VAC	TEST FORCE (LB)
PARYLENE	0.0254/1.0	1500	.15

NOTES: DC BIAS REQUIREMENT: 100 kHz 38 AWG

H (Oe)	0.25	0.35	0.45
--------	------	------	------

Turns:	10	10	10
Voltage (mV):	58	58	58
DC Bias (mA):	16.1	22.6	29.0
Min. Inductance (μ H): (0° to 70°)	56.9	50.7	39.3

Turns:	26	26	26
Voltage (mV):	150	150	150
DC Bias (mA):	6.2	8.7	11.2
Min. Inductance (μ H): (0° to 70°)	385	343	266



Rev	Description	Date	INT
A	Original Draft	1997-7-2	BAC
B	Updated Elect. Specs/ Chg Perm/ Add DC Bias	1998-6-10	TPM
C	Revised All Catalog 36 Cores L w/ DC Bias Per Rev 2	2002-2-25	TPM
D	Changed P/N To -00P Removed Q Coating Per TFC50 Parts List	2005-10-3	TMB
E	Revised Template	2006-6-2	WMM
F	Removed L @ -40° to 85°.	2007-3-19	Dxu
G	Changed the Min. DLB to 1500VAC	2008-11-24	Jcai

Date: 2008-11-24	DWG # 36T0153-00P-G	Rev:
Drawn By: Jcai	Title # 36T0153-00P	G

Steward This document contains information which is proprietary to Steward. No production or publication of this document in whole or in part shall be made without written authorization from Steward.

UNCONTROLLED DOCUMENT