

V4

#### **Features**

- ♦ Low Series Resistance
- ♦ Ultra Low Capacitance
- Millimeter Wave Switching & Cutoff Frequency
- 2 Nanosecond Switching Speed
- Can be Driven by a Buffered TTL
- Silicon Nitride Passivation
- Polvimide Scratch Protection
- ♦ RoHS Compliant

#### **Description**

M/A-COM Technology Solutions MA4AGP907 and MA4AGFCP910 are Aluminum Gallium Arsenide (AlGaAs) flip-chip PIN diodes. These devices are fabricated on OMCVD epitaxial wafers using a process optimized for high device uniformity and exceptionally low parasitics. The end result is a diode with an extremely low RC product, (0.1ps) and 2-3nS switching characteristics. They are fully passivated with silicon nitride and have an added polymer layer for scratch protection. The protective coating prevents damage to the junction and the anode air-bridge during handling and assembly.


# **Applications**

The ultra low capacitance of the MA4AGP907 and MA4AGFCP910 make them ideal for RF switch and phase shifter applications through millimeter wave frequencies. The diodes are designed for use in pulsed or CW applications, where single digit nS switching speed is required. The low capacitance of these diodes make them ideal for use in microwave multi-throw switch assemblies, where the series capacitance of each "off" port adversely loads the input and affects VSWR.

# Absolute Maximum Ratings T<sub>AMB</sub> = +25°C (unless otherwise specified)

Parameter	Absolute Maximum			
Reverse Voltage	MA4AGP907 -50V MA4AGFCP910 -75V			
Operating Temperature	-55°C to +125°C			
Storage Temperature	-55°C to +150°C			
Junction Temperature	+175°C			
Dissipated Power (RF & DC)	50mW			
C.W. Incident Power	+23 dBm			
Mounting Temperature	+280°C for 10 seconds			

# Chip Dimensions MA4AGP907 and MA4AGFCP910



#### Notes:

- 1. Gold Pads 14µM thick.
- 2. Yellow areas indicate ohmic gold mounting pads.
- 3. Dimensions A thru F are identical for both devices

	INCHES		M	M
DIM	MIN.	MAX.	MIN.	MAX.
Α	0.0260	0.0270	0.6604	0.6858
В	0.0135	0.0145	0.3429	0.3683
С	0.0065	0.0075	0.1651	0.1905
D	0.0043	0.0053	0.1092	0.1346
E	0.0068	0.0073	0.1727	0.1854
F	0.0182	0.0192	0.4623	0.4877

- ADVANCED: Data Sheets contain information regarding a product M/A-COM is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not quaranteed.
- measurements. Commitment to develop is not guaranteed.

  PRELIMINARY: Data Sheets contain information regarding a product M/A-COM has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples and/or test data may be available. Commitment to produce in volume is not guaranteed.
- North America Tel: 800.366.2266 / Fax: 978.366.2266
- Europe Tel: 44.1908.574.200 / Fax: 44.1908.574.300
- Asia/Pacific Tel: 81.44.844.8296 / Fax: 81.44.844.8298
   Visit www.macom.com for additional data sheets and product information.

M/A-COM Inc. and its affiliates reserve the right to make changes to the product(s) or information contained herein without notice.



V4

# Electrical Specifications @ T<sub>AMB</sub> = +25°C

Parameter	Symbol	Conditions	Units-	MA4AGP907		MA4AGFCP910	
		Conditions		Тур.	Max.	Тур.	Max.
Total Capacitance	Ст	MA4AGP907 -5V,1MHz	pF	0.025	0.030	0.018	0.021
		MA4AGFCP910 -10V,1MHz					
Total Capacitance <sup>1</sup>	C <sub>T</sub>	-5V, 10GHz	pF	0.020		0.018	0.021
Series Resistance	Rs	+10mA, 1MHz	Ω	5.2	7.0		
Series Resistance <sup>2</sup>	Rs	+10mA, 10GHz	Ω	4.2		5.2	6.0
Forward Voltage	V <sub>F</sub>	+10mA	V	1.33	1.45	1.33	1.45
Reverse Leakage Current <sup>3</sup>	I <sub>R</sub>	MA4AGP907 V <sub>R</sub> = -50V	μA		10		10
Theverse Leakage Current		MA4AGFCP910 V <sub>R</sub> = -75V	μΛ				
Switching Speed <sup>4</sup>	T <sub>RISE</sub> T <sub>FALL</sub>	10GHz	nS	2		2	
Carrier Lifetime	TL	$I_F = 10$ mA / $I_{REV} = 6$ mA	nS			4	

#### Notes:

- 1) Capacitance is determined by measuring the isolation of a single series diode in a  $50\Omega$  transmission line at 10GHz.
- 2) Series resistance is determined by measuring the insertion loss of a single series diode in a  $50\Omega$  transmission line at 10GHz.
- 3) The max rated  $V_R$ ( Reverse Voltage ) is sourced and the resultant reverse leakage current, Ir, is measured to be <10 $\mu A$
- 4) Switching speed is measured between 10% and 90% or 90% to 10% RF voltage for a single series mounted diode. Driver delay is not included.

<sup>•</sup> North America Tel: 800.366.2266 / Fax: 978.366.2266


<sup>•</sup> **Europe** Tel: 44.1908.574.200 / Fax: 44.1908.574.300


Asia/Pacific Tel: 81.44.844.8296 / Fax: 81.44.844.8298
 Visit www.macom.com for additional data sheets and product information.



**V**4

# Typical RF Performance @ T<sub>AMB</sub> = +25°C





**ADVANCED:** Data Sheets contain information regarding a product M/A-COM is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed.


PRELIMINARY: Data Sheets contain information regarding a product M/A-COM has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples and/or test data may be available. Commitment to produce in volume is not guaranteed.


- North America Tel: 800.366.2266 / Fax: 978.366.2266
- Europe Tel: 44.1908.574.200 / Fax: 44.1908.574.300
- Asia/Pacific Tel: 81.44.844.8296 / Fax: 81.44.844.8298
   Visit www.macom.com for additional data sheets and product information.

M/A-COM Inc. and its affiliates reserve the right to make changes to the product(s) or information contained herein without notice.



# Typical RF Performance @ $T_{AMB} = +25$ °C





- North America Tel: 800.366.2266 / Fax: 978.366.2266
- Europe Tel: 44.1908.574.200 / Fax: 44.1908.574.300
- Asia/Pacific Tel: 81.44.844.8296 / Fax: 81.44.844.8298 Visit www.macom.com for additional data sheets and product information.

ADVANCED: Data Sheets contain information regar Fine quedical (\(\frac{1}{2}\) \(\frac{1}{2}\) \(\frac{1}\) \(\frac{1}{2}\) \(


reasurements. Commitment to develop is not guaranteed.


PRELIMINARY: Data Sheets contain information regarding a product M/A-COM has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples and/or test data may be available. Commitment to produce in volume is not guaranteed.



V4

# Typical RF Performance @ T<sub>AMB</sub> = +25°C





**ADVANCED:** Data Sheets contain information regarding a product M/A-COM is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed.

PRELIMINARY: Data Sheets contain information regarding a product M/A-COM has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples and/or test data may be available. Commitment to produce in volume is not guaranteed.

- North America Tel: 800.366.2266 / Fax: 978.366.2266
- Europe Tel: 44.1908.574.200 / Fax: 44.1908.574.300
- Asia/Pacific Tel: 81.44.844.8296 / Fax: 81.44.844.8298
   Visit www.macom.com for additional data sheets and product information.

M/A-COM Inc. and its affiliates reserve the right to make changes to the product(s) or information contained herein without notice.

V4

#### **Device Installation Guidelines**

#### **Cleanliness**

These devices should be handled in a clean environment. The chips are resistant to solvents and may cleaned using approved industry standard practices.

#### Static Sensitivity

Aluminum Gallium Arsenide PIN diodes are ESD sensitive and can be damaged by static electricity. Proper ESD techniques should be used when handling these devices. These devices are rated Class 0, (0-199V) per HBM MIL-STD-883, method 3015.7 [C = 100pF ±10%, R = 1.5kW ±1%]. Even though tested die pass 50V ESD, they must be handled in a static-free environment.

#### **General Handling**

The devices have a polymer layer which provides scratch protection for the junction area and the anode air bridge. Die can be handled with plastic tweezers or picked and placed with a #27 tip vacuum pencil.

#### Assembly Requirements using Electrically Conductive Silver Epoxy and Solder

These chips are designed to be inserted onto hard or soft substrates with the junction side down. They should be mounted onto silk-screened circuits using electrically conductive silver epoxy, approximately 1-2 mils in thickness and cured at approximately 90°C to 150°C per manufacturer's schedule. For extended cure times, > 30 minutes, temperatures must be below 200°C.

#### **Eutectic Die Attached**

Tin rich solders (>30% Sn by weight) are not recommended as they will scavenge the gold on the contact Pads exposing the tungsten metallization beneath and creating a poor solder connection. Indalloy or 80/20, Au/Sn type solders are acceptable. Maximum soldering temperature must be kept below 280°C for less than 10 seconds.


#### Note:

The MA4AGSBP907 which is a solder bumped version of the MA4AGP907, is also available. The datasheet can be viewed on the M/A-COM website at: http://www.macom.com/DataSheets/MA4AGSBP907.pdf

# Ordering Information

Part Number	Packaging
MA4AGP907	Gel Pack
MADP-001907-13050P	Pocket Tape
Part Number	Packaging
MA4AGFCP910	Gel Pack
MADP-000910-13050P	Pocket Tape

# **Circuit Pad Layout**



development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed. **PRELIMINARY:** Data Sheets contain information regarding a product M/A-COM has under

ADVANCED: Data Sheets contain information regarding a product M/A-COM is considering for

development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples and/or test data may be available. Commitment to produce in volume is not guaranteed

North America Tel: 800.366.2266 / Fax: 978.366.2266

Europe Tel: 44.1908.574.200 / Fax: 44.1908.574.300

Asia/Pacific Tel: 81.44.844.8296 / Fax: 81.44.844.8298 Visit www.macom.com for additional data sheets and product information.