



HIGH PERFORMANCE THERMAL GREASE

Tgrease™ 300X is a silicone-based thermal grease for use in high performance CPU's and GPU's. Tgrease™ 300X has a high thermal conductivity of 3.0 W/mK and superior wetting characteristics, resulting in a very low thermal resistance and excellent long term reliability. Tgrease™ 300X has been formulated not to sag or drip with a high thixotropic index for ease of application and reliability.

FEATURES AND BENEFITS

- Low thermal resistance
- Excellent long term stability
- RoHS compliant
- Resists pump out through novel gel technology
- Available in 1kg (quart container), custom syringes

APPLICATIONS

- Computer CPUs and GPUs
- Telecommunications infrastructure
- Network Hardware
- Automotive electronics
- Consumer electronics

Typical Properties		Test Method
Color	Gray	Visual
Density	2.87 g/cc	Helium Pycnometer
Viscosity	400,000 cP	Brookfield DV-II Helipath Spindle T-F 20 RPMs
Thixotropic Index	3.35	Brookfield Viscometer RPMs
Thermal Resistance @ 50 psi @ 344.7 kPa	0.013°C-in ² /W 0.084°C-cm ² /W	ASTM D5470 (modified)
Thermal Conductivity	3.0 W/mk	Hot disk thermal constants analyzer
Bond Line Thickness	0.001 in, 25 microns	

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

STORAGE

Store between 15 and 45°C and a maximum humidity of 50%. Do not store in freezer or refrigerator below 5°C.

APPLICATION

Screen print using a mesh of 61 threads per inch (TPI) or less is recommended for easiest application, however the grease has been successfully applied using up to a 140 TPI mesh (The higher the number = smaller mesh opening). If applying from a can, mix can well prior to use. Dispense via syringe or cartridge by hand or mechanically.

Americas: +1.800.323.3757
LHP.Sales@lairdtech.com
Europe: +46.8.555.722.00
LHP.Sales@lairdtech.com
Asia: +86.10.5933.3682
LHP-ChinaSales@lairdtech.com

www.lairdtech.com

THR-DS-Tgrease-300X 0613

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user, since Laird Technologies and its agents cannot be aware of all potential uses. Laird Technologies makes no warranties as to the fitness, merchantability or suitability of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2013 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trade marks or registered trade marks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights. Document A16846-00 Rev B 06/2013