

THIS DRAWING IS UNPUBLISHED. RELEASED FOR PUBLICATION, 19 .
 © COPYRIGHT 19 BY AMP INCORPORATED. ALL RIGHTS RESERVED.


LOC	DIST	REVISIONS					
		P	LTR	DESCRIPTION	DATE	DWN	APVD
CE	16		E	REVISED PER 0A00-0067-00	08FEB2001	TA	SB

△1 COLOR LISTED IS AFTER CURE.

OBSOLETE	MANUFACTURING AND FIELD USE	ALL	15MIN 100C	2 HR	AMBER	25 2GR PKS	250	501195-7
OBSOLETE	FIELD USE OR WHEN A FAST CURE AT ROOM TEMP REQUIRED	FSMA	45MIN 25C	2 MIN	STRAW	25 2GR PKS	125	501195-6
OBSOLETE	FOR USE IN HIGH TEMP ENVIRONMENT	FSMA	15MIN 100C	40 MIN	AMBER	25 2GR PKS	250	501195-5
	MANUFACTURING AND FIELD USE	FSD, RSD, ST STYLE, FSMA	24HR 25C OR 2HR 65C	30 MIN	BLUE	25 2GR PKS	250	501195-4
OBSOLETE	FIELD USE OR WHEN A FAST CURE AT ROOM TEMP REQUIRED	FSMA	45MIN 25C	2 MIN	STRAW	10 2GR PKS	50	501195-3
OBSOLETE	FOR USE IN HIGH TEMP ENVIRONMENT	FSMA	15MIN 100C	40 MIN	AMBER	25 7GR PKS	500	501195-2
OBSOLETE	MANUFACTURING AND FIELD USE	FSD, RSD, ST STYLE, FSMA	24HR 25C OR 2HR 65C	30 MIN	BLUE	25 7GR PKS	500	501195-1
	APPLICATION	CONNECTOR TYPE	CURE TIME	POT LIFE	△1 COLOR	NO. OF PACKS WT. PER PACK	APPROX # OF CONNECTORS PER BOX	PART NUMBER

501195

B

<small>THIS DRAWING IS A CONTROLLED DOCUMENT FOR AMP INCORPORATED. IT IS SUBJECT TO CHANGE AND THE CONTROLLING ENGINEERING ORGANIZATION SHOULD BE CONTACTED FOR THE LATEST REVISION.</small>		DWN S.URICH 30NOV95 CHK R.RENN 30NOV95 APVD N.MILLER 30NOV95	AMP AMP Incorporated Harrisburg, PA 17105-3608
DIMENSIONS: mm 	TOLERANCES UNLESS OTHERWISE SPECIFIED: 0 PLC ±- 1 PLC ±- 2 PLC ±- 3 PLC ±- 4 PLC ±- ANGLES ±- FINISH -	PRODUCT SPEC - APPLICATION SPEC - WEIGHT -	ADHESIVE, EPOXY SIZE A2 CAGE CODE 00779 DRAWING NO. C-501195 SCALE 1:1 SHEET 1 OF 1 REV E
MATERIAL -		CUSTOMER DRAWING	