



Technical Data

3M™ Maintenance Sorbents

Use

For control of accidental and routine leaks, drips and spills of oils, lubricants and other non-aggressive liquids found commonly in industry. The sorbents are designed to help maintain a clean and safe working environment.

Product Description

3M™ Maintenance Sorbents are made from inert, synthetic fibers principally polypropylene and polyester. They are available in a wide range of formats and are lightweight and nominally dust-free. They have a high adsorption capacity which minimizes the amount of waste for disposal.

Color

Light grey (High Capacity pads and rolls), light grey with multi-colored material flecks (Medium Capacity pads and rolls). Medium Capacity appearance may vary due to recycle content used. Pads and rolls darken when wet as an indication of saturation level. Mini-booms and pillows are white with black print. Rugs are dark grey.

Selection Guide

- Drum covers - Rectangular pad with perforated circle designed to fit on top of 55 gallon drum.
- Folded - Combines four formats in one product. It is perforated every 16 inches (40 cm) and can be unfolded to be used as booms, pillows, sheets or rolls.
- Minibooms - Generally on-land applications to contain and adsorb spills.
- Pillows - Used for bulk absorption of oil on land or water. Particularly useful in drains to act as interceptors.
- Pads - A highly adaptable format. They can be used on water to pick up oil covering large surface areas and in wiping applications.
- Rolls - For fast coverage of large surface areas of water, they can be easily torn to length. Also used as a mat to keep shorelines or banks clean and to place used sorbents upon.
- Rugs - Absorbent rugs help keep floors clean and safe by absorbing oils and grease from shoes, equipment and vehicles.





Typical Liquids Adsorbed

3M™ Maintenance Sorbents are suitable for adsorbing oils, lubricants, petrol cutting fluids and coolants. They adsorb most liquids in the following chemical groups: alcohols, esters, halocarbons, hydrocarbons, silicones.

Liquids	Examples
Coolants/Heat Transfer Fluids	Water, Alcohol, Oils, Glycols
Lubricants	Oils, Water, Silicone Oils
Hydraulic Fluids	Hydraulic Oils, Water, Oil/Water Emulsions
Cutting Oils/Forming Fluids	Oils (mineral, emulsified)
Solvents	Turpentine, Toluene, Xylene, Paraffin
Crankcase Oils	Oils (natural, synthetic)

Limitations of Use

3M recommends that a compatibility test with the liquid of interest be carried out prior to using the sorbent. For use in temperature over 60C it is essential that such a compatibility test is made prior to use. Do not use on aggressive liquids, strong acids, caustic oxidizers or reactive chemicals. In particular there is a risk of degradation with the following: oleum, chlorosulfonic acid, liquid bromine, fuming nitric acid, chromic acid, sulfuric acid and hydrogen peroxide.

Precautions

3M™ Maintenance Sorbents are not in themselves hazardous products, however, they take on the characteristics of the liquids they adsorb. Adequate precautions should be taken when handling or storing hazardous / flammable materials and appropriate personal protective equipment should be worn. Users should be informed of the risks incurred in use, storage and disposal of used sorbents.

Disposal

Dispose of used sorbents only in accordance with local and national regulations. Disposal companies should be consulted for their recommendations.

Waste Minimization

3M recommends that waste streams should be minimized wherever possible. 3M sorbents promote minimization by only being a small part of the total waste. In addition where laws allow, 3M sorbents can be disposed of by incineration yielding less than 0.2% ash (ASTM D-482). The high energy value of the sorbents is also favorable for incineration and waste-to-fuel systems.

Sustainability

High Capacity sorbents contain at least 25% recycled content by weight. Medium Capacity sorbents contain at least 50% recycled content by weight.



Adsorption / Sorbency

The sorbent capacity quoted in the table below is based on testing per ASTM F 726 “Standard Test Method for Sorbent Performance of Adsorbents.” In brief, the sorbent samples were immersed in a “medium” density oil, drained and weighed. In the 1981 version of the standard, samples are immersed for a variable period of time in an attempt to make sure the sorbent is saturated. The sorbent is then drained horizontally. In the 2006 version of the standard, samples are immersed for 15 minutes and then most types are drained vertically. Capacity according to both versions of the standard is presented. Data presented are nominal; there will be variability in sorbent performance. Capacity and speed of adsorption will differ depending on the liquid’s polarity, surface tension and viscosity. Ambient temperature may also affect results. Therefore, results will vary by application.

Product Number	Size	Number / Case	Shipping Case Weight lb (kg)	Nominal capacity per case ASTM F 726-81 gallons (liters)	Nominal capacity per case ASTM F 726-06 gallons (liters)
Drum Cover					
M-DC22DD	26 in x 26 in (66 cm x 66 cm)	25	5 (2.3)	19 (72)	13 (49)
Folded					
M-FL550DD high capacity	5 in x 50 ft (12 cm x 15 m)	3	14 (6.4)	31.5 (119)	24 (90)
Minibooms					
M-MB304	3 in diameter x 4 ft (7.5 cm diameter x 121 cm)	12	13 (5.9)	12 (45)	13.5 (51)
M-MB308	4 in diameter x 8 ft (7.5 cm diameter x 243 cm)	6	13 (5.9)	12 (45)	13.5 (51)
M-MB312	4 in diameter x 12 ft (7.5 cm diameter x 365 cm)	4	13 (5.9)	12 (45)	13.5 (51)
Pillows					
M-PL715	7 in x 15 in (17 cm x 38 cm)	16	7 (3.2)	8 (30)	9 (34)
Pads					
M-PD720GG	7.5 in x 20.5 in (19 cm x 52 cm)	100	13 (5.97)	31.5 (119)	--
M-PD1520DD	15.5 in x 20.5 in (39 cm x 52 cm)	100	10 (4.5)	37.5 (142)	25 (94)
MCM medium capacity	15 in x 17 in (38 cm x 43 cm)	100	6 (2.8)	18 (68)	13.5 (51)
Rolls					
M-RL15150DD	15.5 in x 150 ft (39 cm x 45 m)	1	9 (4.1)	31 (117)	22 (83)
M-RL38150DD	38 in x 150 (96 cm x 45 m)	1	21 (9.5)	76 (287)	54 (204)
MCM medium capacity	15 in x 150 ft (38 cm x 45 m)	1	7 (3.1)	19 (72)	14 (53)
MCM medium capacity	25 in x 150 ft (63 cm x 45 m)	1	11 (5.1)	30 (114)	22 (83)
Rugs					
M-RG36300E	36 in x 300 ft (91 cm x 91 m)	1	55 (25.0)	32 (121)	--
M-RGC36100E with coating	36 in x 100 ft (91 cm x 30 m)	1	24 (10.9)	10.5 (39)	--



Important Notice to User:

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for user's particular purpose and suitable for user's method of application.

Warranty and Limited Remedy: 3M warrants that each 3M product will be free from defects in material and manufacture for 90 days from the date of purchase from 3M's authorized distributor. 3M MAKES NO OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a 3M product does not conform to this warranty, the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price. **Limitation of Liability:** Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted.



Commercial Solutions Division
St. Paul, MN 55144-1000
1-800-852-9722
www.3M.com/facility

NSF and the mark are registered trademarks of NSF International.
3M and Scotch-Brite are trademarks of 3M Company.
Used under license in Canada.
© 3M 2015. All rights reserved.
Celum ID# 787229

