



Inductors

RF chokes, HBC series

Series/Type: B82143A, B82143B

Date: March 2008


© EPCOS AG 2008. Reproduction, publication and dissemination of this publication, enclosures hereto and the information contained therein without EPCOS' prior express consent is prohibited.

HBC choke (High-Current Bobbin Core)

Rated inductance 1 H to 27 H

Rated current 850 mA to 2000 mA

- Ferrite drum core
- Winding: enamel copper wire
- Flame-retardant lacquer coating



B82143A Construction

Features

- Very high rated current
- Low DC resistance
- Suitable for wave soldering ■ RoHS-compatible

Applications

- Decoupling
- Interference suppression
- For electronic household appliances, automotive and entertainment electronics

Terminals

- Central axial leads (B82143A)
- Radially bent to 5 mm lead spacing (B82143B)
- Base material Cu
- Hot-dipped with pure tin

Marking

Inductance indicated by color bands to IEC 60062

Delivery mode and packing units

- Taped, Ammo and reel packing ■


Packing units:

	Ammo (pcs./pack.)	Reel (pcs./reel)
Axial	2500	5000
Radial	2500	2000

Dimensional drawings


B82143A (axial leads, taped)

Dimensions in mm



Minimum lead spacing 12.5 mm

Please read *Cautions and warnings* and *Important notes* at the end of this document.03/08



B82143B

Rated current I_R	Maximum permissible DC current at rated temperature
Inductance decrease $\Delta L/L_0$	$\leq 10\%$ (referred to initial value) at I_R , 20 °C
DC resistance R_{max}	Measured at 20 °C
Resonance frequency $f_{res,min}$	Measured with Agilent 4294A or 8753ES, 20 °C
Solderability (lead-free)	Sn95.5Ag3.8Cu0.7: (245 ±5) °C, (3 ±0.3) s Wetting of soldering area $\geq 90\%$ (to IEC 60068-2-20, test Ta)
Resistance to soldering heat	(260 ±5) °C, 10 s (to IEC 60068-2-20, test Tb)
Tensile strength of leads	≥ 20 N (to IEC 60068-2-21, test Ua)
Climatic category	55/125/56 (to IEC 60068-1)
Storage conditions	Mounted: -55 °C ... +125 °C Packaged: -25 °C ... +40 °C, $\leq 75\%$ RH
Weight	Approx. 0.38 g

⚠ Mounting information

When bending the leads, take care that the start-of-winding areas at the face ends (protected by glue and lacquer) are not subjected to any mechanical stress.

Characteristics and ordering codes

L_R μH	Tolerance ¹⁾	Q_{min}	f_Q MHz	I_R mA	R_{max} Ω	$f_{res, min}$ MHz	Ordering code ²⁾ (reel packing) ³⁾
1.0	$\pm 10\%$ $K_{\underline{\Delta}}$	50	7.96	2000	0.08	195	B82143+1102K000
1.2		50	7.96	1800	0.09	180	B82143+1122K000
1.5		50	7.96	1700	0.10	165	B82143+1152K000
1.8		50	7.96	1650	0.11	155	B82143+1182K000
2.2		50	7.96	1600	0.12	140	B82143+1222K000
2.7		50	7.96	1500	0.13	125	B82143+1272K000
3.3		50	7.96	1450	0.14	115	B82143+1332K000
3.9		50	7.96	1400	0.15	105	B82143+1392K000
4.7		50	7.96	1300	0.17	60	B82143+1472K000

¹⁾ Closer tolerances on request.

²⁾ Replace the + by code letter »A« for axial taping or by »B« for radial taping. ³⁾ For Ammo pack the last digit has to be a »9«. Example: B82143A1102K009


Please read *Cautions and warnings* and

Important notes at the end of this document.03/08


5.6	50	7.96	1250	0.19	45	B82143+1562K000
6.8	40	7.96	1200	0.22	35	B82143+1682K000
8.2	40	7.96	1150	0.24	25	B82143+1822K000
10	40	7.96	1100	0.25	21	B82143+1103K000
12	35	2.52	1050	0.27	17	B82143+1123K000
15	35	2.52	1000	0.30	16	B82143+1153K000
18	35	2.52	950	0.33	15	B82143+1183K000
22	35	2.52	900	0.37	13	B82143+1223K000
27	35	2.52	850	0.42	11	B82143+1273K000

HBC series, 4 9.2 (mm)


Impedance $|Z|$ versus frequency f
 measured with impedance analyzer Agilent 4294A or S-parameter network analyzer Agilent 8753ES, typical values at 20 °C




Inductance L versus DC load current I_{DC}
 measured with LCR meter Agilent 4284A, typical values at 20 °C



Q factor versus frequency f measured with impedance analyzer Agilent 4294A, typical values at 20 °C



Current derating I_{op}/I_R versus ambient temperature T_A (rated temperature $T_R = 40$ °C)



- Please note the recommendations in our Inductors data book (latest edition) and in the data sheets.
 - Particular attention should be paid to the derating curves given there.
 - The soldering conditions should also be observed. Temperatures quoted in relation to wavesoldering refer to the pin, not the housing.
- If the components are to be washed varnished it is necessary to check whether the washing varnish agent that is used has a negative effect on the wire insulation, any plastics that are used, or on glued joints. In particular, it is possible for washing varnish agent residues to have a negative effect in the long-term on wire insulation.
- The following points must be observed if the components are potted in customer applications:
 - Many potting materials shrink as they harden. They therefore exert a pressure on the plastic housing or core. This pressure can have a deleterious effect on electrical properties, and in extreme cases can damage the core or plastic housing mechanically.
 - It is necessary to check whether the potting material used attacks or destroys the wire insulation, plastics or glue.
 - The effect of the potting material can change the high-frequency behaviour of the components.
- Ferrites are sensitive to direct impact. This can cause the core material to flake, or lead to breakage of the core.
- Even for customer-specific products, conclusive validation of the component in the circuit can only be carried out by the customer.



RF chokes

B82143A, B82143B

HBC series, 4 9.2 (mm)

Please read *Cautions and warnings* and *Important notes* at the end of this document.

Important notes

The following applies to all products named in this publication:

1. Some parts of this publication contain **statements about the suitability of our products for certain areas of application**. These statements are based on our knowledge of typical requirements that are often placed on our products in the areas of application concerned. We nevertheless expressly point out **that such statements cannot be regarded as binding statements about the suitability of our products for a particular customer application**.

As a rule, EPCOS is either unfamiliar with individual customer applications or less familiar with them than the customers themselves. For these reasons, it is always ultimately incumbent on the customer to check and decide whether an EPCOS product with the properties described in the product specification is suitable for use in a particular customer application.

2. We also point out that **in individual cases, a malfunction of electronic components or failure before the end of their usual service life cannot be completely ruled out in the current state of the art, even if they are operated as specified**. In customer applications requiring a very high level of operational safety and especially in customer applications in which the malfunction or failure of an electronic component could endanger human life or health (e.g. in accident prevention or life-saving systems), it must therefore be ensured by means of suitable design of the customer application or other action taken by the customer (e.g. installation of protective circuitry or redundancy) that no injury or damage is sustained by third parties in the event of malfunction or failure of an electronic component.
3. **The warnings, cautions and product-specific notes must be observed.**



4. In order to satisfy certain technical requirements, **some of the products described in this publication may contain substances subject to restrictions in certain jurisdictions (e.g. because they are classed as hazardous)**. Useful information on this will be found in our Material Data Sheets on the Internet (www.epcos.com/material). Should you have any more detailed questions, please contact our sales offices.
5. We constantly strive to improve our products. Consequently, **the products described in this publication may change from time to time**. The same is true of the corresponding product specifications. Please check therefore to what extent product descriptions and specifications contained in this publication are still applicable before or when you place an order.

We also **reserve the right to discontinue production and delivery of products**. Consequently, we cannot guarantee that all products named in this publication will always be available.

The aforementioned does not apply in the case of individual agreements deviating from the foregoing for customer-specific products.
6. Unless otherwise agreed in individual contracts, **all orders are subject to the current version of the “General Terms of Delivery for Products and Services in the Electrical Industry” published by the German Electrical and Electronics Industry Association (ZVEI)**.
7. The trade names EPCOS, BAOKE, Alu-X, CeraDiode, CSMP, CSSP, CTVS, DSSP, MiniBlue, MKK, MLSC, MotorCap, PCC, PhaseCap, PhaseCube, PhaseMod, SIFERRIT, SIFI, SIKOREL, SilverCap, SIMDAD, SIMID, SineFormer, SIOV, SIP5D, SIP5K, ThermoFuse, WindCap are **trademarks registered or pending** in Europe and in other countries. Further information will be found on the Internet at www.epcos.com/trademarks.

03/09