3MHighland[™] Label Protection Tape

3565

Product Description	3M TM Highland TM Label Protection Tape 3565 has a clear, strong, moisture-resistant film backing and a strong adhesive that holds well to many treated and finished surfaces. It is used for the attachment and preservation of identifying labels in shipping, storage, and manufacturing applications.		
Construction	Backing	Adhesive	Colors
	3M [™] Scotchpro [™] polypropylene film	Pressure-sensitive synthetic rubber resin. Requires no moisture, heat, or solvent for activation.	Clear
Typical Physical Properties	Note: The following technical information and data should be considered representative or typical only, and should not be used for specification purposes. ASTM Test Method		
Properues			
rroperues	Adhesion to Steel:		
rroperues		AS	STM Test Method
rroperues	Adhesion to Steel: Tensile Strength: Longitudinal:	40 oz./in. width (44 N/100 mm width) 22 lbs./in. width (385 N/100 mm width)	D-3330 D-3759
rroperues	Adhesion to Steel: Tensile Strength: Longitudinal: Transverse: Elongation at Break: Thickness Total:	40 oz./in. width (44 N/100 mm width) 22 lbs./in. width (385 N/100 mm width) 44 lbs./in. width (770 N/100 mm width) 160% 1.9 mil (0.048 mm)	D-3330 D-3759 D-3759 D-3759 D-3759 D-3652
rroperues	Adhesion to Steel: Tensile Strength: Longitudinal: Transverse: Elongation at Break:	40 oz./in. width (44 N/100 mm width) 22 lbs./in. width (385 N/100 mm width) 44 lbs./in. width (770 N/100 mm width) 160%	D-3330 D-3759 D-3759 D-3759
Features	Adhesion to Steel: Tensile Strength: Longitudinal: Transverse: Elongation at Break: Thickness Total:	40 oz./in. width (44 N/100 mm width) 22 lbs./in. width (385 N/100 mm width) 44 lbs./in. width (770 N/100 mm width) 160% 1.9 mil (0.048 mm) 3000+ minutes	D-3330 D-3759 D-3759 D-3759 D-3759 D-3652
	Adhesion to Steel: Tensile Strength: Longitudinal: Transverse: Elongation at Break: Thickness Total: Shear Holding to Fiberboard:	40 oz./in. width (44 N/100 mm width) 22 lbs./in. width (385 N/100 mm width) 44 lbs./in. width (770 N/100 mm width) 160% 1.9 mil (0.048 mm) 3000+ minutes	D-3330 D-3759 D-3759 D-3759 D-3759 D-3652
	Adhesion to Steel: Tensile Strength: Longitudinal: Transverse: Elongation at Break: Thickness Total: Shear Holding to Fiberboard: • Adheres instantly to a variance.	40 oz./in. width (44 N/100 mm width) 22 lbs./in. width (385 N/100 mm width) 44 lbs./in. width (770 N/100 mm width) 160% 1.9 mil (0.048 mm) 3000+ minutes	D-3330 D-3759 D-3759 D-3759 D-3759 D-3652
	Adhesion to Steel: Tensile Strength: Longitudinal: Transverse: Elongation at Break: Thickness Total: Shear Holding to Fiberboard: • Adheres instantly to a var. • Edge tear and split resista.	40 oz./in. width (44 N/100 mm width) 22 lbs./in. width (385 N/100 mm width) 44 lbs./in. width (770 N/100 mm width) 160% 1.9 mil (0.048 mm) 3000+ minutes	D-3330 D-3759 D-3759 D-3759 D-3759 D-3652
	Adhesion to Steel: Tensile Strength: Longitudinal: Transverse: Elongation at Break: Thickness Total: Shear Holding to Fiberboard: • Adheres instantly to a var. • Edge tear and split resista. • Conformable backing.	40 oz./in. width (44 N/100 mm width) 22 lbs./in. width (385 N/100 mm width) 44 lbs./in. width (770 N/100 mm width) 160% 1.9 mil (0.048 mm) 3000+ minutes iety of surfaces. nce.	D-3330 D-3759 D-3759 D-3759 D-3759 D-3652
	Adhesion to Steel: Tensile Strength: Longitudinal: Transverse: Elongation at Break: Thickness Total: Shear Holding to Fiberboard: • Adheres instantly to a var. • Edge tear and split resista • Conformable backing. • Clear, strong, and moistur. • Good adhesion to fiberboard	40 oz./in. width (44 N/100 mm width) 22 lbs./in. width (385 N/100 mm width) 44 lbs./in. width (770 N/100 mm width) 160% 1.9 mil (0.048 mm) 3000+ minutes iety of surfaces. nce.	D-3330 D-3759 D-3759 D-3759 D-3759 D-3652

Highland™ Label Protection Tape

3565

Available Sizes	Standard Widths: Core Size (ID):	2.8 in., 3.8 in., 4.7 in., 5.7 in. (72 mm, 96 mm, 120 mm, 144 mm) 3 in.	
	Storage Conditions	Store in a clean, dry place. Temperature of 40-80°F (4-26°C) and 40-50% relative humidity are recommended.	
For Additional Information	To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit www.3M.com/packaging. Address correspondence to: 3M Industrial Adhesives and Tapes Division Building 21-1W-10, 900 Bush Avenue, St. Paul, MN 55144-1000. Our fax number is 651-778-4244. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00		

IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's application.

3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY

Limitation of Remedies and **Liability**

Important Notice

If the 3M product is proved to be defective, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.



This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9002 standards.



