

### Ceramic Plate Series Thermoelectric Cooler


The CP2-127-10-L-RT-W4.5 is a high-performance and highly reliable standard Thermoelectric Cooler. Assembled with Bismuth Telluride semiconductor material and thermally conductive Aluminum Oxide ceramics. It has a maximum Qc of 76.9 Watts when  $\Delta T=0$  and a maximum  $\Delta T$  of 70.5 °C at Qc = 0.

#### **Features**

- Compact geometric sizes
- DC Operation
- · RoHS-compliant

#### **Applications**

- Thermoelectric Coolers for Reagent Storage
- Thermoelectric Coolers for Handheld Cosmetic Lasers
- Cooling for Centrifuges
- Heads-Up Displays, Imaging Sensors
- Peltier Cooling for Machine Vision



CERAMIC MATERIAL: Al<sub>2</sub>O<sub>3</sub>


SOLDER CONSTRUCTION: 138°C, BiSn


INCHES [ MM ]


Note: Allow 0.020 in [0.5 mm] around perimeter of the thermoelectric cooler and lead wire attachment to accommodate sealant

## **ELECTRICAL AND THERMAL PERFORMANCE**


For maximum performance, be sure to orient the CONTROL side of the TEC against the application to be managed and the HEATSINK side against the heat sink or other heat rejection method. The CONTROL side is always opposite the side with lead attachments. Lead attachment is a passive heat loss and less impactful if located on the side that attaches to the heat exchanger.




























# **SPECIFICATIONS\***

**Hot Side Temperature** 

 $Qcmax (\Delta T = 0)$ 

 $\Delta T max (Qc = 0)$ 

Imax (I @ ATmax)

Vmax (V @  $\Delta$ Tmax)

**Module Resistance** 

**Max Operating Temperature** 

Weight

| 27.0 °C      | 35.0 °C    | 50.0 °C    |
|--------------|------------|------------|
| 76.9 Watts   | 79.2 Watts | 83.3 Watts |
| 70.5°C       | 73.5°C     | 78.8°C     |
| 9.3 Amps     | 9.2 Amps   | 9.1 Amps   |
| 13.9 Volts   | 14.4 Volts | 15.4 Volts |
| 1.39 Ohms    | 1.45 Ohms  | 1.56 Ohms  |
| 80 °C        |            |            |
| 76.0 gram(s) |            |            |

# **FINISHING OPTIONS**

| Suffix | Thickness                            | Flatness / Parallelism                         | <b>Hot Face</b> | Cold Face | <b>Lead Length</b>  |  |
|--------|--------------------------------------|--|-----------------|-----------|---------------------|--|
| L      | 5.588 ±0.254 mm<br>0.220 ± 0.0100 in | 0.004 mm / 0.004 mm<br>0.00015 in / 0.00015 in | Lapped          | Lapped    | 114.3 mm<br>4.50 in |  |

### **SEALING OPTIONS**

| Suffix | Sealant | Color                | <b>Temp Range</b> | Description                      |
|--------|---------|----------------------|-------------------|----------------------------------|
| RT     | RTV     | Translucent or White | -60 to 204°C      | Non-corrosive, silicone adhesive |

# **NOTES**

- 1. Max operating temperature: 80°C
- 2. Do not exceed Imax or Vmax when operating module
- 3. Reference assembly guidelines for recommended installation
- 4. Solder tinning also available on metallized ceramics

Any information furnished by Laird and its agents, whether in specifications, data sheets, product catalogues or otherwise, is believed to be (but is not warranted as being) accurate and reliable, is provided for information only and does not form part of any contract with Laird. All specifications are subject to change without notice. Laird assumes no responsibility and disclaims all liability for losses or damages resulting from use of or reliance on this information. All Laird products are sold subject to the Laird Terms and Conditions of sale (including Laird's limited warranty) in effect from time to time, a copy of which will be furnished upon request.

© Copyright 2019-2022 Laird Thermal Systems, Inc. All rights reserved. Laird  $^{™}$ , the Laird Ring Logo, and Laird Thermal Systems $^{™}$  are trademarks or registered trademarks of Laird Limited or its subsidiaries.

Revision: 00 Date: 06-01-2022

Print Date: 06-10-2022

<sup>\*</sup> Specifications reflect thermoelectric coefficients updated March 2020