

Datasheet revision 1.2

www.chipquik.com

Electronics Grade Silicone Adhesive Sealant (Clear) 20g Squeeze Tube

Product Highlights

Safe for use with Electronics Seals, Bonds, Encapsulates Resistant to Various Chemicals and Oils Non-Corrosive, Non-Conductive Flexible, Durable, Non-Degrading Withstands Moisture, Vibration, Abrasion



Common Uses

Protecting, Sealing and Insulating Corrosion Sensitive Electronic Components and Electrical Materials. OEM Commercial and Industrial Manufacturing for Flexible Permanent Bonding and Sealing.

Instructions

Surfaces should be clean and dry. Unscrew cap, cut the tip off. If tooling is required, do so within the first 10 minutes after dispensing. Apply the silicone to surfaces and remove the excess silicone after tooling with a dry clean cloth. Allow the silicone to cure completely. At room temperature, 25°C (77°F), and 50% relative humidity, the silicone will skin in 10 minutes and fully cure in 24 hours (1/8" bead). The silicone will reach its maximum adhesion in 7 days. Higher humidity accelerates curing.

Specifications

opoollioutiono	
Meets and Exceeds:	ASTM C920, UL Recognized
VOC:	VOC Compliant (< 3 %), Low Odor
Operating Temperature Range:	-57°C to +204°C (-70°F to +400°F)
Curing Time:	10 min (skin), 24 hours (full cure), 7 days (max adhesion)
Shore A Hardness:	30 +/-2
Tensile Strength (at Break):	250 +/- 25 psi
Elongation (at Break):	400 +/- 25 %
Tear Strength:	30 +/- 10 psi
Shrinkage (Weight Loss):	< 5 %
Adhesion Strength (Peel):	8 +/- 2 psi (primed aluminum), 10 +/- 2 psi (glass), 12 +/- 2 psi (primed mortar)
Joint Movement Capability:	+/- 25% (4:1 Safety Factor)
Dielectric Strength:	460 V/mil (18 kV/mm)
Dielectric Constant:	2.7 (at 50 Hz, 1 kHz, and 1 MHz)
Dissipation Factor:	0.0009 (at 50 Hz), 0.0004 (at 1 kHz), 0.0002 (at 1 MHz)
Volume Resistivity:	2 x 10^14
Surface Resistivity:	3 x 10^16
Color:	Clear
Size:	20g squeeze tube

Storage and Handling Store refrigerated or at room temperature 3-25°C (37-77°F).

Shelf Life >36 months

Transportation

This product has no shipping restrictions. Shipping below $0^{\circ}C$ ($32^{\circ}F$) or above $25^{\circ}C$ ($77^{\circ}F$) for normal transit times by ground or air will not impact this product's stated shelf life.