




### RockeTape™ Heat Resistant Thermal Tape RT-AZ Polyimide

#### Product Description

RT-AZ PI consists of a 165 micron (6.5 mil) AeroZero® polyimide aerogel film with a 25.4 micron (1 mil) external polyimide film joined with a 25.4 micron (1 mil) adhesive. The adhesive is a high-performance engineering grade silicone pressure sensitive adhesive (PSA) with a release layer that is peeled off before application to a substrate. Potential substrates include stainless steel, aluminum, glass, and polymer substrates such as polyimides, polyether ketones, polyurethanes, and polyesters. Typical use is thermal barrier/protection of parts in the Aerospace, Defense and Electronic industries.



#### Applications

Prior to peeling the release liner from the adhesive, ensure the surface is clean and free of loose particles. Standard application temperature is 25 °C (77 °F) and the recommended set time for optimal adhesion is 3 days prior to testing. The minimum application temperature is 10 °C (50 °F) and minimum set time is 24 hours before performing any tests. Increasing temperature and dwell time may increase adhesion strength.

#### Features

- ◇ Ultra-thin thermal protection system (TPS)
- ◇ Lightweight
- ◇ RF transparent
- ◇ Flexibility enables use on complex parts
- ◇ Easy application with permanent bonding
- ◇ Flame retardant

#### Uses

- ◇ Launch vehicle protection
- ◇ Supersonic munition and aircraft
- ◇ High performance race cars and boats

#### Standard Dimensions

- ◇ Standard Roll: 25 mm wide x 7.6 m long (1 in x 25 ft)

#### Storage

Recommended Storage Conditions:

- ◇ Temperature: below 25 °C (77 °F)
- ◇ Relative Humidity: below 50%



*Lighten. Protect. Perform.*



### RockeTape™ Heat Resistant Thermal Tape RT-AZ Polyimide Data

| Physical and Mechanical Properties | Method          | Value                |
|------------------------------------|-----------------|----------------------|
| Product Code                       | -               | 5010-11S1-251        |
| Thickness, μm (mil)                | In-House Method | 240 ± 38 (9.5 ± 1.5) |
| Tensile Strength, MPa (ksi)        | ASTM D882-12    | 15 ± 3 (2 ± 0.4)     |
| Young's Modulus, MPa (ksi)         | ASTM D882-12    | 450 ± 50 (65 ± 7)    |
| Tensile Elongation at Break, %     | ASTM D882-12    | 8 ± 2                |
| Density, g/cm <sup>3</sup>         | In-House Method | 0.58 ± 0.05          |

| Thermal Properties                     | Method        | Value         |
|--|---------------|---------------|
| Thermal Conductivity (25 °C), W/m·K    | ASTM C518-10  | 0.046 ± 0.003 |
| Specific Heat Capacity (25 °C), J/g·°C | ASTM C1784-20 | 1.22 ± 0.06   |
| IR Emissivity (Polyimide Surface)      | ASTM E408-13  | 0.85          |

| Thermomechanical Properties                              | Method        | Value     |
|--|---------------|-----------|
| Glass Transition Temp (AZ T <sub>g</sub> , DMA), °C (°F) | ASTM E1640-13 | 305 (580) |
| Decomposition Temp (10 wt% loss, TGA), °C (°F)           | ASTM 2550-17  | 410 (770) |

| Additional Properties              | Method     | Value      |
|------------------------------------|------------|------------|
| Adhesive Strength:                 |            |            |
| 180 °peel on Al Panel, N/m (lb/in) | ASTM D3330 | >200 (1.1) |
| UL Flammability Rating             | UL94 VTMO  | VTM-0      |

Data within this table are typical values for the polyimide product family.  
Product Code # 5010-11S1-251



Blueshift products are manufactured under a certified AS 9100D/ISO 9001:2015 Quality Management System facility. See our website for more information on Blueshift products.