
RTV Silicones





ALL MG PRODUCTS -

Jump to Product Number



Accessories

Adhesives

Brushes

Cleaners / Degreasers

Contact Cleaners

Desoldering Braid

Dusters & Circuit Coolers

EMI / RFI Shielding

Epoxies

Flux and Flux Remover

Glass & Screen Cleaners

Isopropyl Alcohol

Lead Free Solder

Lubricants

Potting & Encapsulating

Protective Coatings

<u>Pens</u>

Prototyping Materials

RTV Silicones

Soldering/desoldering

Specialized Cleaners

<u>Swabs</u>

Thermal Management

Thermally Conductive

Adhesives

Wipes

MOMENTIVE RTV Silicones by **(1)** 1-Part Adhesive Sealant RTV112



for RTV Silicones **2** 1-800-255-8886

Technical Support

M.G. Chemicals Disclaimer for RTV Silicones >

Locate Distributor >

Quick Links

- **MSDS**
- Specifications
- Available Sizes

Related products:



RTV118 Translucent

Resources

- ▶ Selection Guide ▶
- One Part Chart
- Two Part Chart

Find by Application

General Purpose

Aerospace >

Marine >

High Performance Assembly >

Electronics >

Thermal Conductivity >

High Temperature >

Low Temperature >



Google Search MG

Primary Characteristics ▶ White Flowable

▶ BUY NOW

- Acetoxy cure
- Food Applications
- ▶ FDA 21 CFR 177.2600

surface voids, self leveling protective coatings. Will flow into small crevices and hard to reach places. Not for use in delicate electrical and electronic applications in which corrosion of copper, brass, or other sensitive metals is undesirable. Can be used in food contact applications where FDA 21 CFR 177.2600 regulations apply. Reference CDS4319 "Food Contact Applications", "Silicone Rubber Compounds."

Excellent for thin section potting, filling small

Available Sizes

Catalog Number	Sizes Available	Description
RTV112-85ML	85 mL	Tube
RTV112-300ML	300 mL	Cartridge

Specifications

Use	Adhesive Sealant
Special Feature	High Performance
Standards	FDA 21CFR 177.2600
	MIL-A-46106, group 1, type 2
	UL File No. E-36952
NSN	8030-00-11-2763
Cross Reference	RTV118
Uncured Properties	
Consistency	Flowable
Color	White
Specific Gravity	1.05
Tack Free Time	20 min
Cure Through Time (77°F / 50% relative humidity / 1/8" thick)	24 hours
Cure Time (77°F/50% relative humidity)	3 days
Useful Temp. Range	-60°C to 205°C (-75°F to 400°F)
Cured Properties - MECHANICAL	
<u>Hardness</u>	25 (Shore A)
Tensile Strength	2.20 MPa (325 psi)
Elongation	325%
Peel Strength	3 kg/cm (15 lb/in)
Cured Properties - ELECTRI CAL	
Volume Resistivity	6 x 10 ¹⁴ ohm · cm
Dielectric Strength	16 kV/mm (400 V/mil)

Dielectric Constant	2.8 @ 60 Hz	
Cured Properties - THERMAL		
Thermal Conductivity	0.21 W/m · °K	
Brittle Point	-60°C (-75°F)	
Thermal Expansion	27 x 10 ⁻⁵ (°C) ⁻¹	
Other		
Viscosity (@ 25°C)	20,000 cps	

Return to top ^

© 2000 - 2007 MG Chemicals. All rights reserved. Site Map Terms & Conditions Contact Us

web site design by offbeat studio