SPECIFICATION CONTROL DRAWING

55A0816

WIRE, RADIATION-CROSSLINKED, MODIFIED ETFE-INSULATED, NORMAL WEIGHT, GENERAL PURPOSE, 600 VOLT

Date 1-12-17

Revision

Ν


This specification sheet forms a part of the latest issue of Raychem Specification 55A

PRIMARY INSULATION - RADIATION-CROSSLINKED,

MODIFIED ETFE

Primary insulation shall be of a contrasting

pigmentation to that of the jacket.



JACKET - RADIATION-CROSSLINKED, MODIFIED ETFE

TABLE I. CONSTRUCTION DETAILS									
	WIRE SIZE (AWG)	CONDUCTOR STRANDING (number x AWG)	DIAMETER OF STRANDED CONDUCTOR (inch)		FINISHED WIRE				
PART NUMBER <u>1</u> /					MAXIMUM RESISTANCE AT 20°C	DIAMETER (inch)	MAXIMUM WEIGHT		
			MINIMUM	MAXIMUM	(ohms/1000 ft.)	(5)	(lbs/1000 ft.)		
55A0816-26-*	26	19 x 38	.018	.020	49.4	.040 ± .002	1.70		
55A0816-24-*	24	19 x 36	.023	.025	30.1	.045 ± .002	2.30		
55A0816-22-*	22	19 x 34	.029	.031	18.6	.050 ± .002	3.30		
55A0816-20-*	20	19 x 32	.037	.040	11.4	.058 ± .002	4.80		
55A0816-18-*	18	19 x 30	.046	.051	7.1	.070 ± .003	7.70		
55A0816-16-*	16	19 x 29	.052	.058	5.5	.077 ± .003	9.50		

TABLE II. PERFORMANCE DETAILS									
PART NUMBER <u>1</u> /	MANDREL DIAMETE (inch) (± 3%)	R	WEIGHT (lb) (± 3%)						
	LIFE CYCLE, IMMERSION, AND ACCELERATED AGING	COLD BEND	LIFE CYCLE, IMMERSION, AND ACCELERATED AGING	COLD BEND					
55A0816-26-*	.375	1.00	.500	3.00					
55A0816-24-*	.500	1.00	.750	3.00					
55A0816-22-*	.500	1.00	1.00	3.00					
55A0816-20-*	.500	1.00	1.50	4.00					
55A0816-18-*	.750	1.50	2.00	4.00					
55A0816-16-*	1.00	1.50	2.00	5.00					

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.

Tyco Electronics Corporation also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.

Raychem, TE Connectivity, TE Connectivity (logo), and TE (logo) are trademarks

 ${\tt DIMENSIONS\ ARE\ IN\ INCHES\ AND,\ UNLESS\ OTHERWISE\ DESIGNATED,\ ARE\ NOMINAL.}$

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.



Raychem Wire & Cable 501 Oakside Avenue Redwood City, CA 94063-3800 Phone: 1-800-522-6752 Fax: 1-650-361-6297



SPECIFICATION CONTROL DRAWING

ge Revision SCD

2 of 2

Ν

55A0816

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 200°C

Maximum continuous conductor temperature VOLTAGE RATING: 600 volts (rms) at sea level

ACCELERATED AGING (CROSSLINKING PROOF): 300 ± 3°C for 7 hours

BLOCKING: 230 ± 3°C for 24 hours

COLOR: White preferred

CONCENTRICITY: 70% (minimum)

FLAMMABILITY: Procedure 1, 3 seconds (maximum), 3 inches (maximum);

no flaming of facial tissue

HUMIDITY RESISTANCE: Insulation Resistance, 5000 megohms for 1000 ft. (minimum)

IDENTIFICATION, COLOR STRIPING, AND BAND DURABILITY:

125 cycles (250 strokes) (minimum), 500 g weight

IMMERSION: Diameter increase 5% (maximum); no cracking, no dielectric breakdown

INSULATION ELONGATION AND TENSILE STRENGTH:

Elongation,

125% (minimum) for primary insulation

75% (minimum) for total insulation (primary insulation & jacket)

Tensile Strength,

5000 lbf/in² (minimum) for primary insulation

5000 lbf/in2 (minimum) for total insulation (primary insulation & jacket)

INSULATION FLAWS:

Primary Insulation,

Spark Test, 1.5 kV (rms) at 60 Hz; 4.2 kV (rms) at 3 kHz

Impulse Dielectric Test, 6.0 kV (peak)

Finished Wire.

Spark Test, 5.7 kV (rms) at 3 kHz

Impulse Dielectric Test, 8.0 kV (peak)

INSULATION RESISTANCE: 5000 megohms for 1000 ft. (minimum)

INSULATION THICKNESS:

0.003 in. (minimum) for primary insulation

0.004 in. (minimum) for outer jacket

0.009 in. (minimum) for total insulation

LIFE CYCLE: 230 ± 3°C for 500 hours

LOW TEMPERATURE-COLD BEND: -65 ± 3°C for 4 hours

SHRINKAGE: 230 ± 3°C for 6 hours, 0.125 in. (maximum) in 12 inches

SMOKE TEST: 250 ± 5°C, no visible smoke

SURFACE RESISTANCE: 500 meghoms-in. (minimum), both readings THERMAL SHOCK RESISTANCE: $200 \pm 3^{\circ}$ C, 0.060 in. (maximum) VOLTAGE WITHSTAND (Post Environmental): 2500 volts (rms), 60 Hz

WICKING: 2.25 in. (maximum)
WRAP TEST: 313 ± 3°C for 2 hours

1/ PART NUMBER:

The "*" in the part numbers in Tables I and II shall be replaced by a color code designator.

Example: AWG 22, white: 55A0816-22-9

AWG 22, white with a black stripe: 55A0816-22-90