

Tpcm[™] 580 Series Phase Change Material

Innovative **Technology** for a **Connected** World



FOR EXCEPTIONALLY LOW THERMAL RESISTANCE

The Tpcm[™] 580 Series is a high-performance thermal phase change material (PCM) designed to meet the thermal reliability and price requirements of high-end thermal applications. The Series is inherently tacky, flexible and exceptionally easy-to-use. The Tpcm 580 Series is available in four thicknesses: 0.003" (Tpcm 583), 0.005" (Tpcm 585), 0.008" (Tpcm 588), 0.010" (Tpcm 5810) and 0.016" (Tpcm 5816).

At temperatures above its transition temperature of 50°C (122°F), the Tpcm 580 Series begins to soften and flow, filling the microscopic irregularities of the components it comes into contact with. The result is an interface with minimal thermal contact resistance. Due to the gradual change in viscosity (softening), it minimizes migration (pump-out).

The Tpcm 580 Series can be supplied as cut parts in strips and rolls with top tabbed liners for easy application. The top tabbed liner can be removed immediately or provide a protective cover during shipping, and can be removed at assembly. It can also be supplied in sheets and custom die-cut configurations; and meets all environmental requirements including RoHS.

FEATURES AND BENEFITS

- Low total thermal resistance (0.013°C-in²/W at 50 psi)
- Inherently tacky and easy-to-use no adhesive required
- High reliability
- Meets all environmental requirements including RoHS
- Provides high value price / performance point

APPLICATIONS

- Microprocessors
- Chipsets
- Graphic processing chips
- Custom ASICS

global solutions: local support ...

Americas: +1.888.246.9050 Europe: +46.31.704.67.57 Asia: +86.755.2714.1166

CLV-customerservice@lairdtech.com www.lairdtech.com/thermal



Innovative **Technology** for a **Connected** World

Tpcm[™] 580 Series Phase Change Material

SPECIFICATIONS

PROPERTIES	Tpcm™ 583	Tpcm™ 585	Tpcm™ 588	Tpcm™ 5810	Tpcm™ 5816
Construction & composition	Non-reinforced film				
Color	Gray				
Thickness	0.003" (0.076 mm)	0.005" (0.127 mm)	0.008" (0.2 mm)	0.010" (0.25 mm)	0.016" (0.406 mm)
Density	2.87 g/cc				
Operating temperature range	-40°C to 125°C (-40°F to 257°F)				
Phase change softening temperature	50°C (122°F)				
Thermal resistance					
10 psi	0.019°C-in²/W (0.12°C-cm²/W)	0.020°C-in²/W (0.13°C-cm²/W)	0.020°C-in²/W (0.13°C-cm²/W)	0.020°C-in²/W (0.13°C-cm²/W)	0.025°C-in²/W 0.16°C-cm²/W)
20 psi	0.016°C-in²/W (0.10°C-cm²/W)	0.016°C-in²/W (0.10°C-cm²/W)	0.016°C-in²/W (0.10°C-cm²/W)	0.016°C-in²/W (0.10°C-cm²/W)	0.016°C-in²/W (0.10°C-cm²/W
50 psi	0.013°C-in²/W (0.08°C-cm²/W)	0.013°C-in²/W (0.08°C-cm²/W)	0.013°C-in²/W ((0.08°C-cm²/W)	0.013°C-in²/W (0.08°C-cm²/W)	0.013°C-in²/W (0.08°C-cm²/W)
Thermal conductivity	3.8 W/mK				
Volume resistivity	3.0 x 10 ¹² ohm-cm				

STANDARD PACKAGING

Sheets:	9″ x 9″ (228.6 mm x 228.6 mm)
	18" x 18" (457.2 mm x 457.2 mm)

Cut Parts: On strip with top tabbed liner Individual cut through

global solutions: local support...

Americas: +1.888.246.9050 Europe: +46.31.704.67.57 Asia: +86.755.2714.1166

CLV-customerservice@lairdtech.com www.lairdtech.com/thermal

THR-DS-TPCM580 1112

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user; since Laird Technologies and its agents cannot be aware of all potential uses. Laird Technologies makes no warranties as to the fitness, merchantability or suitability of any Laird Technologies materials or products for any specific or general uses. Laird Technologies makes a copy of which will be furnished upon request. © Copyright 2012 Laird Technologies, Inc. All Nights Reserved. Laird, Laird Technologies, the Laird Technologies, and other marks are tade marks or registred naternals of Echnologies (or on an affiliate company thereof). Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights. Document Al 6819-00 Rev A