# 8463A



## **Silver Grease**

8463A is a highly conductive electrical lubricant that uses a specially formulated silver-coated aluminum flake. It is a highly cost-effective alternative to silver-filled grease yet has superior electrical and thermal properties compared to carbon-based greases. It fills voids between adjoining parts, ensuring a continuous electrical path to enable the flow of current.

8463A is excellent for ground connections, rotating connections, rotary switches, variable capacitors, roller inductors, roller bearings, slip rings, slide connectors and potentiometers.

#### **Features & Benefits**

- Improves electrical connections between irregular and pitted surfaces
- · High service temperature range
- Prevents arching, pitting, hotspots, and welds
- · Inhibits corrosion
- · Reduces mechanical wear
- Compatible with metal, plastic, fiber, rubber, and more
- Superior electrical contact and environmental protection

#### **Available Packaging**

Cat. No.	Packaging	Net Vol.	Net Wt.
8463A-3ML	Syringe	3 mL	5.53 g

### **Contact Information**

MG Chemicals, 1210 Corporate Drive Burlington, Ontario, Canada L7L 5R6

Email: support@mgchemicals.com

Phone: North America: +(1)800-340-0772 International: +(1) 905-331-1396 Europe: +(44)1663 362888



# **Properties**

Color	Greyish yellow	
Filler	Silver-coated aluminum	
	alummum	
Base Material	Silicone oil	
Density	1.8 g/mL	
Resistivity	<0.2 Ω·cm	
Thermal Conductivity @ 25 °C	1.0 W/(m·	K)
Evaporation Loss, 22 h @ 165 °C	1.0 %	
Oil Separation, 30 h @ 165 °C	0.11 %	
Worked Penetration, ½ scale	335	
Resistance, 168 h @ 25 °C Distilled Water 50/50 Distilled Water/Ethanol	Pass Fail	
Service Temperature Range	-70–200 °C	
Shelf Life	5 y	

### **Storage and Handling**

Store between 0 and 30 °C in dry area to minimize settling (see SDS).

#### **Disclaimer**

This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.