



## FLEXO® WRAP

### FLEXIBLE MANAGEMENT WITH EASY ON, EASY OFF ACCESS EXPANDS TO FIT OVER INLINE CONNECTORS & SPLICES

Flexo® Wrap (FWN) is an exclusive product engineered and manufactured by Techflex®. FW provides the perfect solution to a wide variety of unique application challenges. The color matched hook and loop closure provides for easy on and off installation, as well as instant and convenient access for harness break-outs and rework of any specific section along the entire length of the run. Combined with the expandable, open weave design, FW will conform to a wide variety of bundle diameters and will wrap around irregular shapes.

#### SIZING CHART

Nominal Size	Part #	Hook & Loop Width	Recommended Applic. Diameter	*Put-Ups		Available Colors	Lbs/100'
				M	L		
½"	FWN0.50	¼"	½"	20'	100'	7	1.30
¾"	FWN0.75	⅝"	½"	15'	100'	7	1.80
1¼"	FWN1.25	⅝"	1"	12'	100'	7	2.30
2"	FWN2.00	⅝"	1¼"	10'	100'	7	3.20
2½"	FXN2.50BK	⅝"	–	10'	100'	BK	3.75

\*Put-Ups: "M" = Shop Spool and "L" = Bulk Spool



#### FEATURES

Material	Polyethylene Terephthalate
Grade	FWN
Monofilament Diameter	.010"
Drawing Number	TF001FWN-WD
Cutting	Hot Knife

#### COLORS



Black (BK), Gray (GY), Beige (BE), Platinum Gray (PG), White (WH),  
\*\*Orange (OR), \*\*Red (RD)

\*\* Custom Colors

#### CERTIFICATIONS





## ABRASION

Abrasion Resistance	<b>MEDIUM</b>
Abrasion Test Machine	Taber 5150
Abrasion Test Wheel	Calibrase H-18
Abrasion Test Load	500g
Room Temperature	70°F
Humidity	63%
Visible Hole Through	900 Test Cycles
Material Destroyed	
Pre-Test Weight	3,772.7 mg
Post-Test Weight	3,391.1 mg
Test End Loss Of Mass Point Of Destruction	381.6 mg

## PHYSICAL PROPERTIES

Monofilament Diameter (ASTM D-204)	.010"
Flammability Rating	UL94
Recommended Cutting	Hot Knife
Colors	7
Wall Thickness	.025"
Tensile Strength (Yarn) (ASTM D-2256 Lbs)	7.5
Specific Gravity (ASTM D-792)	1.38
Moisture Absorption % (ASTM D-570)	.1-2
Hard Vacuum Data (ASTM E-595 at 10-5 torr)	
TML	.19
CVCM	.00
WVR	.16
Smoke D-Max (ASTM E-662)	56
Outgassing	Medium
Oxygen Index (ASTM D-2863)	21

## FLAMMABILITY

Rating	UL94V0
--------	--------

## OPERATING TEMPERATURES

Melt Point (ASTM D-2117)	482°F / 250°C
Maximum Continuous (Mil-I-23053)	257°F / 125°C
Minimum Continuous (Mil-I-23053)	-94°F / -70°C

## CHEMICAL RESISTANCE

1=No Effect 2=Little Effect 3=Affected 4=More Affected 5=Severely Affected

Aromatic Solvents	2
Aliphatic Solvents	1
Chlorinated Solvents	3
Weak Bases	1
Salts	1
Strong Bases	2
Salt Water (O-S-1926)	1
Hydraulic Fluid (MIL-H-5606)	1
Lube Oil (MIL-L-7808)	1
De-Icing Fluid (MIL-A-8243)	1
Strong Acids	3
Strong Oxidants	2
Esters/Ketones	1
UV Light	1
Petroleum	1
Fungus (ASTM G-21)	1
Halogen Free	Yes
RoHS	Yes
SVHC	None