

**N<sub>60</sub><sup>TM</sup> 3.0V 3400F Cell**  
 NE03V03400SW001

# Datasheet


 See Note on Assembly Recommendations<sup>10</sup>
**DIMENSION & WEIGHT**

D1 (±0.5)	60.3 mm
D2 (±0.2)	60.3 mm
L (±0.3)	138.0 mm
H (±0.125)	3.0 mm
d (-0.05)	14.0 mm
Nominal Weight	500 g

**TYPICAL THERMAL CHARACTERISTICS**

Thermal Resistance, $R_{th}$ (Housing)	3.2 °C/W
Thermal Capacitance, $C_{th}$	580 J/°C
Usable Continuous Current ( $\Delta T = 15^\circ\text{C}$ ) <sup>9</sup>	140 A
Usable Continuous Current ( $\Delta T = 40^\circ\text{C}$ ) <sup>9</sup>	225 A

**ELECTRICAL SPECIFICATIONS**

Rated Voltage, $V_R$		<b>3.0 VDC</b>
Surge Voltage <sup>1</sup>		3.15 VDC
Rated Capacitance, $C^2$		<b>3400 F</b>
Capacitance Tolerance	Min. / Max.	3400F / 4080F
	Average <sup>4</sup>	3560F
Initial DC-ESR, $R_{DC}^3$	Max.	0.24 mΩ
	Average <sup>4</sup>	0.15 mΩ
Maximum Leakage Current <sup>5</sup>		12 mA
Maximum Peak Current, Non-repetitive <sup>6</sup>		2,800 A
Maximum Stored Energy, $E_{max}^7$		4.2 Wh
Gravimetric Specific Energy <sup>7</sup>		8.5 Wh/kg
Usable Specific Power <sup>7</sup>		9.0 kW/kg
Impedance Match Specific Power <sup>7</sup>		18.7 kW/kg

**TYPICAL LIFETIME CHARACTERISTICS**

DC Life at High Temperature <sup>8</sup> (Continuous charging at $V_R$ and 65°C)	1,500 hours
Projected DC Life at Room Temperature <sup>8</sup> (Continuous charging at $V_R$ and 25 ± 10 °C)	10 years
Projected Cycle Life at Room Temperature <sup>8</sup> (Cycled from $V_R$ to 1/2 $V_R$ using constant current of 100A at 25 ± 10 °C)	1,000,000 cycles
Shelf Life (Stored without charge at 25 ± 10 °C)	4 years

**TEMPERATURE SPECIFICATIONS**

Operating Temperature Range	-40 ~ 65°C
Storage Temperature Range (Stored without charge)	-40 ~ 70°C

**SAFETY & ENVIRONMENTAL SPECIFICATIONS**

Vibration	ISO 16750-3 Table 12 & 14
Shock	SAE J2464, IEC 60068-2-27
RoHS	Compliant
REACH	Compliant
UL	Compliant (UL 810A)


## NOTE

### 1. Surge Voltage

- > Absolute maximum voltage, non-repetitive. The duration must not exceed 1 second.

### 2. Rated Capacitance (Measurement Method)

- > Constant current charge with 5A to  $V_R$ .
- > Constant voltage charge at  $V_R$  for 5 min.
- > Constant current discharge with 5A to 0.1V.




$$C = \frac{I \times (t_2 - t_1)}{v_1 - v_2}$$

where  $C$  is the capacitance (F);

$I$  is the absolute value of the discharge current (A);  
 $v_1$  is the measurement starting voltage,  $0.8 \times V_R$  (V);  
 $v_2$  is the measurement end voltage,  $0.4 \times V_R$  (V);  
 $t_1$  is the time from discharge start to reach  $v_1$  (s);  
 $t_2$  is the time from discharge start to reach  $v_2$  (s)

### 3. Initial DC-ESR (Measurement Method)

- > Constant current charge with  $4 \times C \times V_R$  [mA] to  $V_R$ .  
*e.g. In case of 3V 3400F cell,  $4 \times 3400 \times 3 = 40,800 \text{ mA} = 40.8 \text{ A}$*
- > Constant voltage charge at  $V_R$  for 5 min.
- > Constant current discharge with 150A to 0.1V.



$$ESR_{DC} = \frac{\Delta v}{I}$$

where  $ESR_{DC}$  is the DC-ESR ( $\Omega$ );

$\Delta v$  is the voltage drop during first 10ms of discharge (V);  
 $I$  is the absolute value of the discharge current (A)

### 4. Average

- > Typical value or percentage spread that may be present in one shipment

### 5. Maximum Leakage Current (Measurement Method)

- > The capacitor is charged to its rated voltage  $V_R$  at 25°C.
- > Leakage current is the amount of current measured after 72 hours of continuous holding of the capacitor at  $V_R$ .

### 6. Maximum Peak Current

- > Current that can be used for 1-second discharging from the rated voltage to the half rated voltage under the constant current discharging mode

$$I = \frac{\frac{1}{2}V_R}{\Delta t / C + ESR_{DC}}$$

where  $I$  is the maximum peak current (A);  
 $V_R$  is the rated voltage (V);  
 $\Delta t$  is the discharge time (sec);  $\Delta t = 1$  sec in this case;  
 $C$  is the rated capacitance (F);  
 $ESR_{DC}$  is the maximum DC-ESR ( $\Omega$ )

- > The stated maximum peak current should **not** be used in normal operation and is only provided as a reference value.

### 7. Energy & Power (Based on IEC 62391-2)

- > Maximum Stored Energy,  $E_{max}$  (Wh) =  $\frac{\frac{1}{2}CV_R^2}{3600}$
- > Gravimetric Specific Energy (Wh/kg) =  $\frac{E_{Max}}{Weight}$
- > Usable Specific Power (W/kg) =  $\frac{0.12V_R^2}{ESR_{DC} \times Weight}$
- > Impedance Match Specific Power (W/kg) =  $\frac{0.25V_R^2}{ESR_{DC} \times Weight}$

### 8. DC Life and Cycle Life Test

- > End-of-Life (EOL) Conditions:
  - Capacitance: -20% from the rated minimum value
  - DC-ESR: +100% from the specified maximum initial value
- > Capacitance and ESR measurements are taken at 25°C.

### 9. Usable Continuous Current

- > Maximum current which can be used within the allowed temperature range under the constant current discharging mode

$$I = \sqrt{\frac{\Delta T}{R_{th} \times ESR_{DC}}}$$

where  $I$  is the maximum continuous current (A);  
 $\Delta T$  is the change in temperature (°C);  
 $R_{th}$  is the thermal resistance (°C/W);  
 $ESR_{DC}$  is the maximum DC-ESR ( $\Omega$ )

### 10. Assembly Recommendations

- > Assembly should be done in such way as not to place undue mechanical stress on the terminals of the cell.
- > Do not exceed the maximum torque value of 14 N-m when assembling threaded type cells.
- > Provide adequate spacing in between cells to secure required insulation strength for the application.
- > Provide sufficient clearance above the safety vent and do not position anything near the safety vent that may be damaged in an event of vent rupture.

The contents of this document are subject to change without notice. The values presented are thought to be accurate at the time of writing. Nesscap does not guarantee that the values are always error-free, nor does Nesscap make any other representation or warranty regarding the accuracy or credibility of the information contained in this document. For more information, please reach us at one of following contacts.



**Nesscap Energy Inc.**  
 Scotia Plaza  
 40 King Street West, Suite 5800  
 Toronto, Ontario, M5H 3S1  
 CANADA  
[marketing@nesscap.com](mailto:marketing@nesscap.com)



**Nesscap Energy Inc.**  
 24040 Camino Del Avion #A118,  
 Monarch Beach,  
 California, 92629  
 USA  
[marketing@nesscap.com](mailto:marketing@nesscap.com)



**Nesscap Co., Ltd.**  
 17, Dongtangiheung-ro 681beon-gil,  
 Giheung-gu, Yongin-si, Gyeonggi-do  
 (17102)  
 REPUBLIC OF KOREA  
[marketing@nesscap.com](mailto:marketing@nesscap.com)



**Nesscap China**  
 Room 1608-09, Anhui Building  
 Chuangzhan Center, No.6007 Shennan  
 Road, Futian District, Shenzhen City  
 CHINA  
[marketing@nesscap.com](mailto:marketing@nesscap.com)



**Nesscap Energy GmbH**  
 Beerengarten 4  
 D-86938 Schondorf  
 GERMANY  
[info@nesscap-energy.de](mailto:info@nesscap-energy.de)