




Specification for:
0W48613TC

110 Delta Drive
 Pittsburgh, PA 15238
 Phone: 412/696-1333
 Fax: 412/696-0333
 Email: magnetics@spang.com

DIMENSIONS



(mm)	Uncoated Nominal:	Min:	Max:
O.D. (A)	85.7	83.77	87.63
I.D. (B)	55.5	53.64	57.63
Ht. (C)	12.7	12.11	13.29

Eff. Parameters		
A _e mm ²	I _e mm	V _e mm ³
189	215	40582

INDUCTANCE

AL value (nH/T ²)	Test conditions
11040 ± 30%	10 kHz, 0.5 mT (For N = 5, use 1.0 mA), 25°C

ELECTRICAL LOSSES

tan δ / μ _i	Production lot limit Average	Test conditions	
≤ 4.1 · 10 ⁻⁶	≤ 3.5 · 10 ⁻⁶	10 kHz	0.5 mT, 25°C
≤ 60 · 10 ⁻⁶	≤ 50 · 10 ⁻⁶	100 kHz	

COATING

Uncoated

NOTE

Spec. Modifications	Previous	Revised
2006.01.13	LF: General W material	LF: Detail as indicated