

Jabil TPE-SEBS 1300 85A Filament

Technical Data Sheet

Product Description

TPE-SEBS 1300 85A 3D printing filament is a Shore 85A elastomer that does not require drying to process and has excellent bed adhesion and ease of printing. TPE-SEBS 1300 85A has low moisture absorption and has better elasticity for applications that require high flexibility and durability. It works on all open-platform direct drive 3D printers and can be run on desktop 3D Printers with PTFE Bowden Tubes. TPE-SEBS can stretch over 600% and is much easier to print than TPU filaments.

TPE-SEBS 85A can be used for parts that need elastomeric properties that can bend, flex and stretch without the need for a heated print bed and has demonstrated a very high success rate in printing complex geometries. TPE-SEBS is similar to rubber and other thermoplastic elastomers in its properties, soft to the touch while still being strong and flexible. It is well suited to printing parts that need to dampen vibrations or products that need to retain flexible properties under weather or heat exposure while still maintaining good elastic properties; such as seals, gaskets, no skid / no mark feet, soft touch grips for power tools, and no slip mats for auto interiors.



Advantages

The TPE-SEBS 85A is a soft material which is great for prototyping where rubber-like or elastomeric properties are required. Advantages of the TPE-SEBS include: low moisture absorption, high flexibility, less visible layer lines, and higher print success rate.

Storage and Use

Because the material is non-hygroscopic, there is no need to dry the filament during printing.

For the latest print profiles, search for Jabil Engineered Materials in the Cura Marketplace.

For complete copies of the Print Settings and the Printing & Drying Guide, visit our [TPE-SEBS 1300 85A Webpage](#).

Properties

Mechanical Properties¹

	Test Condition	Typical Value	Method
Tensile Modulus (MPa)	XY coupons, Ambient	19	ASTM D638, Type IV
Tensile Elongation at Break (%)		900	
Ultimate Tensile Strength (MPa)		6	
Compression Set (%)	XY coupons, Ambient	45	ASTM D395
Tear Strength (N/mm)	XY coupons, Ambient	66	ASTM D624
Durometer (Shore A)	Molded, Ambient	85	ASTM D2240

1. Testing conducted on printed coupons using Jabil's published print profiles. Typical values are for reference only.

Thermal Properties

	Test Condition	Typical Value	Method
Melt Temperature (°C)	20°C/min ramp	163	DSC

Other Physical Properties

	Test Condition	Typical Value	Method
Density (g/cm ³)	Ambient	1.056	ASTM D792

Dimensional Properties

	Test Condition	Typical Value	Method
Diameter: Mean, Indiv. Axis (mm)	In-line, 100% inspection	2.85	Laser Micrometer

Disclaimer: The information in this technical data sheet, including material properties, are obtained from testing representative samples under carefully controlled conditions and are provided for reference only. Material properties may be impacted by storage, handling, processing equipment/parameters, and product design, among other factors. The information is not a substitute for user testing to determine fitness for any specific use and the user is responsible for ensuring safe and lawful use of the product.

No express or implied warranties are provided and the implied warranties of merchantability or fitness for a particular purpose are expressly disclaimed. No representations are made, and no liability is assumed arising from or relating to the product.

Copyright/Trademark: © 2020 Jabil Inc. All rights reserved. JABIL® and the JABIL logo are registered trademarks of Jabil Inc.