

Technical Data Sheet

CR Technology offers a wide variety of thermally conductive pads also known as gap fillers. These materials are available in both silicone and non-silicone formulations.

EVERTHERM pads offer an endless range of thermal conductivity, softness and thickness, are naturally tacky and can be cut to any size or shape for easy installation





Material Properties

- · High thermal conductivity
- · Excellent flame retardant
- Good electrical insulation performance
- Good flexibility and high compression ratio

Applications

- ✓ Semiconductor heat sink
- ✓ Electric Vehicle (EV) Batteries
- Communication & power devises & modules
- ✓ LED lighting equipment
- Electronic components like: LEDs, CPUs, MOS • Mobiles, Laptops, Tablets



EVSF400

Color	Yellow	Visual
Thickness	1.0mm	ASTM D374
Specific Gravity	2.7g/cm3	ASTM D792
Thermal Conductivity	2.50 W/mk	ASTM D5470
Hardness(Shore oo)	30-90	ASTM D2240
Normal Hardness(Shore00)	40/60±5	ASTM D2240
Elongation	40%	ASTM D412
Tensile Strength	30psi	ASTM D412
Electricial Strength	>8000V/mm	ASTM D149
UL Flammability Rating	UL94 V-0	E355606
Volume resistivity	1*1013Ω.cm	ASTM D257
Operating Temperature	-50 - 200°C	——
Thermal Resistance(1mm,@30psi)	0.5°C*in2/W	ASTM D5470
Compression Ratio(1mm,@30psi)	30%	
Dielectric Constant@1 MHz	7.0	ASTM D150
RoHS	PASS	IEC 62321
Halogen	PASS	EN14582
REACH	PASS	EN14372

Standard Sheet Size (Note: Other sheet sizes may be available upon request.)

200 x 300mm

Test fixtures using ASTM D5470. Recorded values include interface thermal resistance. These values are for reference only. The actual application performance is directly related to the applied surface roughness, flatness and pressure.

CR Technology, Inc

- 55 Chase St. Methuen, Massachusetts 01844
- ignition is a sales@crtechinc.com
- 978.681.5300

