



VHB™ Tapes GPH Series

Product Data Sheet

February 2017
Supersedes: August 2016

Product Description

3M™ VHB™ Tape GPH Series, a general-purpose, high temperature, grey, conformable, double-coated, acrylic foam tape with a high initial tack and a soft foam. Available in three different thicknesses with a 3M branded red siliconised polyethylene film liner.

Key Features

- Double-coated acrylic foam tape
- 100% closed-cell acrylic foam
- High-temperature performance (short term 230°C)
- Good balance of high temperature and peel & shear performance
- High initial tack
- Soft foam enables stress relaxation & an easy application
- Good sealing properties
- For indoor and outdoor applications

Applications & Benefits

- 3M™ VHB™ Tapes GPH Series temperature performance enables bonding of materials in applications with high operating temperatures such as prior to processing in a powder coating line
- Capability to bond to a variety of substrates makes 3M™ VHB™ Tapes GPH Series a good fit for multi-material bonding – those substrates have a high or medium surface energy including many metals (e.g. stainless steel) and plastics (e.g. Polyamide, PMMA, ABS)
- For applications in metal working, signage, applications and specialty vehicles

Physical Properties

	3M™ VHB™ Tapes GPH Series GPH-060GF	3M™ VHB™ Tapes GPH Series GPH-110GF	3M™ VHB™ Tapes GPH Series GPH-160GF
Adhesive Type	Acrylic foam adhesive		
Thickness acc. to ASTM D-3652	0.60 mm	1.10 mm	1.60 mm
Foam Density	710 kg/m ³		
Release Liner	3M branded red siliconised polyethylene film		
Tape Colour	Grey		

Performance Characteristics

Type	GPH-060GF	GPH-110GF	GPH-160GF
90° Peel adhesion to Stainless Steel acc. to ASTM D3330, 90° peel angle @ RT, after 72h @ RT dwell	25 N/cm	37 N/cm	34 N/cm
90° Peel adhesion to Polyamide 6 acc. to ASTM D3330, 90° peel angle @ RT, after 72h @ RT dwell	33 N/cm	48 N/cm	55 N/cm
90° Peel adhesion to ABS acc. to ASTM D3330, 90° peel angle @ RT, after 72h @ RT dwell	21 N/cm	33 N/cm	32 N/cm
90° Peel adhesion to PMMA acc. to ASTM D3330, 90° peel angle @ RT, after 72h @ RT dwell	21 N/cm	34 N/cm	37 N/cm
Dynamic Shear acc. to ASTM D1002 on stainless steel, after 72h @ RT dwell	547 N/6.54 cm ²	476 N/6.54 cm ²	375 N/6.54 cm ²
Static Shear Strength acc. to ASTM D3654, after 72h @ RT dwell (Weight held for 10.000 minutes to stainless steel, 3.32 cm ² (0.5 in ²))	23°C – 1000 g 150°C – 500 g		
Normal Tensile (T-Block) acc. to ASTM D897 to Aluminium @ RT, after 72h @ RT dwell, 6.45 cm ² , test speed 50 mm/min	410 N/6.54 cm ²	439 N/6.54 cm ²	470 N/6.54 cm ²
Temperature Performance	Short term (minutes, hours): 230°C Long term (days, weeks): 150°C		

Application Temperature

Ideal application temperature range is 21°C to 38°C. Pressure-sensitive adhesives use viscous flow to achieve substrate contact area. To obtain good performance with all 3M™ VHB™ Tapes, it is important to ensure that the surfaces are clean, dry and free of condensed moisture.

Shelf Life

24 months from date of production when stored at 16°C – 25°C and 40-65% relative humidity.

Performance of tapes is not projected to change even after shelf life expires; however, 3M does suggest that 3M™ VHB™ Tapes are used prior to the shelf life date whenever possible.

Important Notice

PRODUCT USE: All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application. **WARRANTY AND LIMITED REMEDY:** 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product packaging, package inserts, price pages, or 3M product literature. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is proved defective, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to repair or replace the product or refund the purchase price. **LIMITATION OF LIABILITY:** Except to the extent prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes.



3M Industrial Adhesives and Tapes Division
3M Canada
300 Tartan Drive
London, ON N6A 4T1
P.O. Box 5757

Phone 1-800-364-3577
Web 3M.ca/VHB

3M and VHB are trademarks of 3M. Used under license in Canada. © 2017, 3M. All rights reserved.
Printed in Canada. Please recycle. 170408525 E BA-17-23638