

DURA FLEX

INDUSTRIAL HOSE AND CABLE PROTECTION FOR HARSH ENVIRONMENTS DEFLECTS HIGH PRESSURE HOSE RUPTURES · RESISTS SNAGGING

The tightly woven nylon makes Dura Flex the perfect solution for hose & cable protection. The .045 inch wall thickness will protect cables, hoses and ropes from weather, sunlight and abrasion damage. When installed over uncoated cable or chains, DF will prevent scraping, chafing and contact damage to painted or other fragile surfaces. DF is resistant to chemicals, UV damage and rot, and is suitable for continuous outdoor use under all weather conditions. The flexible sleeving cuts with a scissor and the tight construction slides easily over any application.

SIZING CHART

Nominal	Dout #	Wall	*Put-Ups		Available	Lbs/	
Size	Part #	Thickness	M	L	XL	Colors	100'
0.71	DFN0.71BK	.045"	50'	100'	300'	1	2.57
0.83	DFN0.83BK	.045"	50'	100'	300'	1	2.58
0.92	DFN0.92BK	.045"	50'	100'	300'	1	3.22
1.00	DFN1.00BK	.045"	50'	100'	300'	1	3.66
1.13	DFN1.13BK	.045"	50'	100'	300'	1	4.18
1.25	DFN1.25BK	.045"	50'	100'	300'	1	4.49
1.34	DFN1.34BK	.045"	50'	100'	300'	1	4.84
1.59	DFN1.59BK	.045"	50'	100'	300'	1	5.37
1.75	DFN1.75BK	.045"	50'	100'	300'	1	6.13
2.07	DFN2.07BK	.045"	50'	100'	300'	1	7.26
2.38	DFN2.38BK	.045"	50'	100'	300'	1	8.28
2.54	DFN2.54BK	.045"	50'	100'	300'	1	8.98
2.86	DFN2.86BK	.045"	50'	100'	300'	1	9.89
3.34	DFN3.34BK	.045"	25'	50'	300'	1	11.59
3.66	DFN3.66BK	.045"	25'	50'	300'	1	12.25

*Put-Ups: "M" = Shop Spool, "L" = Bulk Spool, and "XL" = Maxi Coil



FEATURES

Material	Nylon
Grade	DFN
Wall Thickness	.045"
Drawing Number	TF001DF-WD
Cutting	Scissors

COLORS



Black (BK)

CERTIFICATIONS





ISO MSHA 6945







ABRASION

Abrasion Resistance Abrasion Test Machine Abrasion Test Wheel Abrasion Test Wheel Abrasion Test Load Room Temperature Humidity Visible Wear& Some Pulling Of Fibers Material Wearing Through At Seam Material Destroyed Pre-Test Weight Post-Test Weight Test End Loss Of Mass Point Of Destruction Taber 5150 Calibrase H-18 Abrasion Test Meight 70% 500 Test Cycles 2,750 Test Cycles 7,191.6 mg 6,680.7 mg 510.9 mg		
Abrasion Test Wheel Calibrase H-18 Abrasion Test Load 500g Room Temperature 80°F Humidity 70% Visible Wear& Some Pulling Of Fibers 500 Test Cycles Material Wearing Through At Seam 2,750 Test Cycles Material Destroyed 3,500 Test Cycles Pre-Test Weight 7,191.6 mg Post-Test Weight 6,680.7 mg Test End Loss Of Mass Point Of 510.9 mg	Abrasion Resistance	VERY HIGH
Abrasion Test Load 500g Room Temperature 80°F Humidity 70% Visible Wear& Some Pulling Of Fibers 500 Test Cycles Material Wearing Through At Seam 2,750 Test Cycles Material Destroyed 3,500 Test Cycles Pre-Test Weight 7,191.6 mg Post-Test Weight 6,680.7 mg Test End Loss Of Mass Point Of 510.9 mg	Abrasion Test Machine	Taber 5150
Room Temperature 80°F Humidity 70% Visible Wear& Some Pulling Of Fibers 500 Test Cycles Material Wearing Through At Seam 2,750 Test Cycles Material Destroyed 3,500 Test Cycles Pre-Test Weight 7,191.6 mg Post-Test Weight 6,680.7 mg Test End Loss Of Mass Point Of 510.9 mg	Abrasion Test Wheel	Calibrase H-18
Humidity 70% Visible Wear& Some Pulling Of Fibers 500 Test Cycles Material Wearing Through At Seam 2,750 Test Cycles Material Destroyed 3,500 Test Cycles Pre-Test Weight 7,191.6 mg Post-Test Weight 6,680.7 mg Test End Loss Of Mass Point Of 510.9 mg	Abrasion Test Load	500g
Visible Wear& Some Pulling Of Fibers 500 Test Cycles Material Wearing Through At Seam 2,750 Test Cycles Material Destroyed 3,500 Test Cycles Pre-Test Weight 7,191.6 mg Post-Test Weight 6,680.7 mg Test End Loss Of Mass Point Of 510.9 mg	Room Temperature	80°F
Material Wearing Through At Seam 2,750 Test Cycles Material Destroyed 3,500 Test Cycles Pre-Test Weight 7,191.6 mg Post-Test Weight 6,680.7 mg Test End Loss Of Mass Point Of 510.9 mg	Humidity	70%
Material Destroyed 3,500 Test Cycles Pre-Test Weight 7,191.6 mg Post-Test Weight 6,680.7 mg Test End Loss Of Mass Point Of 510.9 mg	Visible Wear& Some Pulling Of Fibers	500 Test Cycles
Pre-Test Weight 7,191.6 mg Post-Test Weight 6,680.7 mg Test End Loss Of Mass Point Of 510.9 mg	Material Wearing Through At Seam	2,750 Test Cycles
Post-Test Weight 6,680.7 mg Test End Loss Of Mass Point Of 510.9 mg	Material Destroyed	3,500 Test Cycles
Test End Loss Of Mass Point Of 510.9 mg	Pre-Test Weight	7,191.6 mg
510 9 mg	Post-Test Weight	6,680.7 mg
		510.9 mg

PHYSICAL PROPERTIES

Monofilament Diameter (ASTM D-204)	NA
Flammability Rating	
Recommended Cutting	Scissors
Colors	1
Wall Thickness	.045"
Tensile Strength (Yarn) (ASTM D-2256 Lbs)	
Specific Gravity (ASTM D-792)	1.14
Moisture Absorption % (ASTM D-570)	2.7
Hard Vacuum Data (ASTM E-595 at 10-5 torr)	
TML	1.1
CVCM	.01
WVR	.69
Smoke D-Max (ASTM E-662)	
Outgassing	High
Oxygen Index (ASTM D-2863)	22

FLAMMABILITY

Rating

OPERATING TEMPERATURES

Melt Point (ASTM D-2117)	410°F / 210°C
Maximum Continuous (Mil-I-23053)	248°F / 120°C
Minimum Continuous (Mil-I-23053)	-49°F / -45°C

CHEMICAL RESISTANCE

1=No Effect 2=Little Effect 3=Affected	4=More Affected 5=Severely Affected
Aromatic Solvents	1
Aliphatic Solvents	1
Chlorinated Solvents	1
Weak Bases	1
Salts	1
Strong Bases	2
Salt Water (0-S-1926)	1
Hydraulic Fluid (MIL-H-5606)	1
Lube Oil (MIL-L-7808)	1
De-Icing Fluid (MIL-A-8243)	1
Strong Acids	5
Strong Oxidants	5
Esters/Ketones	1
UV Light	2
Petroleum	3
Fungus (ASTM G-21)	2
Halogen Free	Yes
RoHS	Yes
SVHC	

www.TECHFLEX.com