

TECHNICAL DATA SHEET

Thermoplastic Elastomer TPE

General notes:

- » TPE Olefinic Thermoplastic Elastomer, Permanent Antistatic
- » Soft Plastic, was developed in order to achieve a surface resistance 10⁸-10⁹ Ohm in order to minimize the possibility of charge generation by wearing
- » ESD Protection





Mechanical properties

Tensile strength
Tensile elongation
Hardness, Shore

2 MPa 10 +% 65-75 A

ISO 527 ASTM D 638 ISO 527 ASTM D 638 D-785

Polypropylen compound PP

General notes:

- » PP polypropylene-compound
- » Hard Plastic, its function is to ground the metal tool (through the operators hand and the ESD wrist strap)
- » ESD Protection





Mechanical properties

Tensile strength at break (5mm/min)
Elongation at break (5mm/min)
Tensile modulus +23°C
Tensile strength +23°C
Izod-Impact strength (notched) +23°C

20 MPa >10% 1650 MPa 190 MPa 13 kJ/m ISO 527 ASTM D 638 ISO 179/2C

Thermal properties

Temp. of defl. under load (1.80 MPa) VICAT softening point B (49 N) 56 °C 70 °C ISO 75 ASTM D 648 ISO 306

Other properties

Density 0.97 g/cm³

ISO 1183

This document contains information based on average values as obtained from the results of laboratory tests and observations made on the material. Ideal-tek SA declines all responsibility from an improper use of the product described in this document.