

- Shrink Temperature 212°F (100°C)
- Ideal Finish For Cosmetic Applications
- Heat Resistance Up To 221°F (105°C)
- Excellent Oil, Moisture, And Fungus Resistance
- Easily Installs Over Connectors And Splices



Material Polyvinyl Chloride

Grade H2P

				- rut	oh?		
Nominal Size	Part #	Unshrunk Diameter /mm	Shrunk Diameter /mm	Put-Ups		Available	Lbs/
				Bulk Spool	Shop Spool	Colors	100′
1/16″	H2P0.06	1.6	0.8	1,000'	100'	2	0.20
1/4″	H2P0.25	6.4	3.2	250′	25′	2	0.60
5/16″	H2P0.31	8.0	4.0	250′	25′	2	0.70
3/8″	H2P0.38	9.5	4.8	250′	25′	2	0.80
1/2″	H2P0.50	12.7	6.4	250′	25′	2	1.10
5/8″	H2P0.63	15.9	7.9	250′	25′	2	1.16
3/4″	H2P0.75	19.1	9.5	250′	25′	2	1.90
1″	H2P1.00	25.4	12.7	250′	25′	2	3.00
1 1/2″	H2P1.50	38.1	19.1	100′	25'	2	5.30
2″	H2P2.00	50.8	25.4	100′	25′	2	8.02
2 1/2″	H2P2.50CL	63.5	31.8	100′	25′	Clear CL	9.45
3″	H2P3.00CL	76.2	38.1	50′	25′	Clear CL	18.00

Put-lins -

PVC 2:1 Heatshrink Tubing Shrinks To ½ its original diameter!


PVC tubing is a Polyvinyl Chloride heatshrink tubing that shrinks to ½ its original diameter. During the shrinking operation, the tubing will encapsulate any device inside of it at the time and will assume the contour of that device.

Ultra clear PVC heatshrink tubing is ideal for application where complete transparency is required. Perfect for protecting exposed wires and cables on motorcycles and custom automobiles.

Resists gasoline, oil, and common chemicals; provides protection from abrasion and severe environments.

Perfect tubing for application where complete transparency is required.













Moisture Absorption % ASTM	D-5700.5	5
Flammability Rating	Self-Extinguishing VW- ⁻	1



Corrosion MIL-I-23053

No Corrosion





Measure the Shrinkflex[®] tubing to length and cut with a scissor. The thickness of your bundle, as well as the desired final appearance, will determine the length of the tubing you

cut. Generally, a piece 1 1/2" - 2" long will accommodate almost any need. Single wires, or smaller bundles, require shorter pieces.



Slip the Shrinkflex[®] tubing over the bundle and position it so that both the sleeved and unsleeved portions are suf-

ficiently covered. Notice the small pieces of tubing installed on single wires as part of a color coding system. If your project requires multiple operations, always work up from the smallest to the largest bundle.



Gently apply heat to Shrinkflex[®] tubing from a heat gun, hair dryer or torch with an appropriate attachment. Keep the

heat source far enough away so that hot metal or direct flame does not come in contact with the tubing, wires or sleeving. Move the heat around the bundle to prevent damaging the sleeving and to ensure that all areas of the tubing have been shrunk. Once cooled, your installation is complete.

PHYSICAL **PROPERTIES**

Recommended Cutting	Scissors
Stock Colors	2
Tensile Strength PSI ASTM D-638	3,000
Elongation % ASTM D-638	300
Specific Gravity ASTM D-792	1.32
Deformation % (250°F/121°C, 1 Hr.) MIL-I-23053	50
Heat Shock (250°F/121°C, 1 Hr.) <i>MIL-I-23053</i>	_No Cracking
Cold Bend (14°F/-10°C, 1 Hr.) <i>MIL-I-23053</i>	_No Cracking
Flexibility <i>MIL-I-23053</i>	_No Cracking
Secant Modulus PSI ASTM D-882	19,500
Longitudinal Shrinkage (%)	15
Dielectric Strength (volts/mil) ASTM D-876_	1,083
Volume Resistivity (ohm-cm) ASTM D-876	21.5 x 10 ¹²

© 2021 Techflex[®] - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex[®] is strictly forbidden. Techflex[®] product names and logos are registered trademarks of Techflex[®], unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex[®] makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex[®]'s only obligations are those in standard terms of sale for these products and Techflex® will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications. 08-26