

Tack Flux in 2cc Squeeze Tubes - Sample Pack of 4 Different Fluxes

Product Highlights

Sample pack allows easy testing to find the best flux for your application
 Ideal for all rework, solder, de-solder and reflow applications
 Tack flux will not run all over PCB when applied
 Excellent wetting
 Long stencil life
 Wide process window
 Clear residue
 Can be used with Leaded and Lead-Free applications

RoHS 3 and REACH compliant



Representative Photo Only
 Please note flux color may vary from light yellow to orange/brown

Contains

SMD291	No-Clean Paste Flux - For Rework/Solder/Desolder
SMD291NL	No-Clean Paste Flux - For Lead-Free Applications
SMD4300	Water-Washable No-Clean Paste Flux
SMDLT	No-Clean Paste Flux - For Low Temperature
Flux Activation Temperatures:	SMDLT: 100°C (212°F)
	SMD291, SMD291NL, SMD4300: 140°C (284°F)
Colors:	Light yellow to orange/brown
Packaging:	2cc/2g Squeeze Tube x 4
Shelf Life:	Refrigerated >24 months, Unrefrigerated >24 months

Stencil Life

>8 hours @ 20-50% RH 22-28°C (72-82°F)
 >4 hours @ 50-70% RH 22-28°C (72-82°F)

Stencil Cleaning

Automated stencil cleaning systems for both stencil and misprinted boards. Manual cleaning using isopropyl alcohol (IPA).

Storage and Handling

Store refrigerated or at room temperature 3-25°C (37-77°F). Do not freeze. Allow 4 hours for flux to reach an operating temperature of 20-25°C (68-77°F) before use.

Transportation

This product has no shipping restrictions. Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.

Conforms to the following Industry Standards:

J-STD-004B, Amendment 1 (Solder Fluxes):	Yes
RoHS 3 Directive (EU) 2015/863:	Yes