# 3M<sup>™</sup> Embedded Capacitance Material (ECM)

### **Utilize a Proven Solution**


- A UL certified and RoHS<sup>2</sup> compliant laminate with high capacitance density that can be embedded into PCBs and chip packages as either a power ground plane or a discrete capacitor
- Consists of a very thin layer of ceramic-filled epoxy sandwiched between two layers of copper foil
- Compatible with a large range of PCB material sets and with standard PCB fabrication and assembly processes, including lead-free
- Halogen-free<sup>3</sup> versions available along with a variety of panel sizes and copper thicknesses
- In production in telecom, computer, test and measurement, military/ aerospace, medical and consumer electronics applications


# Simplify Design while Amplifying Performance


- Increases usable board area by allowing for the removal of many, if not all, capacitors equal to or below 0.1 µF and their associated solder joints and vias
- Improves power integrity by reducing power bus noise and PCB impedance
- Reduces EMI by decreasing resonance that causes EMI
- Dissipates heat better than thin FR-4 due to high thermal conductivity and low thermal impedance

# **Enable Product Roadmaps**

- Simplify board layout and routing
- Reduce PCB size, thickness and weight
- Add functionality on fixed form factors
- · Lower spreading inductance
- Decrease need for EMC measures such as metal shells, tapes, etc.
- Reduce interference from digital circuits to analog/RF circuits in mixed signal applications
- Add PCB layers while maintaining similar PCB thickness
- Reduce design spins by solving noise issues early in the design cycle
- Improve PCB panel utilization
- Improve assembly yields and board reliability due to fewer components









### 3M™ Embedded Capacitance Material (ECM)

Property	Test Method	C0614	C1012	C2006
Capacitance/Unit Area (1 kHz)	Supplier Method	6.4 nF/in² (1.0 nF/cm²)	10.0 nF/in² (1.6 nF/cm²)	20.0 nF/in <sup>2</sup> (3.1 nF/cm <sup>2</sup> )
Dielectric Thickness	Cross-section	14 µm (0.55 mils)	12 μm (0.47 mils)	6 μm (0.24 mils)
Copper Type	Supplier Method	RA	ED or RA	RA
Copper Thickness	Cross-section	35 µm	35 μm (ED/RA) or 17 μm (ED)	35 μm RA
Capacitance Tolerance	Supplier Method	+/- 10%	+/- 10%	+/- 10%
Dielectric Constant (1 kHz)	Supplier Method	16	22	22
Dissipation Factor (1 kHz)	Supplier Method	0.005	0.010	0.010
Temperature Coefficient of Capacitance (TCC)	Supplier Method	Meets X7R requirements		
Dielectric Strength (Volts/Mil)	ASTM D149	3300	3000	3000
HiPOT Voltage	IPC-TM-650 2.5.7.2	100 V	100 V	50 V
UL Flammability Rating	UL 94	94 V-0		
UL Relative Thermal Index (RTI)	UL 796	130°C	90°C⁴	90°C⁴
UL Solderability Limits	UL 796	288°C/30 sec.	288°C/20 sec.	288°C/20 sec.
Glass Transition Temperature	Supplier Method (DSC)	120°C		
Moisture Absorption (wt %)	ASTM D570	0.11	0.10	0.10
CTE (ppm/C)	Supplier Method (TMA)	32 (x,y,z)	31 (x,y,z)	31 (x,y,z)
Degradation Temperature	IPC-TM-650 2.3.40	345°C	375°C	375°C
Peel Strength (pli)	IPC-TM-650 2.4.9 modified	4.0	6.0 (ED)/4.0 (RA)	4.0 (RA)
Thermal Conductivity (W/m*K)	ASTM F433 modified	0.5		
Halogen Content (ppm)	BS EN 14582:2007	<400	None Detected	

<sup>1)</sup> All test data provided are typical values and not intended to be specification values.

For more information, please visit our website to learn more: www.3Mcapacitance.com

3M is a trademark of 3M Company.

#### **Important Notice**

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product which are not contained in 3M's current publications, or any contrary statements contained on your purchase order shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

#### Warranty; Limited Remedy; Limited Liability.

This product will be free from defects in material and manufacture for a period of one year from the time of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.



<sup>2) &</sup>quot;RoHS 2011/65/EU" means that the product or part does not contain any of the substances in excess of the maximum concentration values ("MCVs") in EU RoHS Directive 2011/65/EU. The MCVs are by weight in homogeneous materials. This information represents 3M's knowledge and belief, which may be based in whole or in part on information provided by third party suppliers to 3M. In the event any product is proven not to conform with 3M's Regulatory Information Appendix, then 3M's entire liability and Buyer's exclusive remedy will be in accordance with the Warranty stated

<sup>3)</sup> Halogen Free is defined as both 1) no halogen compounds that are intentionally added to the product or used in the manufacturing process for the product and 2) any impurities present are less than 900 ppm bromine, less than 900 ppm chlorine and/or less than 1500ppm total bromine and chlorine. The latter are the levels set forth in certain industry standards for printed circuit boards, such as the International Electrotechnical Commission (IEC) 61249-2-21 standard. This information represents 3M/s knowledge and belief which may be based in whole or in part on information provided by 3rd party suppliers to 3M.

<sup>4)</sup> Epoxy default RTI temperature.