

Datasheet revision 1.2

www.chipquik.com

RMA Tack Flux (for Leaded) in a 10cc syringe w/plunger & tip

Product Highlights Tack Flux Rosin Mildly Activated (RMA) Used for touch up and rework, attachment of BGA spheres, and soldering flip chip components. Low viscosity synthetic **RoHS 3 and REACH compliant**



<u>Representative Photo Only</u> Please note flux color may vary from light yellow to orange/brown

Specifications

Flux Type: Flux Classification: Flux Activation Temperature: Color: Packaging: Shelf Life: Synthetic RMA (for Leaded applications) ROL0 140°C (284°F) Light yellow to orange/brown 10cc/10g Syringe Refrigerated >24 months, Unrefrigerated >24 months

Stencil Life >8 hours @ 20-50% RH 22-28°C (72-82°F) >4 hours @ 50-70% RH 22-28°C (72-82°F)

Stencil Cleaning Automated stencil cleaning systems for both stencil and misprinted boards. Manual cleaning using isopropyl alcohol (IPA).

Storage and Handling Store refrigerated or at room temperature 3-25°C (37-77°F). Do not freeze. Allow 4 hours for flux to reach an operating temperature of 20-25°C (68-77°F) before use.

Transportation

This product has no shipping restrictions. Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.

Conforms to the following Industry Standards: J-STD-004B, Amendment 1 (Solder Fluxes): RoHS 3 Directive (EU) 2015/863:

Yes Yes