



CORE DIMENSIONS					
UNCOATED CORE			35T0231-100		
	MM	INCHES		MM	INCHES
OD	5.84	(.230)	±	.15	(.006)
ID	3.05	(.120)	±	.13	(.005)
TH	3.05	(.120)	±	.13	(.005)
PARYLENE			35T0231-10Q		
OD	5.89	(.232)	±	.15	(.006)
ID	3.00	(.118)	±	.13	(.005)
TH	3.10	(.122)	±	.13	(.005)

INITIAL PERMEABILITY 5000  
 WEIGHT / K 0.64 LBS



ELECTRICAL SPECIFICATION								
	MIN	MIN TOL.	NOM	MAX	MAX TOL.	FREQ.	VOLT.	URNS
	(μH)		(μH)	(μH)		(kHz)	(V)	
L	1.586	(-20%)	1.983	2.380	(+20%)	100	≤ .00091	1
Q	10		-	-		100	≤ .00091	1

COATING SPECIFICATIONS				
	TYPE	coating thickness (mils.)	Min. DLB VAC	TEST FORCE (LB)
35T0231-100	UNCOATED	-	-	-
35T0231-10Q	PARYLENE	1.0	1500	0.30

NOTES:

Rev	Description	Date	INT
A	Original Draft	10/6/2005	JRK
B	REVISED TEMPLATE	4/25/2006	WMM

Date: 4/25/06	DWG #	35T0231-10Q-B	Rev:
Drawn By: WMM	Title #	35T0231-10Q	B

**Steward** This document contains information which is proprietary to Steward. No production or publication of this document in whole or in part shall be made without written authorization from Steward.

UNCONTROLLED DOCUMENT